



Bhagyanagar Gas Ltd.

BHAGYANAGAR GAS LIMITED

(A JOINT VENTURE OF HPCL & GAIL)

BID DOCUMENT FOR

**PROCUREMENT OF STEEL PIPELINES IN HYDERABAD
GA**

UNDER OPEN DOMESTIC

COMPETITIVE BIDDING

e- tender

Bid Document No.: BGL/719/2025-26

VOLUME-II of II

CONTENTS

INDEX

<u>SL.NO.</u>	<u>DESCRIPTION</u>	<u>PAGE NO.</u>
1.0	MATERIAL REQUISITION	03 to 13
2.0	STANDARD SPECIFICATION FOR ERW LINE PIPES	14 to 45
3.0	STANDARD SPECIFICATION FOR 3LPE COATING OF LINE PIPES	46 to 98
4.0	STANDARD SPECIFICATION REPAIR POLYTHYLENE COATING	99 to 105
5.0	ITP- ERW PIPES	106 to 114
6.0	ITP -RAW MATERIAL(HR COIL/ PLATES)	115 to121
7.0	ITP-3 LPE COATING OF LINEPIPES	122 to 130
8.0	CHECKLIST	131
9.0	REFERENCE LIST FOR SUPPLY OF LINE PIPE	132
10.0	COMPLIANCE STATEMENT	133
11.0	REFERENCE LIST OF SUPPLY OF STEEL COIL	134
12.0	DEVIATION SHEET	135
13.0	INSTRUCTION TO BIDDER	136
14.0	VENDOR DRAWINGS / DOCUMENT SCHEDULE	137
15.0	DOCUMENTATION REQUIREMENTS	138 to 147
16.0	QMS	148 to 156
17.0	LIST OF ACCEPTABLE STEEL PLATE & COIL	157 to 160
18.0	MILL CAPABILITY CERTIFICATION	161 to 168
19.0	LIST OF AUTHORIZED TPI AGENCY	169 to 169



BHAGYANAGAR GAS LIMITED (BGL)

PROCUREMENT OF STEEL PIPELINES IN BGL's HYDERABAD GA

MATERIAL REQUISITION



PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Volume II
of II

Bid Document No. BGL/719/2025-26

TABLE OF CONTENTS

1.0	INTRODUCTION	3
2.0	PURPOSE	3
3.0	DEFINITIONS	3
4.0	DOCUMENT PRECEDENCE	3
5.0	SCOPE OF SUPPLY	4
6.0	DESIGN DATA	4
7.0	DOCUMENTS & DATA REQUIREMENTS	7
8.0	LIST OF ATTACHMENTS	11

1.0 INTRODUCTION

BGL was incorporated to implement City Gas Distribution (CGD) projects in the erstwhile Andhra Pradesh region, which now includes Andhra Pradesh and Telangana. The company serves the geographical areas of Hyderabad, Vijayawada, and Kakinada. Furthermore, BGL operates 137 CNG stations in these cities across Andhra Pradesh and Telangana.

2.0 PURPOSE

This document is for Procurement, Manufacturing, Testing & Inspection, Packing & Forwarding, Transportation, Unloading and Stacking of 3LPE coated Carbon Steel Pipe at BGL Site/store to be used in City Gas Distribution Project in Hyderabad, Vijayawada, and Kakinada as per the tender terms & conditions.

3.0 DEFINITIONS

Where used in this document, the following terms shall have the meanings indicated below, unless clearly indicated by the context to this order

PROJECT	City Gas Distribution
OWNER	Bhagyanagar Gas Limited (BGL)
CONSULTANT	VCS Quality Services Private Limited (VCSQSPL) the party to act for and on behalf of OWNER for the EPMC Services.
MANUFACTURER	The party, which manufactures and supplies equipment and services to the OWNER or to Contractor
MR	Material Requisition

4.0 DOCUMENT PRECEDENCE

It shall be the responsibility of the MANUFACTURER/ VENDOR to inform the PURCHASER of any errors, ambiguities, inconsistencies, discrepancies or conflict of information that may be found to exist in any document, specification or drawing submitted by the PURCHASER.

In case of conflict, the order of precedence shall be as follows:

- a. MR
- b. Basic Documents (Specifications)
- c. Codes and Standards

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

As a general rule in the event of any discrepancy between technical matter and local laws/ regulations (and documents above listed) the most stringent shall be applied.

MANUFACTURER/ VENDOR shall notify PURCHASER of any apparent conflicts between MR, specifications, related datasheets, any code and standards and any other specifications noted herein. (Resolution and/ or interpretation precedence shall be obtained from PURCHASER in writing before proceeding with the design/ manufacturer or completion of services.)

5.0 SCOPE OF SUPPLY

The scope of supply covers Design, Manufacturing, Inspection, Testing, coating of 3LPE and Transportation of Carbon Steel Line Pipes to BGL Site/Store at Hyderabad, Vijayawada, and Kakinada as per detail given below:

SIZE (Inch)	THK. (mm)	MATERIAL (PSL-2)	EXTERNAL COATING	METHOD	QTY (mtrs)
HYDERABAD					
12"	6.4	API 5L Gr. X-52	3LPE	ERW	2000
10"	6.4	API 5L Gr. X-52	3LPE	ERW	9000

The above quantities are indicative. Purchaser reserves the right to increase or decrease the quantity at the time of award. Bidder has to quote for full quantity, else the bid shall be liable for rejection.

6.0 DESIGN DATA

Description	Value
Product	Natural Gas
Design Pressure (Maximum)	49 Kg/cm ²
Material Specification	API 5L Gr. X-52
Corrosion Protection	3 Layer PE coated

NOTES:

- 1.0 Negative tolerance on Pipe wall thickness is not acceptable. Negative Tolerance if specified in Standard Specification shall not be considered and shall be superseded by this MR.
- 2.0 Overall length tolerance shall be (-) Zero and (+) One pipe length to complete the ordered quantity.
- 3.0 Pipe Manufacturer shall furnish valid license to use API monogram on API 5L Line pipes – Product Specification Level 2 (PSL-2) quality for the

Bid Document No. BGL/719/2025-26

proposed pipe mill(s) along with the offer. The submitted API license shall be valid throughout the manufacturing period till completion of order.

- 4.0 Steel shall be procured from approved steel mill only.
- 5.0 Charpy impact test shall be carried out at (-) 29°C.
- 6.0 Quantity may vary \pm 5% for coated pipe. Final quantity will be informed to successful bidder during placement of order.
- 7.0 Mill Hydro test shall be carried out at 95% of SMYS.
- 8.0 Pipes length shall be as per Clause 9.11.3.3 of line Pipe Specification
- 9.0 External Coating:
- Supply of all coating material as per specification (VCS-SS-PP-2003) for carrying out 3LPE coating. The minimum thickness of finished coating shall be as per aforesaid specification.
 - The bidder's proposed coating raw material supplier(s) shall be manufacturer of the materials meant for the three-layer side extruded polyethylene coating of pipes. They must have manufactured and supplied the offered grades of materials within the last seven years reckoned from the bid due date. These manufacturer(s) shall be evaluated at the bid stage and the bidder shall submit necessary letter of authorization and confirmation (as applicable) from such proposed manufacturer(s). Bidder offer shall be unconditional irrespective of the finally qualified raw material manufacturer(s).
 - Cleaning and surface preparation of pipes, application of 3-layer side extruded polyethylene coating on line pipes, carrying out inspection and testing, repairing of coating defects, re-testing, any cutting of pipes for the purpose of PQT or regular production testing, carrying out re-beveling and all associated works after cutting etc. and carrying out all coating works as per specification no VCS-SS-PP-2003. Application shall also include coating of pipes of non-standard lengths obtained in case of cutting of bare pipes necessitated for removal of dents/defects.
- 10.0 Handling, loading, transportation, unloading, Stacking/Storing of coated pipes to designated storage yards, any material requirement for stacking, all necessary arrangement shall be in bidder scope.
- 11.0 Bidder shall inspect of all coated line pipes in presence of Owner representative while handing over of pipes. Holiday inspection for visually damaged, coating damaged pipes etc. shall be carried out by bidder while handing over of pipes. Repair of damaged pipes, beveled end defects and damaged coating (including supply of coating materials for repair) noticed at the time of handing over of coated pipes. All handling, lifting tools etc. required for inspection of coated pipes at Storage Yards shall be carried out by the bidder.
- 12.0 Pipe Internal Diameter inspection by Pull through (95% of ID) shall be carried out by bidder during handling over pipes to owner.
- 13.0 Pipe roughness shall be 40 Micron.

- 14.0 For butt weld end, bevel shall be in accordance with API specification 5L.
- 15.0 Both pipe ends of each pipe shall be provided with metallic or high impact plastic bevel protectors/end cap as per Manufacturer's standard. Bevel protectors/end shall be of a design such that they can be re-used by coating applicator for providing on externally anticorrosion coated pipes subsequent to coating of line pipe. The details of the bevel protector/end caps shall be furnished for approval prior to start of the production.
- 16.0 Plastic push fit types end caps shall be installed on all small diameter pipe ends.
- 17.0 All major damage to pipe ends/ bevels, including dents or gauges, shall be repaired by removal of damaged pipe material and rebeveling. No welding on the pipe surface shall be allowed. If owner get a defective pipe & the pipe is un-acceptable to owner, then that pipe shall be replaced by supplier without any extra cost.
- 18.0 Inspection of Field Test and Warranty
- Purchaser shall be reimbursed by Manufacturer for any pipe furnished on this order that fails under field hydrostatic test if such failure is caused by a material/manufacturing defect in the pipe. The reimbursement cost shall include pipe, labor and equipment rental for finding, excavating, cutting out, installation of replaced pipe in position, all incidental expenses and administrative costs. The field hydrostatic test pressure will not exceed that value which will cause a calculated hoop stress equivalent to 95 percent of specified minimum yield strength
- In case Manufacturer so desires, he will be advised at least two weeks in advance so that his representative may witness the hydrostatic test in field, however, the testing and leak (if any) finding and repair operation shall not be postponed because of absence of the Manufacturer's Representative.
- 19.0 Bidder shall furnish quotation only in case he can supply material strictly as per this MR and specification forming part of MR.
- 20.0 Indicative ITP for line pipe & Coating is enclosed with MR/Tender. Minimum inspection and testing requirement of the line pipes shall be governed by attached ITP with Tender. Vendor shall submit their ITP after award for approval covering the requirement specified in tender ITP.
- 21.0 All items shall be provided with EN 10204, 3.2 Certification. Inspection of Steel Plate/Coil/Billet required for manufacturing of Line Pipe shall also be 3.2 certified as per EN 10204. To carrying out inspection as per EN 10204, 3.2 certification, Vendor shall appoint TPIA from the attached TPIA list at bidder's own cost.
- 22.0 Color bands of 50 mm width to be placed at both the ends, inside of Bare Pipes at a distance of 150 mm from the pipe ends and outside of 3LPE Coated Pipes at a distance of 450 mm from the pipe ends.
- 23.0 White Band marking inside for all the items.
- 24.0 Bidder shall submit Forms for Check List (FORM-A), Reference list for

Supply of line pipe (FORM-B), Compliance statement (FORM-C), Reference list for Supply of steel (FORM-D), Deviation Sheet, duly filled, signed and stamped along with the bid. Bidder to note that previous track record shall be filled up in Form of reference list only, with all details as required in attached format. Track records in the other formats are not acceptable.

- 25.0 Pipes shall be ordered only to Specified grade as in MR/SOR. Intermediate grades shall not be acceptable. Higher grade pipe shall not be considered as a substitute for a pipe ordered without CONSULTANT/ BGL prior approval.
- 26.0 The manufacturer shall be required to establish and maintain quality assurance system in accordance with ISO: 9001 or equivalent. CONSULTANT/ BGL reserve the right to audit manufacturer's quality system.
- 27.0 If the offer contains any technical deviations or clarifications or stipulates any technical specifications (even if in line with MR requirements) and does not include complete scope & technical/ performance data required to be submitted with the offer, the offer shall be liable for rejection.
- 28.0 The submission of prices by the Bidder shall be construed to mean that he has confirmed compliance with all technical specifications of the corresponding item(s).
- 29.0 Inspection and tests performed/witnessed by purchaser's inspector shall in no way relieve the manufacturer's obligation to perform the required inspection and test.
- 30.0 Bidder must submit all documents/ drawings/ calculations as specified in relevant specification along with his offer and after award of order.
- 31.0 Purchaser's inspector reserves the right to perform stage wise inspection and witness tests, as indicated in specification at manufacture's works prior to shipment. Manufacturer shall give reasonable notice of time and shall provide without charge reasonable access and facilities require for inspection to the purchaser's inspector. Inspection and tests performed/witnessed by purchaser's inspector shall in no way relieve the manufacturer's obligation to perform the required inspection and test.

7.0 DOCUMENTS & DATA REQUIREMENTS

The table hereunder specifies the quantities and the nature of the documents to be submitted by the Manufacturer to the PMC.

The documents required at the inquiry stage and to be included in the bid are listed under column A.

The documents required after award of the AGREEMENT and subject to the written approval of the PMC are listed under column B.

The final and certified documents are listed under column C.

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Volume II
of II

Bid Document No. BGL/719/2025-26

Any document, even when preliminary, shall be binding and therefore duly identified and signed by the Manufacturer. It shall bear the PMC Project reference, the Material Requisition number and the identification number.

The documents are fully part of the supply which shall be complete only if and when the documents complying fully with the material requisition requirements are received by the engineer.

Item	Documents and Data	A	B		C	
		Number of copies	Number of copies	Required date	Number of copies	Required date
1.	Drawing/data submittal list and schedule	3	4	1 week + monthly	4	2 weeks after approval
2.	Production, test and delivery schedule (per item)	--	4	1 week + monthly	4	2 weeks
3.	Progress report	--	4	Daily + weekly + monthly	--	--
4.	Catalogues / References	3	--	--	--	--
5.	Description of application and quality with technical data of 3LPE for external coating	3	4	3 weeks	4	2 weeks after approval + with final techn. File
Item	Documents and Data	A	B		C	
		Number of copies	Number of copies	Required date	Number of copies	Required date
6.	Code compliance certificate (Quality manual, ISO certificate,	3	4	3 weeks	4	2 weeks after approval



PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Volume II
of II

Bid Document No. BGL/719/2025-26

	API License)						
7.	QA/QC program (First Day Production + Regular production separately)	--	4	2 weeks	4	2 weeks after approval	
8.	Inspection and test procedures	--	4	3 weeks	3	2 weeks after approval + with final techn. file	
9.	A description with calculation for handling, storage, transportation procedure during total manufacturing cycle and long storage procedure		4	4 weeks	--	--	
10.	Duly filled & signed Technical Questionnaire & documents.	3	--	--	--	--	
11.	List of fabrication and control operations (LOFC)	--	4	2 weeks	4	2 weeks after approval	
12.	NDE reports & Procedure	--	4	When available	4	2 weeks after approval + with final techn. file	
13.	Heat treatment reports (When available)	--	4	When available	4	2 weeks after approval + with final techn. file	
Item	Documents and Data	A		B		C	
		Number of copies	Number of copies	Required date	Number of copies	Required date	
14.	Hydrotest and air test report (When available)	--	4	When available	4	2 weeks after approval + with final techn. file	

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Volume II
of II

Bid Document No. BGL/719/2025-26

15.	Material certificate	--	4	1 week after test	4	With final techn. file
16.	List of subcontractors with their scope	--	4	2 weeks	--	With final techn. file
17.	Copy of purchase orders to subcontractors	--	4	2 weeks	--	With final techn. file
18.	Copy of purchase order	--	--	--	--	With final techn. file
19.	Packing/shipping list w/weights and dimensions	--	4	4 weeks	4	2 weeks before shipping
20.	Final technical file	--	--	--	6	With shipping

NOTES

1) Durations in column B (Required date) are weeks after Purchase Order date.

Durations in column C (Required date) are weeks after document approval. Due date of each document may be proposed.

2) Latest submittal time for:

- Test procedure : 2 weeks before test
- Test report : 2 weeks after test

3) Final technical file shall be supplied in hard copy as indicated, and in electronic format (PDF Acrobat files) on two (2) CD-ROMs

8.0 LIST OF ATTACHMENTS

1. Specification for ERW Line Pipe-Doc. No. VCS-SS-PP-2052,
2. Specification for 3 Layer Polyethylene Coating of Line Pipes- Doc. No. VCS-SS-PP-2003
3. Specification for repair of Polyethylene Coating- Doc. No. VCS – SS – PP -2027
4. ITP for Electric welded pipes- Doc. No. VCS-ITP-PP-2016.
5. ITP for Steel- Doc. No. VCS-ITP-PP-2026.
6. ITP for 3-layer PE coating of line pipes- Doc. No. VCS-ITP-PP-2017.
7. Checklist- Doc. (Form-A)
8. Reference List for Supply of Pipe (FORM-B).

9. Compliance Statement – (FORM-C)
10. Reference List for Supply of Steel (FORM-D).
11. Deviation Sheet – Doc. No. VCS-SD-DS-001.
12. Instruction to Bidder – Doc. No. VCS-SD-ITB-001.
13. Vendor drawings document schedule. – Doc. No. VCS-SD-VS-001.
14. Standard Specification -Quality Management (VCS-SS-PP-2044)
15. Std Specification for Documents requirement from Supplier (VCS-SS-PP-2043)
16. List of Acceptable Steel Plate / Coil / Billets Manufacturers – Doc. No.
C251151-00-PP-LST-2001
17. Line Pipe Manufacturing Mill Capability Certification

STANDARD SPECIFICATION

FOR

ERW LINE PIPE

CONTENTS

1. SCOPE.....	4
2. NORMATIVE REFERENCES.....	4
3. PIPE GRADE, STEEL GRADE AND DELIVERY CONDITION	4
4. MANUFACTURING.....	5
5. ACCEPTANCE CRITERIA	6
6. INSPECTION	12
7. MARKING	18
8. COATINGS AND THREAD PROTECTORS.....	18
9. RETENTION OF RECORDS	18
10. PRODUCTION REPORT.....	18
11. INSPECTION OF FIELD TESTS & WARRANTY.....	19

1. SCOPE

1.1 Coverage

This specification establishes the minimum requirements for the manufacture of ERW steel line pipe in accordance with the requirements of API (American Petroleum Institute) Specification 5L, Forty-Sixth Edition, April 2018 and makes restrictive amendments to API Specification 5L. Unless modified and/or deleted by this specification, the requirements of API Specification 5L shall remain applicable.

The sections, paragraphs and annexes contained herein have the same numbering as that of API Spec 5L in order to facilitate reference. Additional requirements, which are not specified in API Spec 5L, have also been numbered and marked as "(New)".

The coverage by this specification is limited to line pipe to be used in onshore pipelines transporting non-sour hydrocarbons in liquid or gaseous phase. The product specification level for line pipe to be supplied as per this specification shall be "PSL 2".

1.2 Application of The API Monogram

The Manufacturer shall have a valid license to use API Monogram and line pipes supplied as per this specification shall bear API monogram in accordance with the requirements of Annex A of API Specification 5L, Forty—Sixth Edition, April 2018 for Product Specification Level PSL 2.

1.3 (New) Pipe Size

This Specification shall be applied to line pipe of size 4.5" (114.3 mm) OD thru 20" (508.0 mm) OD (both sizes included).

2. NORMATIVE REFERENCES

The latest edition (edition in force at the time of issue of enquiry) of following additional references are included in this specification:

ASTM E112-12: Standard Test Methods for Determining Average Grain size

3. PIPE GRADE, STEEL GRADE AND DELIVERY CONDITION

3.1 Pipe Grade and Steel Grade

3.1.2 Line pipe supplied to this specification shall conform to Product Specification Level 2 (PSL2) as given in Table 1 of this specification and consists of an alpha or alphanumeric designation that identifies the strength level of the pipe. The steel name (designating a steel grade), linked to the chemical composition of the steel, additionally includes a suffix that consists of a single letter (M) that identifies the delivery condition as per Table 3 of this specification.

Table 1 of API Spec 5L stands replaced by Table 1 of this specification.

Table 1- Pipe grades, steel grades and acceptable delivery conditions

PSL Delivery Condition Pipe grade/ steel grade a, b.

PSL -2 Thermomechanical rolled BM, X42M, X46M, X52M, X56M, X60M, X65M & X70M

a Deleted

b The suffix (M) for PSL 2 grades belongs to steel grade.

3.2 Delivery condition

3.2.2 The delivery condition for starting material shall be in accordance with Table 1 of this specification.

4 MANUFACTURING

4.1 Process of Manufacture

Pipe furnished to this specification shall be manufactured in accordance with the applicable requirements and limitations given in Table 2 of API Spec 5L and Table 3 of this specification.

Table 3 of API Spec 5L stands replaced by Table 3 of this specification.

Table 3 - Acceptable manufacturing routes for PSL 2 pipe

Type of Pipe	Starting Material	Pipe forming	Pipe Heat treatment	Delivery condition
ERW	Thermomechanical-rolled coil	Cold forming	Heat treating a of weld area only	M

a See clause 8.8 of this specification for applicable heat treatment

Electric welding shall be performed with a minimum welding current frequency as per latest edition of relevant codes and standards. The welding system shall have an integrated control in which following data as a minimum shall be monitored:

- Welding Temperature
- Welding speed
- Current and Voltage

Abutting edges of the coil shall be milled or machined immediately before welding. The width of the coil shall be continuously monitored.

4.3 Starting Material

4.3.2 Line pipe furnished to this specification shall be made from steel produced in basic oxygen or electric arc furnace and cast by continuous casting only.

4.3.3 The steel used for manufacture of pipe shall be fully killed and fine grained with ASTM grain size number 7 or finer as per ASTM E 112.

4.8 Treatment of Weld Seams In EW And LW Pipes

4.8.2 LW pipe and PSL 2 ERW pipe

The weld seam and the entire Heat Affected Zone (HAZ) shall be heat treated so as to simulate a normalizing heat treatment in order to control the grain structure so that no untampered martensite remains in the weld seam and the HAZ, and the mechanical properties of heat-treated zone approximate that of the parent metal.

Heat treatment temperature of the weld seam and the entire HAZ shall be continuously measured and recorded.

4.8 Cold Sizing and Cold Expansion

4.8.1 Pipes furnished to this specification shall be non-expanded.

4.9 Jointers

4.11.1 Jointers on pipes are not permitted.

4.10 ACCEPTANCE CRITERIA

5.2 CHEMICAL COMPOSITION

5.2.2 For pipes supplied as per this specification, the chemical composition of each heat of steel on product analysis shall be as given in Table 5 of this specification.

Table 5 of API Spec 5L stands replaced by Table 5 of this specification.

Table 5 - Chemical composition for pipe

Element	Mass fraction based upon heat and product analyses (%)
---------	--

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

C ^b	0.16	max. (For Grade BM to X56M)
	0.12 ^f	max. (For Grade X60M to X70M)
Si	0.15 ^{m(new)}	min.
	0.45	max.
Mn ^b	1.20	max. (For Grade BM to X46M)
	1.40	max. (For Grade X52M & X56M)
	1.60	max. (For Grade X60M & X65M)
	1.70	max. (For Grade X70M)
P	0.020	max.
S	0.015	max.
V	0.05	max. (For Grade BM to X46M)
	^d	max. (For Grade X52M to X70M)
Nb	0.05	max. (For Grade BM to X46M)
	^d	max. (For Grade X52M to X70M)
Ti	0.04	max. (For Grade BM to X46M)
	^d	max. (For Grade X52M to X70M)
Al ^{n(new)}	0.02 ^{o(new)}	min.
	0.07	max.
Cr	0.20	max.
Mo	0.10	max. (For Grade BM to X65M)
	0.20	max. (For Grade X70M)
Cu	0.35	max.
Ni	0.20	max.
N ^{n(new)}	0.012	max.
B	0.0005	max.
a Based upon product analysis as per clause 9.2.4 and 9.2.5 of API Spec 5L, the CE _{Pcm}		

limits apply if $C \leq 0.12\%$ and CE_{IIW} limits apply if $C > 0.12\%$. For pipes of all grades, sizes and wall thicknesses, Carbon Equivalent shall comply with the following limits:

$CE_{Pcm} \leq 0.20\%$

$CE_{IIW} \leq 0.40\%$

Boron content shall be considered in CE_{Pcm} formula even if it is less than 0.0005%.

b Deleted

c Deleted

d $Nb + V + Ti \leq 0.15\%$

e Deleted

f Deleted

g Deleted

h Deleted.

I Deleted

j Deleted

k Deleted

l Deleted

(New)m : Minimum for Si is not applicable for Al killed steel.

(New)n : Al/N shall be minimum 2 (not applicable to titanium-killed steel or titanium-treated steel)

5.2.2 For heat analysis and product analysis, all the elements listed in Table 5 of this specification shall be analysed and reported, even if those are not purposely added but are present as residuals only.

If alloying elements other than those specified in Table 5 of this specification are added to the steel, the limits of the additional components shall be agreed with the Purchaser.

5.3 TENSILE PROPERTIES

5.3.2 The finished pipe (after all heat treatment & sizing operations) shall conform to the requirements of Table 7 of API Spec 5L and as modified herein.

The actual yield strength shall be as close as possible to the specified minimum yield strength (SMYS) but in no case it shall exceed the limits specified here under:

API Spec 5L Grade	Permissible	
in excess of SMYS, MPa (psi) Up to and including X46 M		131
(19,000)		

X52M to X60M	125 (18,000)
X65M to X70M	120 (17,400)

The ratio of body yield strength and body tensile strength of each test pipe on which yield strength and ultimate tensile strength are determined, shall not exceed 0.90.

The tensile strength of the weld (after heat treatment of the weld seam) shall be equal to or higher than the specified minimum tensile strength of the base metal.

The minimum elongation of base metal shall be determined in accordance with the formula given in foot note (f) of Table 7 of API Spec 5L, however, minimum elongation in no case shall be less than 20%.

5.6 Flattening Test

Acceptance criteria for flattening tests shall be as follows:

- a) For ERW pipe of grade \geq X60 and $t \geq 12.7$ mm, there shall be no opening of the weld before the distance between the plates is less than 66% of the original outside diameter. For all other combinations of pipe grade and specified wall thickness, there shall be no cracks or breaks in either weld or parent metal before the distance between the plates is less than 50% of the original outside diameter. Dye penetrant testing shall be used to positively confirm the presence of crack, break or opening.
- b) For ERW pipe with a $D / t \geq 10$, there shall be no cracks or breaks other than in the weld before the distance between the plates is less than 33% of the original outside diameter.
- c) For all pipes, there shall be no evidence of lamination or burnt metal during the entire test before opposite walls of the pipe meet.

Note: The weld extends to a distance of 13 mm on each side of the weld line. The original outside diameter is the specified outside diameter.

5.8 Cvn Impact Test For PSL 2 Pipe

5.8.1 General

5.8.1.2 From the set of three Charpy V-notch impact test pieces, only one is allowed to be below the specified average absorbed energy value and shall meet the minimum single absorbed energy value requirement as specified in Table 8 of this specification.

5.8.2 Pipe body tests

5.8.2.1 The average (set of three test pieces) absorbed energy value (KvT) for each pipe body test shall be as specified in Table 8 of this specification, based upon full sized test pieces at a test temperature of 0°C(32°F) or at a lower test temperature as specified in the Purchase Order/ Material Requisition/Data sheets.

Table 8 of API Spec 5L stands replaced by Table 8 of this specification.

Table 8 - CVN absorbed energy requirements for pipe body, weld and HAZ of PSL 2 pipe

Pipe Grade	Full-size CVN absorbed energy (KvT) ^{a,b} [J]	
	Average	Minimum
BM	40	32
X42M	40	32
X46M	40	32
X52M	40	32
X56M	40	32
X60M	42	34
X65M	45	36
X70M	50	40

a. The required KvL (longitudinal direction test pieces) values shall be 50% higher than the required KvT values.
b. Testing shall be performed at a test temperature of 0° C (32°F) or at a lower temperature as specified in the Purchase Order /Material Requisition/Data sheets..

5.8.2.2 The minimum average (set of three test pieces) shear fracture area shall be at least 85 % with one minimum value of 75%, based at a test temperature of 0 °C (32 0F) or at a lower test temperature as specified in the Purchase Order/ Material Requisition/Data sheets.

5.8.3 Pipe weld and HAZ tests

The average (set of three test pieces) absorbed energy value (Kv1) for each pipe weld and HAZ test shall be as specified in Table 8 of this specification, based upon full-size test pieces at a test temperature of 0°C (32°F) or at a lower test temperature as specified in the Purchase Order/ Material Requisition/Data sheets

5.10 Surface Conditions, Imperfections and Defects

5.10.1 General

5.10.1.2 All pipes shall be free from cracks, sweats, leaks and slivers. Pipe containing such defects shall be treated in accordance with clause C.3 b) or c) of API Spec 5L.

5.10.3 Arc burns

5.10.3.2 Arc burns shall be treated in accordance with clause C.3 b) or c) of API Spec 5L. As a reference method for confirming the existence of an arc burn, the area shall be buffed with wire brush or sanding disc and etched with 10% solution of ammonium persulfate or a 5% solution of nital.

However, arc burns can be considered for acceptance, in case the same is re-crystallized by seam heat treatment. In such case, the Manufacturer shall demonstrate the re-crystallization to Purchaser by taking a sample as per clause 10.2.3.8 (New) of this specification.

5.10.4 Laminations

Any lamination or inclusion either extending into the face or bevel of the pipe or present within 50 mm from pipe ends shall be classified as defect. Pipes that contain such defects shall be rejected or cut back until no lamination or inclusion is present at the pipe ends and shall be treated in accordance with clause C.3 b) or c) of API Spec 5L.

5.10.5 Geometric deviations

5.10.5.2 For dents, the length in any direction shall be $\leq 0.5 D$ and the depth, measured as the gap between the extreme point of the dent and the prolongation of the normal contour of the pipe, shall not exceed the following:

- a) 3.2 mm for cold-formed dents with sharp-bottom gouges and not encroaching upon the specified minimum wall thickness
- b) 6.4 mm for other dents
- c) 1 mm at the pipe ends, i.e. within a length of 100 mm at each of the pipe ends.
- d) Any dent on weld and heat affected zone (HAZ).

Dents that exceed the above specified limits shall be considered as defect and shall be treated in accordance with clause C.3 b) or c) of API Spec 5L. Acceptable cold-formed dents with sharp-bottom gouges shall be treated in accordance with clause C.2 of API Spec 5L & as modified in this specification.

5.10.6 Hard Spots

Any hard spot larger than 50 mm (2.0 in) in any direction and hardness greater than 248HV10 shall be classified as defect and treated in accordance with clause C.3 b) or C.3 c) of API Spec 5L.

5.10.7 Other surface imperfection

Other surface imperfections found by visual inspection or non-destructive inspection shall be investigated, classified and treated as follows:

- a) Imperfections that have a depth $\leq 0.05 t$ and do not encroach on the minimum specified wall thickness shall be classified as acceptable imperfections and shall be treated in accordance with Clause C.1 of this specification.
- b) Imperfections that have a depth $> 0.05 t$ and do not encroach on the minimum specified wall thickness shall be classified as defects, and shall be dressed-out by grinding in accordance with Clause C.2 of API Spec 5L and as modified in this specification or shall be treated in accordance with clause C.3 b) or c) of API Spec 5L.
- c) Imperfections that encroach on the minimum specified wall thickness shall be classified as defects and treated in accordance with clause C.3 b) or c) of API Spec 5L.

5.11 Dimensions, Mass and Tolerances

5.11.3 Tolerances for diameter, wall thickness, length and straightness

5.11.3.1 The diameter and out-of-roundness shall be within the tolerances given in Table 10 of this specification.

Table 10 of API Spec 5L stands replaced by Table 10 of this specification.

Table 10 - Tolerances for diameter and out-of-roundness.

Specified outside Diameter (D) mm (inch)	Diameter tolerances ^d		Out-of-roundness ^{e (new)}	
	Pipe except the end ^a	Pipe end ^{a,c}	Pipe except the end ^a	Pipe end ^{a,c}
$D \leq 168.3 (6 \frac{5}{8})$	$\pm 0.0075 D$	-0.4 mm to + 1.6mm	0.020D	0.015 D up to a maximum of 2.0mm
$168.3 (6 \frac{5}{8}) < D \leq 273.1 (10 \frac{3}{4})$	$\pm 0.0075 D$	$\pm 0.005 D$	0.020D	2.0mm
$D > 273.1 (10 \frac{3}{4})$	$\pm 0.0075 D$ up to a maximum of $\pm 3.0\text{mm}$	$\pm 1.6\text{mm}$	0.020D	3.0mm

a The pipe end includes a length of 100 mm at each of the pipe extremities.

b Deleted

c The diameter tolerance and out-of-roundness tolerance shall apply on inside diameter. The inside diameter, based on circumferential measurement, shall be calculated as $ID = (D - 2t)$.

d For determining compliance to the diameter tolerances, the pipe diameter is defined as the circumference of the pipe in any circumferential plane divided by Pi (π).

e (New) Out-of-roundness tolerances apply to maximum and minimum diameters as measured with bar gage, caliper, or device measuring actual, maximum and minimum diameters.

- 5.11.3.2 In addition to API requirements, the wall thickness of each pipe shall be checked along the circumference at both ends and at the mid location of pipe body at 12 0' clock, 3 0' clock, 6 0' clock

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

and 9 O' clock positions. The tolerances for wall thickness shall be as given in Table 11 of this specification.

Table 11 of API Spec 5L stands replaced by Table 11 of this specification.

Table 11- Tolerances for wall thickness

Wall thickness (mm)	Tolerances c, d (mm)
t < 15.0 mm	+0.20 t -0.0t
t ≥ 15.0 mm	+3.0 mm -0.0 mm
a Deleted b Deleted c The + ve tolerance for wall thickness does not apply to the weld area. d See 9.13.2 of API Spec 5L and as modified herein for additional restrictions.	

5.11.3.3 All pipes shall be supplied with length between 11.5 m and 12.5 m. However pipe with length between 10.0 m and 11.5 m can also be accepted for a maximum of 5% of the ordered quantity. The minimum average length of the entire ordered quantity in any case shall be 12.0 m. Overall length tolerance shall be (-) Zero and (+) One pipe length to complete the ordered quantity. Table 12 of API Spec 5L stands deleted.

5.11.3.4 The tolerances for straightness shall be as follows:

- a) The total deviation from a straight line over the entire pipe length, as depicted in Figure 1 of API Spec 5L shall not exceed 12 mm.
- b) The local deviation from straight line, as depicted in Figure 2 of API Spec 5L, in 1.0 m (3.0 ft) portion at each pipe end shall be ≤ 3.0 mm (0.120 in),

5.12 Finish of Pipe Ends

5.12.5 Plain ends

5.12.5.6

(New) During removal of inside burrs at the pipe ends, care shall be taken not to remove excess metal and not to form an inside cavity on bevel. Removal of excess metal beyond the minimum wall thickness as indicated in clause 9.11.3.2 of this specification shall be a cause for re-bevelling. In case root face of bevel is less than that specified, the pipe ends shall be re-bevelled and rectification by filing or grinding shall not be done.

5.12.5.7

(New) Bevel Protectors

Both pipe ends of each pipe shall be provided with metallic or high impact plastic bevel protectors as per Manufacturer's standard. Bevel protectors shall be of a design such that they can be re-used by coating applicator for providing on externally anti-corrosion coated pipes subsequent to coating of line pipe.

5.16 (New) Reverse Bend Test

All pipes shall meet the minimum acceptance criteria for Reverse Bend Test as follows:

A specimen which fractures completely prior to the engagement of mandrel and specimen as specified in clause 10.2.4.9 (New) of this specification, or which reveals cracks or ruptures in the weld or heat affected zone longer than 4 mm shall be rejected. Cracks less than 6 mm long at the edges of the specimen shall not be cause for rejection. Dye penetrant testing shall be used to positively confirm cracks or openings.

6 INSPECTION

6.1 Types of Inspection and Inspection Documents

6.1.3 Inspection documents for PSL 2 pipes

6.1.3.1 Inspection certificate 3.2 in accordance with EN 10204 shall be issued for each dispatched pipe by Purchaser's authorized representative.

6.2 Specific Inspection

6.2.1 Inspection frequency

6.2.1.2 For PSL 2 pipe, the inspection frequency shall be as given in Table 18 of this specification.

Table 18 of API Spec 5L stands replaced by Table 18 of this specification.

Table 18 - Inspection frequency of pipe.

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Volume II
of II

Bid Document No. BGL/719/2025-26

Sl. no.	Type of inspection	Frequency of inspection
1	Heat analysis ^a	One analysis per heat of steel
2	Product analysis ^b	Two pipes per lot (maximum 100 pipes) per heat
3	Tensile testing of the pipe body	Two pipes per test unit of not more than 100 pipes per heat
4	Tensile testing of the longitudinal weld seam of pipe ^c	Two pipes per test unit of not more 100 pipes per heat
5	CVN impact testing of the pipe body	Once per test unit of not more than 50 pipes
6	CVN impact testing of the weld and HAZ of pipe	Once per test unit of not more than 50 pipes
7	Flattening test of pipe	As shown in Figure 6 a) of API Spec 5L
8	Reverse Bend Test (New)	Same as Figure 6 a) of API Spec 5L
9	Hardness testing	Any hard spot exceeding 50 mm (2.0 in) in any direction
10	Hydrostatic testing	Each pipe
11	Weighing of pipe	Each pipe shall be measured and recorded
12	Wall thickness measurement ^d	Each pipe
13	Pipe diameter and out-of roundness ^d	Each pipe
14	Length	Each length of pipe shall be measured and recorded
15	Straightness ^d	Each pipe
16	Tolerances for the weld seam ^d a) Radial offset of coil edges b) Height of flash and c) Depth of groove after trimming of inside flash	Each pipe

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

17	Visual inspection	Each pipe
18	Metallographic testing (including Vicker's hardness test) of the longitudinal seam weld of pipe as defined in clause 10.2.5 of this specification	At least one finished pipe from each lot of 50 pipes per heat or at least once per operating shift (12 hrs max.) whichever is occurring more frequently and whenever changes of grade, diameter or wall thickness are made and whenever significant excursions from operating heat treatment conditions are encountered and at the beginning of the production of each combination of specified outside diameter and specified wall thickness.
19	Other dimensional testing	Random testing, with the details left to the discretion of the manufacturer
20	Non-destructive inspection	In accordance with Annex E of API Spec 5L and as modified herein
<p>a Where the steel mill is not a part of an integrated pipe mill, heat analysis shall be reported by the Manufacturer prior to start of pipe production.</p> <p>b Pipes selected shall be such that one at the beginning of the heat and one at the end of the heat are also represented.</p> <p>c Pipe produced by each welding machine shall be tested at least once per week.</p> <p>d Measurement shall be recorded at least 3 times per operating shift (12 hrs maximum).</p> <p>e "Test unit" is as defined in clause 3.1.60 of API Spec 5L.</p>		

6.2.2 Samples and test pieces for product analysis

Samples shall be taken, and test pieces prepared, in accordance with ISO 14284 or ASTM E1806. Samples used for product analysis shall be taken from finished pipes only.

Samples for product analysis from coil may be used provided the traceability of samples is guaranteed.

6.2.3 Samples and test pieces for mechanical tests

6.2.3.1 General

In addition to API Spec 5L requirements, samples and test pieces for various types of tests shall be taken from Figure 5 b) and Figure 6 a) of API Spec 5L and Figure 10.2.4.9.1 & 10.2.5.3 of this specification, whichever is applicable, and as given in Table 20 of this specification.

Table 20 of API Spec 5L stands replaced by Table 20 of this specification.

Sample Location	Type of test	Number, Orientation and location of test pieces per sample ^a	
		Specified outside diameter, D mm (in)	
		< 219.1 mm (8.625 in)	≥ 219.1 mm (8.625 in)
Pipe body	Tensile	1 L90	1T180
	CVN	3T90	3T90
Seam Weld	Tensile	---	IW ^b
	CVN	3W and 3HAZ	3W and 3HAZ
	Hardness	1W (As shown in figure 10.2.5.3 of this specification)	
Pipe body and weld	Flattening	As shown in figure 6 a) of API Spec 5L	
	Reverse Bend	As shown in figure 10.2.4.9.1 of this specification	
See figure 5 (b) of API Spec 5L for an explanation of the symbols used to designate orientation and location.			
b Test specimen shall be tested for ultimate tensile strength only.			

6.2.3.2 Test pieces for the tensile test

Rectangular test pieces, representing the full wall thickness of the pipe, shall be taken in accordance with ASTM A370 and as shown in Figure 5 b) of API Spec 5L.

Longitudinal tensile tests for pipe body with specified outside diameter, $D < 219.1$ mm (8.625 inch) shall be carried out on a strip specimen representing full wall thickness of the pipe prepared according to ASTM A370.

Transverse tensile test for pipe body with specified outside diameter, $D \geq 219.1$ mm (8.625 inch) shall be carried out on flattened rectangular test pieces.

For tensile test piece, both inside and outside flash of weld in excess of pipe wall thickness shall be removed from the test piece either by grinding or machining.

6.2.3.3 Test pieces for the CVN impact test

In addition to the API Spec 5L requirements, following shall also be applicable:

The test pieces shall be prepared in accordance with ASTM A370. Non-flattened test pieces shall be used. The axis of the notch shall be perpendicular to the pipe surface.

Charpy V-notch impact testing shall be performed on full-sized test pieces. However, if preparation of full size test piece is not possible, then standard sub-sized test pieces shall be prepared as per ASTM A370.

Lower pipe sizes wherein preparation of transverse sub-sized specimen is not possible, CVN impact testing shall be carried out on longitudinal test specimen [see Note 'a' of Table 8 of this specification].

6.2.3.7 Test pieces for flattening test

The test pieces shall be prepared in accordance with ISO 8492. The length of each test piece shall be ≥ 60 mm.

Minor surface imperfections may be removed by grinding.

6.2.3.8 Test pieces for Macro graphic and metallographic tests

(New) Test piece for metallographic testing shall be taken transverse to the longitudinal weld seam as indicated in Figure 10.2.5.3 of this specification. The test piece shall be suitably ground, polished and etched to reveal the macro-structure.

6.2.3.9 Test pieces for Reverse bend test

(New) Ring specimen of width between 100 mm to 115 mm shall be taken from the pipe.

Reverse bend test shall be carried out as per clause 10.2.4.9 (New) of this specification.

6.2.4 Test methods

6.2.4.3 CVN impact test

The Charpy test shall be carried out in accordance with ASTM A370.

6.2.4.7 Flattening test

In addition to the API Spec 5L requirements, following shall also be applicable: The flattening test shall be carried out in accordance with ISO 8492.

6.2.4.9 Reverse bend test

(New) The mandrel shall be plunged into the test piece prepared in accordance with clause

10.2.3.9 (New) of this specification, with the weld in contact with the mandrel, to such a depth that the angle of engagement between mandrel and specimen reaches 60° as shown in figure 10.2.4.9.1 of this specification. If the combination of diameter & wall thickness of pipe and radius of mandrel is such that the angle of engagement cannot reach 60°, then the mandrel shall be plunged into the specimen until opposite walls of the specimen meet.

Selection of Mandrel

The reverse bend test shall be carried out with a mandrel, whose radius (R), or width (A) shall be calculated for any combination of diameter, wall thickness and grade with the following formula:

$$A = 2R = \frac{1.4(D-t)t}{e(D-2t) - 1.4t} - t$$

Where,

D - Specified

outside diameter of pipe,

mm t - Specified

wall thickness of pipe, mm

1.4 - Peaking factor

e - Strain

Minimum value of 'e' shall be as per Table 23 of API Spec 5L reproduced as below:

Table 23 — Strain Values for Guided-bend Test

Pipe grade	Strain value 'e'
Gr. B	0.1375
X42	0.1375
X46	0.1325
X52	0.1250
X56	0.1175
X60	0.1125
X65	0.1100
X70	0.1025

6.2.5 Macro graphic and metallographic tests

6.2.5.3 The test piece shall be visually examined using a minimum 40X magnification to provide evidence that heat treatment of weld zone is adequate and there is no untempered martensite or detrimental oxides from the welding process present along the weld seam. The metallographic examination shall be documented on micrographs (at 10X to 20X magnification). In case imperfections or defects are observed, it will become a cause for re-evaluation of welding parameters and heat treatment as deemed necessary by Purchaser's Representative.

Vickers hardness tests shall be carried out on each test piece taken for metallographic examination in accordance with ISO 6507-1, at locations indicated in Fig. 10.2.5.3 of this specification. Indentation in the HAZ shall start as close to the fusion line as possible. The resulting Vickers hardness value at any point shall not exceed 248HV10. The maximum difference in hardness between the base metal and any reading taken on the weld or heat affected zone shall be less than 80HV10. Modalities of retest shall be in accordance with clause 10.2.12.7 of API Spec 5L.

6.2.6 Hydrostatic test

6.2.6.1 Test pressure shall be held for a minimum period of 15 seconds for all sizes and grades of pipes.

6.2.6.2 In addition to the requirements of API Spec 5L, following shall also be applicable:

The pressure gauge used for hydrostatic testing shall have a minimum range of 1.5 times and maximum range of 4 times the test pressure. The test-pressure measuring device shall be calibrated by means of a dead-weight tester only. The test configuration shall permit bleeding of trapped air prior to pressurization of the pipe.

6.2.6.5 The test pressure for all sizes and grades of pipe shall be such that hoop stress (fibre stress) generated is at least 95% of SMYS, computed based on the Equation (6) indicated in clause 10.2.6.5 of API Spec 5L. Table 26 of API Spec 5L stands deleted.

6.2.7 Visual inspection

6.2.7.1 Each pipe shall be visually examined for entire external surface and internal surface to the extent feasible and shall be free of defects in finished condition. Visual examination shall be carried out in a sufficiently illuminated area; minimum 1000 1x. If required additional lights shall be used to obtain good contrast and relief effect between imperfections and backgrounds.

6.2.8 Dimensional testing

6.2.8.1 Diameter measurements shall be made with a circumferential tape only.

6.2.8.7 The measuring equipment requiring calibration or verification under the provisions of API Spec 5L shall be calibrated with manual instruments at least once per operating shift (12 hours maximum). Such calibration records shall be furnished to Purchaser's Representative on request.

6.2.10 Non-destructive inspection

Non-destructive inspection shall be performed in accordance with Annex E of API Spec 5L and as modified herein.

6.2.11 Reprocessing

This clause of API Spec 5L stands cancelled.

6.2.12 Retesting

6.2.12.1 Recheck analyses

Modalities of recheck analysis shall be as per API Spec 5L as applicable to the lot being tested (see Table 18 of this specification). However, during individual testing, each pipe shall be fully analysed to meet the requirements of Table 5 of this specification.

6.2.12.9 Reverse bend retests

(New) Reverse bend retest provisions shall be same as specified for flattening retests in clause 10.2.12.3 of API Spec 5L.

7 MARKING

7.1 General

7.1.1 Pipe manufactured in accordance with this specification shall be marked by the manufacturer as per the requirements of API Spec 5L and as modified herein. Marking shall be in English language and International System (SI) of Units.

7.1.5 (New) Marking shall also include Purchase Order number, item number, pipe number and heat number.

7.2 Pipe markings

7.2.1 k) (New) Actual length in metres and actual pipe weight in kg shall be marked

7.2.3 c) (New) Paint used for stencil marking shall withstand a temperature (New) up to 250°C expected to be experienced during further external anti-corrosion coating operations of line pipe by coating applicator.

7.2.4 The pipe number shall be placed by cold rolling or low stress dot marking or vibro-etching on the outside surface of the pipe at an approximate distance of 50 mm from both ends. In case of non-availability of either cold rolling or low stress dot marking facility in pipe mill, an alternative marking scheme of a permanent nature may be proposed by the Manufacturer.

7.2.8 A colour code band shall be marked on inside surface of finished pipe for identification of pipes of same diameter but different wall thickness, as indicated in the Purchase Order. The colour code band shall be 50 mm wide and shall be marked at a distance of 150 mm from the pipe ends.

8 COATINGS AND THREAD PROTECTORS

8.1.1 Unless otherwise specified in the Purchase Order, the pipes shall be delivered bare, free of any trace of oil, stain, grease and paint. Varnish coating shall be applied on the marking area.

Bevels shall be free of any coating.

9 RETENTION OF RECORDS

In addition to the records indicated in API Spec 5L, the Manufacturer shall retain the records of all additional tests and calibration records mentioned in this specification including the hard copy records of ultrasonic testing carried out on pipe/coil as well as pipe ends.

10 PRODUCTION REPORT

(New) The Manufacturer shall provide one electronic copy and six hard copies of production report in English language indicating at least the following for each pipe. International system of units (SI) shall be adopted.

- Pipe number
- Heat number from which pipe is produced
- Pipe length and weight
- Pipe grade

The Manufacturer shall provide one electronic copy and six hard copies of acceptance certificates which shall include the results of all tests required as per this specification and performed on delivered material giving details of, but not limited to, the following:

- All test certificates as per clause 10.1.3 of API Spec 5L and as modified herein.
- Records of qualification of welders and procedures for repair welding.
- Certified reports of dimensional inspection, surface imperfections & defects.

- Data on test failures, rejected heats/lots, etc.
- All other reports and results required as per this specification.

The certificates shall be valid only when signed by the Purchaser's Representative. Only those pipes, which have been certified by the Purchaser's Representative, shall be dispatched from the pipe mill.

In the event of small quantities of pipes supplied against this specification, the production report may consist of only test certificates required as per clause 10.1.3 of API Spec 5L and as modified herein and other test reports/results required as per this specification.

11 INSPECTION OF FIELD TESTS & WARRANTY

(New) Purchaser shall be reimbursed by Manufacturer for any pipe furnished on this order that fails under field hydrostatic test if such failure is caused by a material/ manufacturing defect in the pipe. The reimbursement cost shall include pipe, labour and equipment rental for finding, excavating, cutting out and installation of replaced pipe in position. The field hydrostatic test pressure will not exceed that value which will cause a calculated hoop stress equivalent to 95 percent of specified minimum yield strength.

In case Manufacturer so desires, he will be advised at least two weeks in advance so that his Representative may witness the hydrostatic test in field, however, the testing and leak (if any) finding and repair operation shall not be postponed because of absence of the Manufacturer's Representative.

Annex B

Manufacturing Procedure Qualification for PSL 2 Pipe

B.1 INTRODUCTION

B.1.1 This annex specifies additional provisions that apply for the PSL 2 pipes ordered as per this specification.

B.1.2 Two lengths each of completely finished pipes from two different heats (i.e. a total of four pipe lengths) shall be selected at random for testing as per clause B.5.1 of this specification to verify that the manufacturing procedure results in the quality of pipes which are in complete compliance with this specification. The pipes thus tested shall be considered to be the test pipes required per heat or per lot as per relevant clauses of this specification.

These manufacturing procedure qualification tests (MPQT) shall be repeated upon any change in the manufacturing procedure as deemed necessary by Purchaser's Representative. The manufacturing procedure qualification tests shall be carried out on pipes for each wall thickness, each diameter and each grade of steel.

B.1.3 Verification of the manufacturing procedure shall be by qualification in accordance with clause B.3, B.4 and B.5 of API Spec 5L and as modified herein.

Note: In the event of small quantities of pipes (i.e. less than 50 numbers) ordered against this specification, like those for bends and other similar applications, as specifically called out in the Purchase Order, the manufacturing procedure qualification test as per clause B.5.1 of this specification shall not be carried out. Pipes in such case shall be accepted based on regular production tests.

B.3 CHARACTERISTICS OF THE MANUFACTURING PROCEDURE SPECIFICATION

Before pipe production commences, Manufacturing Procedure Specification (MPS) for manufacturing of pipes and Statistical process control charts shall be prepared by pipe manufacturer (including all information as per clause B.3 a), b) and e) of API Spec 5L) and submitted for approval of the Purchaser.

B.5 MANUFACTURING PROCEDURE QUALIFICATION TESTS (MPQT)

B.5.1 For the qualification of the manufacturing procedure, all tests & inspections specified in Table 18 and clause B.5.2 of this specification shall be conducted on all the pipes selected for testing as per clause B.1.2 of this specification.

B.5.2 The Manufacturer shall submit to Purchaser a report giving the results of all tests mentioned below. The report shall be agreed and signed by Purchaser's Representative, prior to start of regular production.

The various tests to be conducted on each pipe shall be as follows. The test method and acceptance values shall be as per this specification unless specified differently in this Annex.

a. Visual Examination

All pipes shall be examined visually for dimensional tolerances and apparent surface defects.

b. Ultrasonic Examination

The weld seam of all pipes shall be examined ultrasonically by automatic ultrasonic equipment.

c. Mechanical Properties

The mechanical properties of all pipes shall be tested and shall meet the requirements of this specification. Purchaser's Representative will select the places in pipe from where the test pieces shall be extracted.

The following tests shall be conducted:

i. Flattening test

Two (2) flattening test pieces shall be extracted; one test piece shall be tested with weld at 0° and other at 90°.

ii. Tensile test

Tensile tests shall be conducted on:

For pipe with specified outside diameter, $D < 219.1$ mm (8.625 inch):

- Two (2) longitudinal test pieces from base metal

For pipe with specified outside diameter, $D \geq 219.1$ mm (8.625 inch):

- Two (2) transverse test pieces from base metal
- Two (2) transverse test pieces from the longitudinal weld seam

iii. Metallographic tests

Six (6) weld cross-section test pieces, three (3) from each end of pipe weld seam shall be taken for metallographic examination. Two of these shall be tested for hardness at room temperature after etching, one from each pipe

iv. CVN impact testing

CVN impact test shall be performed on test pieces extracted as follows:

- Four sets of three (3) transverse test pieces each from base metal
- One set of three (3) transverse test pieces with weld in middle
- One set of three (3) transverse test pieces with HAZ in middle

The minimum average (set of three test pieces) absorbed energy value (KvT) at the test temperature specified in clause 9.8 and Table 8 of this specification shall be complied with for test pieces extracted from base metal, weld and HAZ.

v. Fracture toughness testing

Four (4) sets of CVN base metal test pieces shall be tested at - 40°C, - 10°C, 0°C and + 20° C for shear area and absorbed energy to produce full transition curve. The minimum average (set of three test pieces) shear fracture area at the test temperature specified in clause 9.8 of this specification shall be complied with. For other temperatures, the value shall be for information only.

Annex C

Treatment of surface imperfections and defects

C.1 TREATMENT OF SURFACE IMPERFECTIONS

Surface imperfection not classified as defect as per this specification shall be cosmetically dressed-out by grinding.

C.2 TREATMENT OF DRESSABLE SURFACE DEFECTS

C.2.3 Complete removal of defects shall be verified by local visual inspection and by suitable non-destructive inspection. To be acceptable, the wall thickness in the ground area shall be in accordance with clause 9.11.3.2 of this specification.

Annex E

Non-destructive inspection for Pipe

The Purchaser reserves the right to depute its Representative(s) to perform inspection and witness tests in all phases of manufacturing and testing starting from steelmaking to finished line pipe ready for shipment. Manufacturer shall comply with the provisions regarding inspection notice, plant access, compliance and rejection mentioned in the Annex Q (New) of this specification. The Manufacturer shall give the Purchaser reasonable notice of the starting date of normal production and the work schedule. Any action or omission on part of Purchaser's Representative shall not relieve the Manufacturer of his responsibility and obligation to supply material in strict accordance with this specification.

E.1 QUALIFICATION OF PERSONNEL

E.1.1 All personnel performing NDT activities shall be qualified in the technique applied, in accordance with latest edition of ISO 9712, ISO 11484 or ASNT No. ASNT-TC-1A or equivalent

All NDT shall be performed in accordance with written procedures. These procedures shall have prior approval of the Purchaser.

Inspector Qualification

Acceptable qualification for NDT inspectors shall be as specified below:

(i) For UT

For UT, at least one Level III qualified inspector shall be available to the mill for overall supervision. Level III inspectors shall be ASNT Level III or ACCP Professional Level III and certified in applicable method.

A level II inspector is required for shift supervision, manual weld inspection and calibration of all systems (both manual and automated).

(ii) For all other NDT methods

Evaluation of indications Level II & Level III inspector

E.3 METHODS OF INSPECTION

E.3.1 General

E.3.1.1 The electric weld of the pipe shall be inspected by ultrasonic methods (Refer Table E.1 of API Spec 5L) for full length (100%) for the entire thickness, using automatic ultrasonic equipment in accordance with clause E.5 of API Spec 5L and as modified in this specification.

E.3.1.3 Location of NDT equipment in the manufacturer's facility shall be such that final inspection of weld seam of pipe shall be performed after hydrostatic testing.

E.3.2 Pipe End Inspection - Welded Pipe

E.3.2.1 Pipe ends including weld at the pipe ends not covered by automatic ultrasonic equipment shall be inspected by manual ultrasonic equipment with same sensitivity and capability as automatic equipment, or, such non-inspected pipe end shall be cut-off. Records in accordance with E.5.4 of API Spec 5L shall be maintained.

E.3.2.3 Ultrasonic inspection in accordance with the method described in ISO 10893-8 shall be used to verify that the 50 mm (2.0 in) wide zone at each pipe end is free of any laminar imperfections in the circumferential direction.

E.3.2.4(New) Bevel face of each pipe end shall be magnetic particle inspected for the detection of laminar imperfections in accordance with ISO 10893-5

E.5 ULTRASONIC AND ELECTROMAGNETIC INSPECTION

E.5.1.1 In addition to the API Spec 5L requirements, all automatic ultrasonic equipment shall have an alarm device, which continuously monitors the effectiveness of the coupling. The equipment for the automatic inspection shall allow the localization of both longitudinal and transverse defects corresponding to the signals exceeding the acceptance limits of the reference standard. The equipment shall be fitted with a paint spray or automatic marking device and alarm device for areas giving unacceptable ultrasonic indications. All ultrasonic testing equipment shall be provided with recording device. In addition, an automatic weld tracking system shall be provided for correct positioning of the probes with respect to weld centre.

E.5.2. Ultrasonic and electromagnetic inspection reference standards

E.5.2.1 The reference standard (calibration pipe) shall have the same specified diameter and wall thickness as specified for the production pipe being inspected.

E.5.2.2 Reference standards shall be of sufficient length to permit calibration of ultrasonic inspection equipment at the speed to be used in normal production.

The reference standard (calibration pipe) shall also be of the same material, type and have the same surface finish and heat treatment as the pipe being inspected.

E.5.2.3 Reference standards

E.5.2.3.1 Reference standards for pipe weld UT:

(New) Reference standard shall contain as reference indicators i.e. machined notches as given in Table E.7 of this specification

Table E.7 of API Spec 5L stands replaced by Table E.7 of this specification.

Table E.7 — Reference Indicators

Item	Reference indicators		
	Number of notches and orientation ^a		Notch Type ^b
	OD	ID	
Weld Seam	1L	1L	N10
<p>a The symbol indicates the orientation of the notch i.e. L = Longitudinal. Reference indicators shall be located as per Figure E.1 of this specification.</p> <p>b Dimensions of Notch type N10 shall be 0.1 t x 50 mm x 1 mm (Depth x maximum Length x maximum width), where, 't' is the specified wall thickness. The depth tolerance is $\pm 15\%$ of the specified notch depth or ± 0.05 mm, whichever is greater.</p>			

E.5.2.3.2 Reference standards for coil/ pipe body UT:

(New) Reference standard for the ultrasonic inspection of coil or pipe body (except the coil edges/pipe ends) shall contain continuous machined notch of following dimension:

- a) width, w : 8 mm, with a tolerance +0.8/ - 0.0 mm
- b) depth, d : $0.25 t < d < 0.5 t$, where 't' is the specified wall thickness

Reference standard for the ultrasonic inspection of coil edges (area adjoining weld seam)/ pipe ends shall have 6.4 mm (1/4 inch) diameter FBH of a depth 0.5 t, where 't' is the specified wall thickness.

E.5.3 Instrument standardization

E.5.3.2 The instrument shall be calibrated with appropriate reference standard (refer E.5.2 of API Spec 5L and as modified herein) at following intervals:

- Once at the beginning of each operating shift (12 hours maximum).
- Once in between of each operating shift i.e, 3 hrs to 4 hrs after the first
- Every time there is change in probes or working condition of the UT machine.
- Every time the running of the system gives rise to doubts on its efficiency.

If during the above calibration verification, it is found that the equipment has not functioned satisfactorily in the opinion of the Purchaser's Representative, all the pipes or coils already inspected after the previous verification shall be inspected again at Manufacturer's cost.

E.5.5 Acceptance Limits

E.5.5.2 For ultrasonic inspection of pipe/coil, any imperfection that produces an imperfection greater than the acceptable limits shall be treated as following:

a) Locations showing indications above the acceptance limits during automatic ultrasonic inspection may be re-examined by manual ultrasonic method. If no defects are located during re-examination, the original findings may be ignored. Additional scanning may be requested by Purchaser's Representative to check questionable areas.

E.5.6 Disposition of defects found by Ultrasonic and electromagnetic inspection

Disposition of any imperfection in pipe/coil that produces an indication greater than the acceptable limits as specified in Table E.9 (New) of this specification shall be classified as defect and shall be given disposition as specified in (e) or (f) of E.10 of API Spec 5L.

E.7 RESIDUAL MAGNETISM

E.7.2 The longitudinal magnetic field shall be measured on all sizes of pipes. Measurement on pipe in stack shall not be considered valid. Such measurements shall be taken on the root face or square cut face of finished plain-end pipes.

E.7.3 Measurements shall be made using Hall - effect gaussmeter only.

E.7.4 Measurements shall be made on each end of a pipe for 5% of the pipes produced but at least once per 4 hr per operating shift (12 hrs maximum).

E.7.6 Four readings shall be taken approximately 90° apart around the circumference of each end of the pipe. The average of the four readings shall not exceed 2.0 mT (20 gauss) and no single reading shall exceed 2.5 mT (25 gauss). All residual magnetism measurements shall be recorded.

E.8 LAMINAR IMPERFECTIONS IN THE PIPE BODY OF EW, SAW AND COW PIPE

E.8.1 The coil, except the longitudinal coil edges (area adjoining weld seam), shall be ultrasonically tested for laminations using an oscillating or straight running pattern of probes in accordance with ISO 10893-9 amended as follows:

The distance between adjacent scanning tracks shall be sufficiently small to ensure detection of minimum allowed imperfection size. The minimum coverage during automatic ultrasonic inspection shall be $\geq 20\%$ of the coil surface uniformly spread over the area.

Acceptance limit for laminar imperfection in the coil, except the longitudinal edges, shall be as per Table E.9 (New) of this specification. Disposition of defects shall be as per clause

E.5.6 of this specification.

Table 3 of ISO 10893-9 stands replaced by Table E.9 (New) of this specification.

E.9 LAMIMAR IMPERFECTIONS ALONG THE STRIP/ PLATE EDGES OR PIPE WELD SEAM OF EW, SAW AND COW PIPES

The longitudinal edges of the coil (area adjoining weld seam) shall be 100% ultrasonically inspected in accordance with ISO 10893-9 amended as follows:

UT shall be performed over 25 mm wide zone along each side of the trimmed longitudinal edges of the coil.

Acceptance limit for lamellar imperfection in the longitudinal edges of the coil shall be as per Table E.9 (New) of this specification. Disposition of defects shall be as per clause

E.5.6 of this specification.

Table 2 of ISO 10893-9 stands replaced by Table E.9 (New) of this specification.

Table E.9 - Acceptance criteria for lamellar imperfection in coil/ pipe body (New)

Location	Maximum individual imperfection		Minimum imperfection size considered			Maximum population density ^a
	Area mm ²	Length ^b mm	Area mm ²	Length ^b mm	Width ^c mm	
Coil, except the longitudinal edges	1000	100 ^d	300	35	8	10 (per 1.0 m x 1.0m)
Longitudinal edges of the coil	500	40	----	20	--	4 (per 1.0 m length)

a Number of imperfections of size smaller than the maximum imperfection size and greater than the minimum imperfection size.

b Length is the dimension at right angles to the scan track.

c Width is the dimension parallel to the scan track.

d Any planar imperfection which is not parallel to the coil surface is not acceptable.

e For an imperfection to be larger than the minimum imperfection size, the minimum area, minimum length and minimum width given for the coil/ pipe body, all have to be exceeded.

E.10 DISPOSITION OF PIPES CONTAINING DEFECTS

a) The repaired area shall be 100% rechecked by magnetic particle or ultrasonic inspection to ensure complete removal of defects. However for repair of cosmetic type of defects, MPI may not be conducted if so directed by Purchaser's Representative on case to case basis. The pipes having a thickness less than the minimum allowed in accordance with this specification, after repair by grinding shall be treated for disposition in accordance with (c) or (d) of clause E.10 of API Spec 5L.

E.11 ROTARY ULTRASONIC INSPECTION OF PIPE (ALTERNATIVE METHOD)

(New) As an alternative, full pipe may be ultrasonically inspected after welding of longitudinal seam by rotary ultrasonic testing method (pipe in rotating condition) in accordance with ISO 10893-8 amended as follows:

The coverage area during ultrasonic inspection shall be 100 % of the pipe body including weld seam, sides of the weld seam and pipe ends.

The reference standard for the weld seam as per clause E.5.2.3.1 and Table E.7 of this specification shall be used for the rotary ultrasonic testing.

If the manufacturer opts for rotary ultrasonic testing of full pipe in accordance with this clause, then, the requirement for ultrasonic inspection as per clause E.3.1.1, E.3.2.3, E.8 and E.9 of API Spec 5L and as modified herein shall not be applicable.

Annex G

PSL 2 Pipe with Resistance to Ductile Fracture Propagation

G.1 INTRODUCTION

G.1.1 This annex specifies additional provision that apply for pipes ordered as per this specification.

G.2 ADDITIONAL INFORMATION TO BE SUPPLIED BY THE PURCHASER

G.2.1 CVN minimum average absorbed energy value (based on full-sized test pieces) for each test as per G.3.2 shall be as per table G of this specification for BM, weld and HAZ.

Table G.1, G.2 & G.3 of API specification 5L stands replaced by Table G of this specification.

Table G-CVN Absorbed Energy Requirements for Pipe Body, Weld and HAZ of PSL2 Pipe.

Pipe Grade	Full size CVN Absorbed Energy (K _v T) ^{a,b} (J)	
	Average	Minimum
BM	40	32
X42M	40	32
X46M	40	32
X52M	40	32
X56M	40	32
X60M	42	34
X65M	45	36
X70M	50	40
a. The required K _v L (Longitudinal direction test pieces) value shall be 50% higher than the required K _v T values. b. Testing shall be performed at a test temperature of 0°C (32°F) or at a lower temperature as specified in the purchase order.		

Annex Q (New)

Purchaser Inspection

Q.1 INSPECTION NOTICE

Advance notice shall be given by the manufacturer prior to the start of production to the purchaser to inspect/witness the manufacturing activities including tests.

Q.2 PLANT ACCESS

The inspector representing the purchaser shall have unrestricted access, at all times while work of the contract of the purchaser is being performed, to all parts of the manufacturer's works that will concern the manufacture of the pipe ordered. The manufacturer shall afford the inspector all reasonable facilities to satisfy the inspector that the pipe is being manufactured in accordance with this specification. All inspections should be made at the place of manufacture prior to shipment, unless otherwise specified on the purchase order, and shall be so conducted as not to interfere unnecessarily with the operation of the works.

Q.3 COMPLIANCE

The manufacturer is responsible for complying with all of the provisions of this specification. The purchaser may make any investigation necessary to be satisfied of compliance by the manufacturer and may reject any material that does not comply with this specification.

Q.4 REJECTION

If the Purchaser Representative rejects pipes repeatedly for any recurring cause, this shall be adequate reason to refuse final inspection of subsequent pipes until the cause has been investigated and corrective action taken by the Manufacturer.



Bhagyanagar Gas Limited

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

Volume II
of II





FIGURE: 10.2.4.9.1 REVERSE BEND TEST



PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA


Bid Document No. BGL/719/2025-26



—●— LOCATIONS WHERE HARDNESS MEASUREMENT TO BE CARRIED OUT.
H.A.Z. HEAT AFFECTED ZONE

FIGURE: 10.2.5.3

METALLOGRAPHIC SPECIMEN AND LOCATIONS FOR HARDNESS MEASUREMENT



- L1 - Longitudinal inside notch (N10) at weld line
- L2 - Longitudinal outside notch (N10) at weld line

FIGURE: E.1

REFERENCE STANDARD FOR UT OF LONGITUDINAL WELD SEAM



Bhagyanagar Gas Ltd.
Bhagyanagar Gas Limited

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

Volume II
of II

SPECIFICATION FOR 3 LAYER POLYETHYLENE COATING OF LINEPIPES

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

REVISION RECORD						
Rev.	Revision Date	Prepared by	Checked by	Approved by	Authorized by	Revision Description
00	23.06.2017					Issued as Standard Specification
		AS	SM	AD	SK	
01	24.09.2019					Re-Issued as Standard Specification
		JV	MC	AD	SK	
02	28.01.2020					Document formatting, numbering updated from SS-PL-002 to VPC-PP-SS-2003 other detail update as marked
		MB	MC	AD	SK	
03	24.01.2022					VCS QMS Integration.
		AS	MC	HK	GW	
04	05.08.2022					VCS QMS Integration-Revised.
		RP	MC	HK	GW	

ABBREVIATION

APS	Application Procedure Specification
ASTM	American Society for Testing and Materials
CD	Cathodic Disbondment
DIN	Deutsches Institut für Normung
DSC	Differential Scanning Calorimetry
ESCR	Environmental Stress Cracking Resistance
FBE	Fusion Bonded Epoxy
ISO	The International Organization for Standardization
HDPE	High-Density Polyethylene
PQT	Procedure Qualification Trial (Test)
QAP	Quality Assurance Plan
ITP	Inspection and Testing Plan
OWNER	Company (companies) that own(s) and /or operate(s) pipeline(s).
APPLICATOR	Company that undertakes the coating application in accordance with the provisions of this document.
CONTRACTOR	A party contractually appointed by the Owner to fulfill all, or any of the activities associated with design, construction and operation.
CONSULTANT	Professionals, who provide technical support, perform trouble-shooting functions and customer issues.
MANUFACTURER	Company responsible for the manufacture of coating materials, chemicals and consumables.
SSPC	The Society for Protective Coatings

CONTENTS

1.0	SCOPE
2.0	REFERENCE DOCUMENT
3.0	PLANT SCALE AND INSTALLATION
4.0	COATING MATERIALS
5.0	FUNCTIONAL REQUIREMENTS AND PROPERTIES OF COATING
6.0	COATING DOCUMENTATION TO BE SUBMITTED:
7.0	APPLICATION OF COATING:
8.0	COATING PROCEDURE QUALIFICATION
9.0	RE-QUALIFICATION OF PROCEDURE QUALIFICATION
10.0	COATING PROCEDURE TESTS DURING PRODUCTION
11.0	QUALITY ASSURANCE
12.0	HANDLING, STORAGE AND TRANSPORTATION OF BARE & COATED PIPES:
13.0	REPAIR OF COATING
14.0	MARKING
15.0	INSPECTION, MEASURING AND TEST EQUIPMENT
16.0	RELEASE OF FINISHED COATED PIPES:
ANNEXURE-I	
LIST OF ACCEPTABLE COMBINATIONS OF COATING MATERIALS	

1.0 SCOPE

- 1.1 This specification covers the minimum requirements for supply/arrangement of all materials, plant, equipment, plant sites, consumables, utilities and application including all labour, supervision, inspection and tests, transportation, handling, coating integrity etc. for application of external anti-corrosion coating of pipes by using 3 Layer Side Extruded Polyethylene coating conforming to ISO 21809-‘Petroleum and Natural Gas Industries-External Coatings for buried and submerged pipeline transportation systems-Part 1:Polyolefin Coatings’, and the requirements of this specification.

In case, Applicator/ Contractor feels more stringent testing shall be followed to meet all testing requirements of this specification, then Applicator / Contractor is free to do such stringent testing including equipment calibration etc.

The three-layer coating as per this specification shall belong to coating Class B of ISO 21809- 1: 2018 and shall be suitable for design temperature range of (-) 40 °C to (+) 80 °C.

External 3LPE coating of line pipe consists of:

- a) 1st Layer: Electrostatically sprayed primed layer of epoxy powder;
- b) 2nd Layer: Application of grafted co-polymer adhesive by side extrusion process
- c) 3rd Layer: Application of medium / high density polyethylene by side extrusion process in order to obtain plant-applied, integrated, anti-corrosion 3LPE coating.

All the above coating layers are applied with specified individual thickness, conforming the requirements relevant applicable codes, specifications & standards and also meeting the expected design life for intended uses.

2.0 REFERENCE DOCUMENT

Reference has also been made to the latest edition (edition enforce at the time of issue of enquiry) of the following standards, codes and specifications. The edition enforces at the time of floating the enquiry shall be termed as latest edition.

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

ISO 21809-1 :2018	Petroleum and Natural Gas Industries-External Coatings for buried and submerged pipelines used in pipeline transportation systems – Part 1: Polyolefin coatings (3-layer PE and 3-layer PP).
ISO 21809-2 :2014	Petroleum and Natural Gas Industries-External Coatings for buried and submerged pipelines used in pipeline transportation systems – Part 2: Single Fusion-bonded Epoxy Coatings.
ASTM D149	Standard Test Method for Dielectric Breakdown Voltage and Dielectric Strength of Solid Electrical Insulating Materials at Commercial Frequencies.
ASTM D257	Standard Test Methods for DC Resistance or Conductance of Insulating Materials.
ASTM D792	Standard Test Method for Density and Specific Gravity (Relative Density) of Plastics by Displacement.
ASTM D1238	Test Method for Melt Flow Rates of Thermoplastics by Extrusion Plastometer.
ASTM D1603	Standard Test Method for Carbon Black Content in Olefin Plastics.
ASTM D1693	Standard Test Method for Environmental Stress-Cracking of Ethylene Plastics.
ASTM D4940	Standard Test Method Conductometric Analysis of Water-Soluble Ionic Contamination of Blast Cleaning Abrasives.

API RP 5L1	Recommended Practice for Railroad Transportation of Line pipe
API RP 5LW	Recommended Practice for Transportation of Line pipe on Barges and Marine Vessels.
API RP 5LT	Recommended Practice for Truck Transportation of Line Pipe
DIN EN 30670:2012	Polyethylene Coating on Steel Pipes and Fittings- Requirements and Testing.
BS EN 10204	Metallic Products – Types of Inspection Documents
ISO 306	Plastics-Thermoplastic materials- Determination of Vicat softening temperature (VST)
ISO 527-2	Plastics - Determination of tensile properties - Part 2: Test conditions for moulding and extrusion plastics.
ISO 527-3	Plastics - Determination of tensile properties - Part 3: Test conditions for films and sheets
ISO 868	Plastics and ebonite - Determination of indentation hardness by means of a durometer (Shore hardness)

ISO 1133-1	Plastics – Determination of the melt mass- flow rate (MFR) and melt volume –flow rate (MVR) of thermoplastics-Part 1: Standard method.
ISO 1183	Plastics – Methods for determining the density of non-cellular plastics.
ISO 2808	Paints and varnishes - Determination of film thickness
ISO 8501-1	Preparation of Steel Substrates before Application of Paints and Related Products – Visual Assessment of Surface Cleanliness – Part 1: Rust grades and preparation grades of uncoated and steel substrates and of steel substrates after overall removal of previous coatings.
ISO 8502-3	Preparation of Steel Substrates before Application of Paints and Related Products – Tests for assessment of Surface Cleanliness – Part 3 – Assessment of Dust on Steel Surfaces Prepared for Painting (Pressure-Sensitive Tape method).
ISO 8503-4	Preparation of Steel Substrates before Application of Paints and Related Products – Surface roughness characteristics of blast-cleaned steel substrate - Part 4: Method for the calibration of ISO surface profile comparators and for the determination of surface profile – Stylus instrument procedure.
ISO / TS 9002	QualityManagement Systems: Guidelines for the application of ISO 9001.
ISO 11124 (all parts)	Preparation of Steel Substrates Before Application of Paints and Related Products – Specification for metallic blast-cleaning abrasives.
ISO 11357-6	Plastics - Differential scanning calorimetry (DSC) - Part 6: Determination of oxidation induction time (isothermal OIT) and oxidation induction temperature (dynamic OIT).

ISO 15512	Plastics - Determination of water content
SSPC AB3	Ferrous metallic abrasives.
SSPC- SP1	Solvent cleaning
SSPC Guide15	Field Methods for Extraction and Analysis of Soluble Salts on Steel and Other Nonporous Substrates
API 5L	Specification for Line Pipe
ASME B31.4	Pipeline Transportation Systems for Liquids and Slurries
ASME B31.8	Gas Transmission and Distribution Piping Systems.
AWWA Spec	Standard Methods for the Examination of Water and Wastewater

The Applicator/ Contractor shall be familiar with the requirements of these documents and shall make them readily available at the coating plant to all persons concerned with carrying out the works specified in this specification.

- 3.0 PLANT SCALE AND INSTALLATION:
- 3.1 Applicator/ Contractor shall size coating plant(s) after evaluating the scale of work and the time schedule required for the works. Coating plant(s), both new and existing, shall be installed into a yard whose geometry and dimensions are such as to allow the execution of a continuous work schedule. For this purpose, the Applicator/ Contractor shall ensure non-stop work execution owing to prohibitive adverse weather conditions and install requisite equipment and plant in roofed and adequately weather-protected areas.
- 3.2 Plant equipment, machinery for abrasive blasting, induction heating, chemical pre-treatment, spray of FBE powder, extrusion of adhesive and polyethylene, quenching, cut back preparation and other facilities shall be in first class operating condition to at least meet the job requirements of quality and production. Worn out and improvised plants are not acceptable. The Contractor has to select the Applicator from the Vendor list specified elsewhere in the Tender document.
- 3.3 The epoxy booth shall be sized to accommodate number of spray guns (virgin & re-cycled) required for application of required quantity of fusion bond epoxy powder to be electrostatically sprayed on to the pipe to achieve required thickness as specified.
- 3.4 Plant shall have fusion bond epoxy powder storage room with power back up for air conditioning or de-humidifier equipment capable of storing epoxy powder as per temperature & humidity conditions as per manufacturer's recommendation. Conveying of epoxy powder from storage room to fluidized bed shall be thru a suitably designed conveying system. Manual powder feeding shall not be permitted. Proper sieving system shall be available for both virgin and re-cycled powder. System for ratio control of virgin & re-cycled powder should be available.
- 3.5 HDPE & Adhesive granules shall be separately stored in identified shed area, protected from direct sunlight, heat and water as per manufacturer's recommendations.
- 3.6 The air used for fluidization of epoxy powder shall be free from f. For this purpose, dehumidifiers and / or air dryer as necessary shall be provided along with necessary monitoring and control systems. Fluidized bed shall have magnets adequate to remove iron and steel shaving contaminant from recycled powder.
- 3.7 The conductivity of DI (De-Ionized) water (if used) shall be less than 5 micro-siemens/cm and rinse water pressure shall be minimum 1500 psi.
- 3.8 The Applicator/ Contractor shall, at his own responsibility and cost, provide and prepare all necessary area for the storage of bare and coated pipe and all other materials, for coating yard, stock-piling and other temporary installation. For each area,

Applicator/ Contractor shall provide necessary agreements as required with the land owner(s)/relevant Authorities, and, on work completion, to clean and pay settlement and claims for damages, as applicable.

3.9 The Applicator/ Contractor shall at its own responsibility and cost, provide for water and power supply and other utilities and consumables and obtain authorization regarding access roads and other permits required for the execution of works conforming to all the requirements of the governing Authorities.

3.10 The Applicator/ Contractor shall at its own expense provide a fully equipped laboratory and test facilities with adequate inventory to carry out tests required for the procedure qualification and regular production. Material manufacturer shall conduct the tests for each grade of material in Approved external independent laboratory (preferably ISO 17025 certified or equivalent having good track records of pipe coating testing) and provide complete test report (not older than 3 years) prior conducting Procedure Qualification Trail (PQT).

3.11 The Applicator/ Contractor shall be fully responsible for adherence to all statutory regulations applicable for handling, storage and disposal of the hazardous chemicals during the coating works.

3.12 The Applicator/ Contractor shall be responsible for obtaining all statutory approvals/clearances from relevant Authorities including Pollution Control Board, as applicable for the coating plant(s).

4.0 COATING MATERIALS:

4.1 The three-layer coating system shall comprise of a fusion bond epoxy layer, co-polymeric or grafted adhesive and high-density polyethylene (HDPE) topcoat. Coating materials shall be suitable for the service conditions and the pipe sizes involved. The coating materials i.e., epoxy powder (FBE), adhesive and polyethylene compound shall have proven compatibility. The coating system and materials shall be pre-qualified and approved by Owner/ Consultant in accordance with provisions of Annexure I of this specification. Applicator / Contractor shall obtain prior approval from Owner for the coating system and coating materials.

4.2 The coating material manufacturers shall carry out tests for all properties specified in clause 5.4.1, 5.4.2 & 5.4.3 and Table 2, 3 & 4 respectively for each batch of epoxy, adhesive and polyethylene compound. The coating materials manufacturer shall issue test certificates as per BS EN 10204, 3.1 for each batch of materials supplied to Applicator/ Contractor indicating all contents/ parameters required for batch certification as per clause 9.3, Table 6 of ISO 21809-1:2018 and the same shall be submitted to Owner for approval prior to their use.

4.3 In addition to Manufacturer's certificate, the Applicator/ Contractor shall draw two samples per batch of epoxy, adhesive and polyethylene in the presence of Owner Representative and test for the following properties at the coating laboratory prior to its use in order to establish compliance with the manufacturer's test certificates.

4.3.1 Epoxy Powder:

- Density
- Gel Time
- Particle size
- Moisture content
- Thermal characteristics (Tg1, Tg2 & ΔH)

4.3.2 Adhesive:

- Density
- Melt Flow Rate
- Vicat Softening Temperature
- Water Content

4.3.3 Polyethylene:

- Melt Flow Rate
- Density
- Vicat Softening Temperature
- Water Content
- Oxidation Induction Time

In case of failure of any of the above tests in any batch, that batch of material shall be tested for all other tests required as per clause 5.4.1, 5.4.2 & 5.4.3 and Table 2, 3 & 4 respectively, including the tests which failed. If all tests pass, the batch shall be accepted for coating. If any of the tests fail, entire batch of material shall be rejected and shall not be used for the coating.

4.4 All materials to be used shall be supplied in sealed, damage free containers and shall be suitably marked with the following minimum information:

- Name of the Manufacturer
- Grade or Trade name
- Health, safety and environmental Instructions
- Type of Material
- Batch Number
- Place of Manufacture
- Manufacturing Date / Shelf Life/Expiry Date (if applicable)
- Quantity

All materials noted to be without above identification shall be deemed suspect and shall be rejected by Owner. Such materials shall not be used for coating and shall be removed from plant/ factory and replaced by Applicator/ Contractor at his expense.

4.5 Applicator/ Contractor shall ensure that all coating materials are properly stored in accordance with the Manufacturer's recommendation at all times, to prevent damage and deterioration in quality prior to use. Documentary evidence for the same shall be provided for verification by Owner/ Consultant.

4.6 Applicator/ Contractor shall be required to use all materials on a date received rotation basis, i.e., first in - first used basis.

5.0 FUNCTIONAL REQUIREMENTS AND PROPERTIES OF COATING:

5.1 The coating shall be able to withstand a maximum in service operating temperature up to +80°C and shall conform to "Class B" as per ISO 21809-1:2018.

5.2 The topcoat polyethylene used shall be a black readymade compound, fully stabilized against influence of ultraviolet radiation (i.e., sunlight), oxygen in air and heat (due to environmental temperature up to +80°C). No appreciable changes shall occur during exposure to such environments up to at least a period of 8500 hours. The Applicator / Contractor shall submit certificate from Manufacturer in this regard.

5.3 Thickness of the Coating System:

Minimum thickness of each layer and total thickness of finished 3LPE coating system shall be as under:

Table 1: Minimum Thickness of Coating System				
Pipe size (OD)	Thickness of Epoxy Layer (mm)	Thickness of Adhesive Layer mm	Thickness of HDPE Layer mm	Total Thickness of 3LPE coating mm
4.5" to 10.75"	0.2	0.2	2.3	2.7
12.75" to 20"	0.2	0.2	2.7	3.1

For SAW pipes, 10% reduction on total thickness of applied coating measured on the apex of the weld seam shall be acceptable.

5.4 Properties

Properties of coating material and coating system shall comply with the requirements indicated in subsequent paragraphs. Applicator/ Contractor shall choose brand of epoxy powder, adhesive & HDPE as per approved vendor list (refer Annexure I) that shall achieve the functional requirements and properties of coating system as specified in clause no. 5.1, 5.2 and 5.4 of this specification respectively.

The acceptable combinations of coating material shall be as per Annexure-I.

5.4.1 Properties of Epoxy Powder (FBE):

Table 2 – Epoxy (FBE) Properties:

Table 2 – Epoxy (FBE) Properties:				
Sl. No.	Properties	Unit	Requirements	Test Method
1	Density	g/cm ³	Within ± 0.05 of the manufacturer's specified nominal value	ISO 21809-1 Annex M
2	Gel Time at 205°C $\pm 3^\circ\text{C}$	s	Within 20% of the nominal value specified by the manufacturer	ISO 21809-1 Annex J
3	Particle Size	%	3.0% retained on 150 μm sieve $\leq 0.2\%$ retained on 250 μm sieve and within manufacturer's specification	ISO 21809-2
4	Moisture Content	% mass	≤ 0.6	ISO 21809-1 Annex K

5	<p>Thermal Characteristics (Tg1, Tg2, ΔH)</p> <p>Minimum Glass Transition Temperature (Tg2)</p>	°C	<p>Within manufacture's Specification.</p> <p>≥ 95 and within manufacturer's specification</p>	ISO 21809-1 Annex D
---	---	----	--	---------------------

The colour of epoxy powder shall be either green or dark red or any other colour approved by Owner except grey colour.

5.4.2 Co-polymeric or Grafted Adhesive:

Table 3 – Co-polymeric or Grafted Adhesive Material Properties:				
Sl. No.	Properties	Unit	Requirements	Test Method
1	Density	kg/m ³	≥930 and within manufacturer's specification	ISO 1183
2	Melt Flow Rate (MFR)	g/10 min	≥1.0 and within manufacturer's specification	ISO 1133-1
3	Water Content	%	≤0.05	ISO 15512
4	Strain at Break at 23°C ± 3°C	%	≥600	ISO 527-2
5	Stress at yield 23°C ± 3°C	MPa	≥8	ISO 527-2
6	Vicat Softening Temperature (A/50, 9.8 N)	°C	≥100	ISO 306

5.4.3 Properties of Polyethylene (HDPE) Compound:

Table 4 - HDPE (Top coat) Material Properties:				
Sl. No.	Properties	Unit	Requirements	Test Method
1	Density of black compound	g/cm ³	≥0.940	ISO 1183
2	Melt flow rate (MFR)	g/10 minutes	≥0.25 and within manufacturer's specification	ISO 1133-1

3	Water Content	%	≤0.05	ISO 15512
4	Carbon Black Content	%	2-3	ISO 6964
5	Carbon Black Dispersion		Max Grade 3	ISO 18553
6	Hardness	Shore D	≥55	ISO 868
7	Strain at break at 23°C ± 3°C	%	≥600	ISO 527-2
8	Stress at Yield at 23°C ± 3°C	MPa	≥17	ISO 527-2
9	Vicat Softening Temperature (A/50, 9.8 N)	°C	≥110	ISO 306
10	Environmental Stress Cracking Resistance (ESCR) (50°C, F50)	h	≥ 1000 Cond.B, 10% Igepal CO630 or If density of black compound >0.955 g/cm ³ ≥ 300 Cond.B, 100% Igepal CO630	ASTM D 1693
11	Oxidation Induction Time (Intercept in the tangent method)	min	≥30 at 2100C	ISO 11357-6
12	UV Resistance and Thermal Ageing	%	Δ MFR ≤35	ISO 21809-1 Annex G
13	Volume resistivity @ 23°C ± 2°C	Ohm-cm	≥1016	ASTM D 257
14	Dielectric Withstand, 1000 Volts/second rise @ 23°C ± 2°C	V/mm	≥30,000	ASTM D 149

5.4.4

Properties of Applied 3LPE Coating:

Table 5 - On Cured Epoxy (FBE) film of 3LPE Coating				
Sl. No.	Properties	Unit	Requirements	Test Method
1	Minimum Epoxy Layer Thickness	mm	0.2	ISO 2808
2	Degree of Cure % Cure ΔT _g	% °C	Minimum 95 -3°C ≤ ΔT _g ≤ +3°C	ISO 21809-1 Annex D

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Volume II
of II

Bid Document No. BGL/719/2025-26

3	Holiday Detection (Test Voltage set to 5V per μm of minimum specified epoxy coating thickness)	V	No holidays	ISO 21809-2 Clause 10.3.2
4	Dry Adhesion	-	Rating 1 or 2	ISO 21809-2 Clause A.4
5	Hot Water Adhesion 24 h at 75°C+3°C	-	Rating 1 to 2	ISO 21809-2 Clause A.16
6	Hot Water Adhesion 28 days at 75°C+/-3°C	-	Rating 1 to 3	ISO 21809-2 Clause A.16
7	Cross-Section Porosity	-	\leq compared with Fig. A.11 of ISO 21809-2	ISO 21809-2 Clause A.12
8	Interface Porosity	-	\leq compared with Fig. A.12 of ISO 21809-2	ISO 21809-2 Clause A.12
9	Flexibility at 0°C	Degree per ppd	No cracking, tear, disbondment or delamination at 2° ppd length	ISO 21809-2 Clause A.13
10	Impact Resistance at 0 °C	J	> 1.5	ISO 21809- 2, Clause A.14

Table 6 - On Extruded Adhesive film of 3LPE coating

Sl. No.	Properties	Unit	Requirements	Test Method
1	Minimum Adhesive Layer Thickness	mm	0.20	ISO 2808
2	Strain at Break at 23°C \pm 3°C	%	\geq 600	ISO 527-2
3	Stress at Yield at 23°C \pm 3°C	MPa	\geq 8	ISO 527-2
4	Vicat Softening Temperature (A/50, 9.8 N)	°C	\geq 100	ISO 306

Table 7 - On HDPE Top Coat layer and 3LPE coating

Sl. No.	Properties	Unit	Requirements	Test Method
1	Continuity or Holiday of 3LPE coating @ 25 kV	---	Free of defects and discontinuities, delaminations, separations and holidays	ISO 21809-1 Annex B

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Volume II
of II

Bid Document No. BGL/719/2025-26

2	Peel Strength of 3LPE Coating at 23°C +/-3°C at 80°C +/-3°C	N/mm	≥18 ≥5 No disbonding between steel & epoxy	ISO 21809-1 Annex C2
3	Impact strength of 3LPE Coating at 23°C +/-3°C	J/mm	>7	ISO 21809-1 Annex E
4	Indentation of PE top coat @ 230C +/-20C @800C +/-20C	Mm	≤0.2 ≤0.4	ISO 21809-1 Annex F
5	Strain at Break of PE Top Coat at 230C +/-30C	%	≥400	ISO 527-2
6	Product Stability during Application of PE Top Layer process	%	Δ MFR ≤20 (Variation between virgin compound granulate before application and coating after application of the same batch tested by applicator)	ISO 1133-1
7	Cathodic Disbondment of 3LPE Coating at 23°C +/-3°C/28d/-1.38V at 65°C +/-3°C/24h/-3.38V at 80°C +/-3°C/28d/-1.38V	mm	≤5 ≤4 ≤15	ISO 21809-1 Annex H
8	Flexibility of 3LPE Coating (-2°C to 0°C, cool for minimum 1 h)	Degrees per pipe length diameter	No cracking at an angle 2° per pipe diameter length	ISO 21809-1 Annex I
9	Resistance to Hot Water Immersion of 3LPE Coating (80±3°C, 48 h)	mm	Average ≤2.0 and Maximum 3.0 mm	ISO 21809-1 Annex L
10	Specific Electrical Coating Resistance (23 °C ± 2 °C)	Ωm ²	≥10 ⁸	DIN 30670 Annex J
11	Hardness of 3LPE Coating	Shore D	≥ 55	ISO 868
12	ΔTg	°C	-3°C ≤ ΔTg ≤ + 3°C	ISO 21809-1 Annex D

6.0 COATING DOCUMENTATION TO BE SUBMITTED:

6.1 Upon award of the CONTRACT, the Applicator / Contractor shall submit within two

(2) weeks, for Owner approval, a detailed report in the form of bound manual outlining, but not limited to, the following:

- 6.1.1 Details of plant(s), location(s), layout, capacity and production rate(s).
- 6.1.2 Details of the equipment available to carry out the coating works including surface preparation, epoxy powder application and its recycling system, adhesive & polyethylene extrusion, moisture control facilities available for coating materials.
- 6.1.3 Details of process control and inspection equipment required for the coating process such as temperature control, thickness control, holiday testers, etc.
- 6.1.4 Facilities in the yard for unloading, handling, transport, production, storage, stockpiling, loading of bare and coated pipes and warehouses for storage of other coating materials.
- 6.1.5 Plant Organization Chart and availability of manpower including coating specialist.
- 6.1.6 Details of utilities/facilities such as water, power, fuel, access roads and communication etc.
- 6.1.7 Details of chemical pre-treatment facilities including process control, inspection equipment for phosphoric acid wash, de-ionized water wash, chromate treatment (if specified), drying system, etc.
- 6.1.8 Solid/ liquid waste management system procedure and facility details for safe disposal of chemical and organic substances.

After Owner has given approval; no change in plant set-up shall be made. However, unavoidable changes shall be executed only after obtaining written approval from Owner.

6.2 At least six (6) weeks prior to the commencement of production coating, a detailed procedure of the Applicator / Contractor's methods, material proposed, etc., shall be formulated by the Applicator/ Contractor and submitted for Owner approval in the form of a bound manual. The procedure shall include, but not limited to, the following information and proposals:

- 6.2.1 Incoming inspection and pipe tracking;
- 6.2.2 Pipe inspection at the time of bare pipe receipt;
- 6.2.3 Steel surface preparation, including preheating, removal of steel defects, method of pipe cleaning, dust removal, abrasive blast cleaning and surface profile; methods of measurements and consumables;
- 6.2.4 Pipe heating, temperatures and its control prior to epoxy application;
- 6.2.5 Complete details of raw materials including current data sheets showing values for all the properties specified together with quality control and application procedure recommendations from manufacturer(s);

- 6.2.6 Application of FBE powder, adhesive and polyethylene, including characteristics, temperature, line speed, application window, curing time, etc.
- 6.2.7 Quenching and cooling, including time and temperature;
- 6.2.8 Quality Assurance System, Quality Plan, Inspection and Testing Plan and reporting formats, including instrument and equipment types, makes and uses, etc.
- 6.2.9 Detailed method of repair of coating defects duly classified depending upon nature and magnitude of defects and repair thereof including coating stripping technique;
- 6.2.10 Details of instrument and equipment calibration methods including relevant standards and examples of calibration certificates;
- 6.2.11 Complete details and inventory of laboratory and equipment for procedure qualification (PQT) and regular production;
- 6.2.12 Pipe handling and stock piling procedures, pipe end protection and protection against adverse ambient conditions during storage;
- 6.2.13 Sample of recording and reporting formats, including laboratory reports, certificates;
- 6.2.14 Complete details of test certificates for raw materials including test methods and standards used;
- 6.2.15 Test certificates from PE compound manufacturer for long term tests UV resistance / Thermal aging & Specific electrical coating resistance or coating resistivity. These test certificates shall not be older than three years;
- 6.2.16 Health, Safety and Environment Plans;
- 6.2.17 Storage details of coating materials and chemicals;
- 6.2.18 Continuous temperature monitoring at various stages of coating.

The APS (Application Procedure Specification) shall cover all items associated with quality control as defined in purchase specification & in this specification and mutually agreed.

The APS, including any revisions, shall be approved by the owner prior to the start of qualification and production.

7.1 Pipe Surface Preparation:

7.1.1 Unless specified otherwise, the pipes supplied shall be free from mill applied oil, grease, paints, or other visible contaminant but may be subjected to contamination occurring during transit.

7.1.2 Prior to cleaning operation, Applicator / Contractor shall visually examine the pipes and shall ensure that all defects and irregularities (lamination, sliver and scratches), flats and other damages have been repaired or removed as per applicable specification. The Applicator / Contractor shall also remove marking stickers, if any, present within the pipe. Record shall be kept of such marking on the stickers to ensure traceability of pipe after coating.

7.1.3 Any dirt, deleterious matter, salt and contaminants (like oil, grease, etc.) detrimental to the formation of a good coating bond or coating quality shall be removed prior to coating application. Contaminants may be removed by the use of non-oily solvents like acetone, xylol, etc. Gasoline or kerosene shall not be used for this purpose. Visible oil and grease spots shall be removed by solvent wiping. Solvent cleaning shall be in accordance with SSPC-SP1. Steel surface shall be allowed to dry before abrasive cleaning.

7.1.4 All pipes shall be preheated to a temperature of 65°C to 85°C prior to abrasive blast cleaning using induction heating or radiant heating. The external surface of the pipe shall be cleaned using two dry abrasive blast cleaning units (each having two centrifugal wheels) to achieve the specified surface cleanliness and profile. If specified, Chemical pre-treatment with phosphoric acid solution as per Clause 7.2 of this specification shall be carried out after the second abrasive blaster.

7.1.5 At no time shall the blast cleaning be performed when the relative humidity exceeds 85%. The Applicator / Contractor shall measure the ambient conditions at regular intervals during blast cleaning and coating operations and keep records of prevailing temperature, humidity and dew point. The blast cleaned surface shall neither be contaminated with dirt, dust, metal particles, oil, water or any other foreign material, nor shall the surface or its anchor pattern be scarred or burnished. All blast cleaned pipe surface shall be kept in dust free enclosure prior to coating. After blast cleaning, all surfaces shall be thoroughly inspected under adequate lighting to determine anchor pattern, quality of blasting and identify any surface defects prior to coating application. All surface defects such as slivers, scab, burns, laminations, welds spatters, scratches, etc. shall be removed / rectified, inspected and then pipes shall be re-blasted.

7.1.6 The abrasive blast cleaning units shall have an effective dust collection system to ensure total removal of dust generated during blast cleaning from the pipe surface. The equipment used for abrasive blast cleaning shall meet the specified requirements and shall be free from oil, water soluble salts and other forms of contamination to ensure that the cleaning process is not impaired. Traps, separators and filters shall be checked for condensed water and oil at the start of each shift and emptied and cleaned regularly. During abrasive blast cleaning, the metallic abrasive shall be continuously sieved to remove dust, fines, corrosion products and other contaminants. The quality of abrasive working mix shall be checked at every four hours.

7.1.7 Abrasives used for blast cleaning shall comply ISO 11124. Hardness, size and ratio of shot and grit to be used in abrasive Blaster #1 & #2 shall be specified in the Inspection and Testing Plan (ITP) test plan to meet the required surface profile and other surface preparation criteria.

7.1.8 Abrasive cleaning carried out shall be such that the resultant surface profile is not dished and rounded when viewed with 30X magnification.

7.1.9 The blast cleaned surface of the pipe shall conform to near white metal finish (Sa 2½) of ISO 8501-1.

7.1.10 Surface of pipe after abrasive blast cleaning shall have an anchor pattern of 75 to 100 microns (RZ/ Ry5). This shall be measured for each pipe by portable digital surface roughness tester (Stylus Method) as per ISO 8503-4 and it shall be verified twice /shift. For retaining records, surface profile may be checked with Press-O-Film (Replica Tape Method) as per ISO 8503-5.

7.1.11 In addition to checking of degree of cleanliness (Sa 2 ½), blast cleaned pipe surface shall be also checked for degree of dust (dust level) and shape of profile. Degree of dust shall comply the requirements of ISO 8502-3.

7.1.12 After final abrasive blast cleaning, all pipes shall be tested for presence of soluble salts. One test shall be carried out on each pipe. The acceptance criteria shall be 20 mg/m² or 2 g/cm² (max). An approved salt meter (SCM 400 or equivalent) shall be used to carry out using salt tests and shall be calibrated in accordance with the equipment manufacturer's recommendations.

Any pipe having salt contamination exceeding 2µg/cm² shall be de-ionized water washed and then re-checked for salt contamination.

In case, salt level is still greater than 2 µg/cm², chemical pre-treatment of steel pipes after abrasive blasting using phosphoric acid wash, followed by high pressure water wash (>1500 psi) shall be carried out as per clause 7.2. The applicator shall specify the method of chemical pre-treatment in coating documentation, namely ITP and APS.

In case, chemical pre-treatment of all steel pipes after abrasive blasting with phosphoric acid wash is a mandatory requirement, the same shall be specified by the Owner.

7.1.13 All surface defects such as slivers, scab, burns, laminations, welds spatters, gouges, scores, indentations, slugs or any other defects considered injurious to the coating integrity made visible during after first blast cleaning shall be reported to the Owner Representative and on permission from Owner Representative, such defects shall be removed by filing or grinding. After any grinding or rectification, the remaining wall thickness shall be checked and compared with specified thickness. Any pipes having thickness less than minimum

specified thickness shall be kept aside and disposed off as per the instructions of Owner /Owner's Representative. The method employed to remove surface defects may burnish or destroy the anchor pattern or contaminate the surface. Pneumatic tools shall not be used unless they are fitted with effective air/oil and water traps. Where burnishing results in destruction of anchor pattern, it shall be ensured that anchor pattern shall be restored during second abrasive blasting. Pipes having rectification by grinding and ground areas more than 50 mm shall be re-blasted thru using both the abrasive blasters.

7.1.14 Suitable plugs shall be provided at both pipe ends to prevent entry of any shot/grit into the pipe during blast cleaning operations. These plugs shall be removed after blast cleaning. Alternatively, the Applicator / Contractor may link the pipes suitably together to prevent the entry of any short/grit into the pipe.

7.1.15 All pipes shall be visually examined for presence of any shot/grit/loose material left inside the pipe during blast cleaning. Suitable mechanical means (stiff brush) shall be employed to remove the same before the pipes are processed further. In addition, inside surface of the pipe shall also be visually inspected for presence of any foreign material or shots and grit (free or embedded/sticking to pipe inside surface). The pipe inside surface shall be examined using sharp floodlight focused at the middle of the pipe at one end while inspection is carried out visually from another end. Any foreign material or shots/grit present in the pipe shall be completely removed by mechanical brush, high pressure air jets or by tilting of pipe, etc.

7.1.16 The maximum allowable elapsed time between completion of the final blasting operations and commencement of the chemical pre-treatment or coating process shall be such that no detectable oxidation of the surface occurs. Relative humidity readings shall be recorded every half an hour during the blasting operations in the immediate vicinity of the operations. The maximum elapsed time shall not exceed the duration given below:

Table 8

Relative Humidity (%)	Maximum Elapsed Time
> 80	2 hours
70 to 80	3 hours
< 70	4 hours

Any pipe not processed within the above time-humidity requirement shall be completely re-blasted. Any pipe showing flash rusting shall be re-blasted even if the above conditions have not been exceeded. The dew point shall be 3°C less than the pipe temp. & RH shall be less than 85%.

7.2 Chemical pre-treatment with phosphoric acid solution (if specified):

7.2.1 All pipes shall be provided chemical pre-treatment with phosphoric acid solution having concentration of 10% (+2%). Oakite 31 / 33 or equivalent shall be used to remove all soluble salts and other soluble contaminants.

7.2.2 The applicator shall provide data sheets and supporting documentation for the phosphoric acid to be used. The documentation shall verify that the phosphoric acid is suitable for the treatment of line pipe prior to the application of the specific fusion bonded epoxy powder and the final coating will meet fully the requirements of this specification.

7.2.3 The pipe temperature immediately prior to the phosphoric acid treatment shall be in the range of 45 to 70°C.

7.2.4 The dwell time of the phosphoric acid wash on the pipe surface shall be minimum 20 s or as recommended by the manufacturer.

7.2.5 The ph of the pipe surface shall be determined after dwell time at a frequency of once per hour. The measured ph shall be as follows:

After phosphoric acid wash: 1 to 2

7.2.6 Phosphoric acid treatment shall be followed immediately by washing with de-ionized (di) water. De-ionized water used shall conform to the following requirements:

Table 9

Sl. No.	Properties	Unit	Requirements
a.	Turbidity	NTU	1 max.
b.	Conductivity	µS/cm	5 max.
c.	Hardness	-	Nil
d.	Total Alkalinity as CaCO ₃	mg/l	2 to 3
e.	Chloride as Cl ⁻	mg/l	1 max.
f.	Sulphate as SO ₄ ⁼	mg/l	1 max.
g.	pH	-	6.5 to 7.5

Tests to determine the above properties shall be carried out in accordance with “Standard Methods for the Examination of Water and Wastewater” published jointly by American Public Health Association, American Water Works Association and Water Pollution Control Federation.

Quality of the de-ionized water shall be monitored at the start of each shift and at every four hours interval. Non-compliance of de-ionized water w.r.t. the above requirements shall cause stoppage of the operations.

High pressure water rinse (>1500 psi) after phosphoric acid wash shall be used to remove any trace of treatment residue. A minimum 1 liter of de-ionized water per square meter of pipe surface area shall be used and correct rinsing volume shall be established in order to ensure that pH of pipe surface shall be in the range of 6 to 7.

7.2.7 The pH of the pipe surface after the de-ionized water rinse shall be checked at a frequency of once in every hour. pH value shall be as follows:

After de-ionized water wash: 6 to 7

7.2.8 After the de-ionized water wash, the pipe shall be dried with dry air, pre-heated to a temperature of 75°C to 85°C.

7.2.9 The salt tests shall be carried out after de-ionized water rinse at one end of each pipe at the blasting inspection bed. The acceptance criteria shall be 2µg/cm². An approved salt meter (SCM 400 or equivalent) shall be used to carry out salt tests and shall be calibrated in accordance with the equipment manufacturer’s recommendations.

7.3 Chemical Pre-treatment with Chromate Solution (If specified):

7.3.1 Following completion of abrasive blast cleaning, all pipe surface shall be chemically pre-treated with chromate solution having concentration of 10% (+2%), Gardobond 4504 PC or equivalent.

7.3.2 The applicator shall provide data sheets and supporting documentation for the chemical to be used. The documentation shall verify that the chemical is suitable for the treatment of line pipe prior to the application of the specific fusion bonded epoxy powder being applied and the final coating will meet fully the requirements of this specification.

7.3.3 The chemical pre-treatment shall be applied fully in accordance with the chemical manufacturer’s instructions and in a manner that ensures 100% coverage of the pipe surface without introducing surface contamination.

7.3.4 The applicator shall check that the concentration of the chemical pre-treatment solution remains within the above range or as recommended by the chemical manufacturer for the pipe coating process. The concentration shall be checked at start of shift, every 4 h thereafter and every make-up of each fresh solution batch, using a method recommend by the chemical

manufacturer. The applicator shall also ensure that the chemical pretreatment solution remains free from contamination at all times. Recycling of chemical pre-treatment solution is not permitted.

7.3.5 The applicator shall ensure that the temperature of the substrate is maintained between 40°C and 80°C and the chromate solution temperature does not exceed 60° or as recommended by the manufacturer.

7.3.6 The chromate coating shall be smooth, even, free from runs, drips or excessive application and lightly adherent with no flaking of the coating. The chromate coated steel must be thoroughly dried immediately after application.

7.4 Coating Application:

The external surface of the abrasive blasted cleaned pipe conforming to clause 7.1,

7.2 and 7.3 of this specification shall be immediately coated with 3-Layer Polyethylene (3LPE) coating in accordance with the procedures approved by Owner, relevant standards and this specification. In general, the procedure shall be as follows:

7.4.1 Pipe Heating:

- Immediately prior to heating of pipe, all dust and grit shall be removed from inside of the pipe by a combination of air blast, brushing and vacuum cleaning. Suitable arrangement shall be made to protect the bevel ends from getting damaged during the coating operation.
- Induction heater shall be used for heating the pipe. The method shall be capable of maintaining uniform temperature along the total length of the pipe. Appropriate frequency shall be used to ensure 'deep heating' and intense skin heating is avoided. This shall be demonstrated on bare pipes prior to start of PQT. Oxidation of the cleaned pipe surfaces prior to coating (in the form of bluing or other apparent oxide formation) is not acceptable.
- External surface of the pipe shall be heated to about 225°C to 240 °C. The targeted temperature shall be selected to achieve proper wettability of steel surface. The pre-heating temperature tolerance above and below the selected target temperature should also be specified during PQT and cure time / line speed window setting should be done for the specified range. Required pipe temperature shall be maintained as it enters the FBE powder coating chamber.

The required pipe target temperature can be selected outside the 225°C to 240°C range in case of specific epoxy manufacturer's recommendation, however in no case will the target temperature be selected below 200°C or exceed 250°C

- Temperature of the pipe surface shall be continuously monitored & recorded by using optical pyrometers and checked with contact thermometers. The recording method shall allow to correlate each line pipe.

The monitoring instrument shall be able to raise an alarm/activate audio system (hooter) in the event of tripping of induction heater or in the event of pipe temperature being outside the range recommended by the manufacturer.

- Any deviation from the application temperature range recommended by manufacturer shall be rectified. If immediate rectification is not feasible, the production shall be stopped until cause of deviation has been removed. Any pipe coated during the duration of temperature deviation shall be identified by marking and rejected. Such rejected pipes shall be stripped, re-cleaned and recoated.
- Temperature measuring & monitoring equipment shall be calibrated twice every shift and/or as per Owner Representative's instruction.
- Applicator shall ensure that pipe surface emissivity variations are minimized during pipe heating. To avoid significant variance, more than once blasted joints should be coated at the same time and not mixed with joints blasted only once.

7.4.2 Pipe Coating:

- Subsequent to pipe heating, coating consisting of following layers shall be applied onto the pipe:

7.4.2.1 Electrostatic application of epoxy powder of minimum dry film thickness 0.20 mm, unless otherwise specified. The maximum thickness shall not exceed the epoxy thickness specified by epoxy powder manufacturer.

7.4.2.2 Co-polymeric or grafted adhesive application by side extrusion, having minimum thickness 0.20 mm;

7.4.2.3 HDPE application by side extrusion to minimum thickness as specified based on minimum 3LPE coating thickness on pipe body and weld seam as per Table 1.

The coated pipe shall be subsequently quenched and cooled in water for a period that shall sufficiently lower the temperature of pipe coating ($< 80^{\circ}\text{C}$) to permit handling and inspection.

- Only those coating material which are pre-qualified and approved by Owner / Consultant in accordance with provisions of Annexure I of this specification and qualified in accordance with requirements of clause 5.4.1, 5.4.2, 5.4.3, 5.4.4 and Table 2, 3, 4 & 5 of this specification shall be utilized for coating.
- All production coating application shall be carried out as per application parameters recommend by coating material manufacturers and procedure qualification tests (PQT) shall be carried out as per Clause 10.5 and Table 10, 11 & 12 of this specification.
- Coating materials shall be inspected in accordance with the manufacturer's recommendation prior to coating application and it shall be ensured that the materials are moisture free. In case

the relative humidity exceeds 80%, the adhesive and polyethylene material shall be dried using hot air dryer.

- Throughout the production, the blasting line speed, pre-heating temperature and coating line speed shall be monitored continuously and data recorded as per Table 10 & 11. Values during production run shall be within a range of +/-10% of the values and verified during PQT.

Variation of the recorded temperature values versus the set pre-heating temperature shall be within range of 5% along the pipe length with the exception of the cut back lengths.

During production, if the above parameters (i.e., blasting speed, pre-heating temperature and the coating line speed, etc.) require modification from the approved PQT, a new PQT shall be performed.

Prior to starting the application of fusion bonded epoxy powder, the recovery system shall be thoroughly cleaned to remove any unused powder remaining from a previous line pipe coating application. The use of recycled powder shall be permitted subject to:

7.4.2.4 Satisfactory qualification of the reclaimed system during PQT stage;

7.4.2.5 The proportion of the reclaimed powder in the working mix does not exceed 20% at any one time;

7.4.2.5.1 The quality of the recycled powder being routinely checked during production, at a minimum frequency of once per shift and consistently meets the requirements stated at per Clause para 5.4.1 and Table 2.

7.4.2.5.2 Dry compressed air (free of oil and moisture) shall be used in the coating chamber and FBE spraying system. Filters, dehumidifier / dryer as required along with control and monitoring system shall be provided for this purpose. Dew point of compressed air used to supply the fluidized bed, epoxy spray system and epoxy recycling system shall be at least (-) 40°C and this shall be monitored and checked during PQT and regular production at frequency of start of each shift, then once in a shift and at any breakdown.

7.4.2.6 Air pressure in the epoxy spray guns shall be controlled, continuously monitored and recorded by using suitable instruments. The air pressure shall be controlled within the limits established during coating procedure qualification. The monitoring system shall be able capable of raising an alarm / activate audio system (hooter) in the event of change in air pressure beyond the set limits. Any deviation from the pre-set limits shall be rectified. If immediate rectification is not feasible, the production shall be stopped until cause of deviation has been removed. Any pipe coated during the duration of air pressure deviation shall be identified by suitable marking and rejected. Such rejected pipes shall be stripped and recoated.

Thickness of cured FBE layer shall be minimum 0.2 mm as specified in Table 1.

7.4.2.7 Extruded adhesive layer shall be applied before gel time of the epoxy coating has elapsed and within the gel time window recommended by FBE manufacturer. Applicator shall establish, to the satisfaction of the Owner's Representative, that the adhesive is applied within the gel time window of epoxy and at the temperature recommended by the adhesive manufacturer. Applicator shall state the minimum and maximum time interval between epoxy and adhesive application at the proposed pre-heat temperature and line speed. The extrusion temperature of the adhesive film shall be continuously recorded.

7.4.2.7.1 Thickness of extruded adhesive layer shall be minimum 0.20 mm as specified in Table 1.

7.4.3 Adhesive layer shall be continuous and free of void, air entrapment. Under no circumstances polyethylene top layer can be in contact FBE layer.

- Extruded polyethylene layer shall be applied over the adhesive layer within the time limit established during PQT stage and within the time/temperature range recommended by the manufacturer. The extrusion temperature of polyethylene film shall be continuously recorded. The monitoring instruments shall be independent of the temperature control equipment. The instruments shall be calibrated prior to start of each shift. The applied coating shall be cooled to a temperature (<80°C) that prevents handling damage during finishing and final inspection.

7.4.3.1 Thickness of extruded polyethylene layer and 3LPE coating shall be as specified in Table 1.

- Applicator shall ensure that there is no entrapment of air or void formation along the seam weld (where applicable) during application of coating. Air entrapment below the coating and also along the coating overlap shall be prevented by forcing the coating on to the pipe using high pressure roller of suitable design during coating application. In case it is not adequately achieved, Applicator shall supplement by other methods to avoid air entrapment. The methods used shall be witnessed and approved by Owner.

- Resultant coating shall have a uniform gloss & aesthetic appearance and shall be free from air bubbles, wrinkles, holidays, irregularities, discontinuities, separation between layers of polyethylene & adhesive, etc.

- 3LPE coating shall terminate 150 mm (+) 20/ (-) 0 mm from pipe ends.

Applicator shall adopt mechanical brushing and / or tooling device for termination of 3LPE coating at pipe ends. Edge of the polyethylene layer shall be shaped to form a bevel angle not exceeding 30° in the direction of pipe axis.

FBE layer at the cut back shall protrude 20+/-5mm from the edge of the toe of the polyethylene layer. Damaged FBE toe shall be repaired aesthetically using compatible liquid epoxy, recommended by FBE manufacturer.

8 COATING PROCEDURE QUALIFICATION:

8.1 Procedure Qualification Tests (PQT):

Procedure Qualification Tests (PQT) shall be carried out only after obtaining written approval of the above procedures and Inspection and Testing Plan (ITP) from the Owner. No change in the procedure shall be made after the Owner has given approval.

At the start of the project, the Applicator shall, at his expense, carry out a coating Procedure Qualification Tests (PQT). During PQT, the following shall be carried out by the Applicator:

8.1.1 Qualify various procedures forming a part of coating operations mentioned above and as detailed subsequently;

8.1.2 Carry out raw material testing on the batches of all coating materials to be used for PQT viz. FBE epoxy powder, adhesive granules, PE top coat granules, confirming compliance to properties as per clauses 5.4.1, 5.4.2 and 5.4.3 respectively;

8.1.3 3LPE coating application to prove that plant, materials, and coating procedures result in a quality of end product conforming to the properties stated in Clause 5.3, 5.4.4 and Table 10, 11 and 12 of this specification, relevant standards, specifications and material manufacturer's recommendations;

8.2 PQT's shall be carried for the following scenarios:

8.2.1 For each pipe diameter on maximum wall thickness (wall thickness to be decided by the Owner);

8.2.2 For each type of pipe (ERW);

8.2.3 For each coating material combination

8.2.4 For each plant.

Applicator shall give seven (7) working days' notice to witness all procedures and tests.

A batch representing a normal production run, typically 15 pipes, shall be coated in accordance with the approved coating procedure and the coating operations shall be witnessed by Owner or its Representative. Out of these pipes, at least one pipe at the start & one pipe at the end of PQT shall be coated partly with epoxy layer (approx. 3-4 m), partly with both epoxy & adhesive layers (approx. 3-4) and rest portion with all the three layers. Remaining pipes shall have all the three layers.

At least 7 (seven) test pipes shall be selected by Owner or its Representative for coating procedure qualification tests and shall be subjected to procedure qualification testing as described hereinafter. Owner or its Representative shall witness all tests. Out of 7 (seven) test pipes, 2 (two) pipes partly coated with epoxy layers and partly coated with both epoxy & adhesive layers shall be included. Remaining 5 (five) test pipes shall have all the three layers.

On successful completion of PQT, coating of all seven pipes shall be removed completely and recoated as per approved coating procedure at Applicator's expense. Remaining 8 (eight) pipes will be accepted by Owner provided they meet the requirements of this specification and need not be stripped and re-cycled.

8.3 Qualification of Procedures:

8.3.1 Epoxy Powder Application & Recycling:

During procedure qualification, number of guns for electrostatic spray of FBE powder (virgin and reclaimed), air pressure in the epoxy spray guns, satisfactory functioning of monitoring system, line speed v/s coating thickness, etc. shall be established.

Dew point of compressed air used to supply the fluidized bed, epoxy spray system and epoxy recycling system shall be recorded during the PQT.

Also, Applicator shall remove 2 samples of reclaimed powder from the reclamation system. These samples of reclaimed powder shall be subjected to detailed visual examination, laboratory testing (gel time, density, thermal analysis, particle size, and moisture content, etc.). The properties of the reclaimed powder shall be within the range specified by the manufacturer of epoxy powder. In case the properties of the reclaimed powder are out of the range specified by the manufacturer, Applicator shall not use the reclaimed powder during the regular production.

8.3.2 Pipe Pre-heating:

The Applicator shall establish the temperature variation due to in-coming pipe temperature, line speed variation, wall thickness variation, emissivity, interruptions, etc. and document the same during the PQT stage. During PQT, proper functioning of pipe temperature monitoring and recording system including alarm / hooter shall be demonstrated to the Owner Representative.

8.3.3 Surface Preparation

The procedure to clean and prepare the pipe surface shall be in accordance with the requirements of this specification. Blasting speed, ratio of shot to grit shall be established during procedure qualification testing, such that the resultant surface profile is not dished and rounded. The qualification shall be performed through a visual inspection, measurement of

roughness and check of the presence of salt contamination & dust on the abrasive blast cleaned pipe surface.

8.3.4 Chemical Pre-treatment:

8.3.4.1 Phosphoric Acid Wash followed by De-ionized Water Wash (If specified):

The procedure to apply the chemical pre-treatment viz. phosphoric acid wash followed by de-ionized water wash shall be in accordance with the recommendations of the manufacturer and shall result in intended cleaning requirements of this specification. Working solution preparation, maintaining concentration, application procedure including method of spreading, spreading rate, drying times, etc. depending upon the cleanliness / temperature of the incoming pipe and the line speed shall be established. Pipe pre-heat temperature vs line speed vs dwell time, rinsing procedure including pressure of the rinse water, testing & control, rectification measures, drying procedure etc. shall be clearly established during PQT. Also, the quality of the de-ionized water shall be established during PQT.

8.3.4.2 Chromate Treatment (if specified):

The procedure to apply the chromate treatment shall be in accordance with the recommendations of the manufacturer. Working solution preparation, maintaining concentration, pipe temperature before application, chromate solution temperature, application procedure including method of spreading, drying times, etc. depending upon the temperature of the incoming pipe and the line speed shall be established. Pipe temperature vs. line speed, testing & control, rectification measures shall be clearly established during PQT.

8.3.5 Coating Application:

The Owner Representative will check the correctness of each coating application operation, values of the main parameters of each operation, pre-heating pipe surface temperature prior to epoxy powder application temperature, line speed, fusion bonded epoxy gel / curing time, temperature and flow rate of co-polymer adhesive and polyethylene, etc. and the same shall be recorded. These values shall be complied with during regular production.

8.4 Qualification of Coating Repair:

During PQT, Coating repair qualification shall be carried out using approved repair materials and approved procedure by competent Repair personnel or Insulator under supervision of QC Inspector or Engineer.

Type of Repair	No. of Location / Test	Detailed Inspection
Cosmetic Repair (By heating & rolling)	1 Pipe (2 Locations)	Visual

Repair with Melt Stick	1 Pipe (2 Locations)	Visual, Thickness and Holiday Inspection
Patch Repair	1 Pipe (2 Patches)	Visual, Thickness, Holiday Inspection @25 kV Peel Test: ≥ 2.5 N/mm @23±3°C; ≥ 0.2 N/mm @80±3°C; No separation of epoxy layer from the steel surface.
Heat- shrinkable Sleeve (HSS) Repair (System 14-B of ISO 21809-3)	1 Pipes (2 HSS)	Visual, Thickness, Holiday Inspection @25 kV Peel Test (Table 17 of ISO 21809-3): ≥ 5 N/mm @23±3°C; ≥ 0.3 N/mm @80±3°C; No separation of epoxy layer from the steel surface.

On successful completion of coating repair qualification activities and its inspection & testing, Repair Materials, Repair Personnel or Insulator and Repair Procedure are qualified for the entire project.

8.5 Qualification of Applied Coating during PQT:

Procedure Qualification tests shall be carried out on partly coated epoxy, adhesive and fully 3LPE coated pipes, as detailed here under in accordance with Table 12 of this specification.

8.5.1 Tests on pipe coated partly with Epoxy (FBE) and partly with Epoxy & Adhesive Layers:

8.5.1.1 Degree of Cure:

Epoxy film samples (minimum 4 nos./pipe) shall be scrapped from the coated pipe and the samples shall be taken for cure test using Differential Scanning Calorimetry (DSC) procedure mentioned in Annexure D of ISO 21809-1. Care shall be taken to remove the samples of full film thickness avoiding inclusion of steel debris. Glass transition temperature differential (Tg) and % cure (H1) shall comply with the requirements as specified in Clause 5.4.4 and Table 5.

8.5.1.2 Epoxy Layer Thickness:

Epoxy layer thickness shall be checked on two pipes at every one meter spacing at 3, 6, 9 and 12 o'clock positions using calibrated digital thickness gauge as per ISO 2808. The thickness shall comply with the requirement as specified in Table 1.

Digital thickness gauge shall be verified at the start of each shift using standard foil or shim within 5% tolerance.

8.5.1.3 Adhesive Layer Thickness:

Adhesive layer thickness shall be checked two pipes at every one meter spacing at 3, 6, 9 and 12 o'clock positions using calibrated digital thickness gauge as per ISO 2808. The thickness shall comply with the requirement as specified in Table 1.

Digital thickness gauge shall be verified at the start of each shift using standard foil or shim within 5% tolerance.

8.5.1.4 Holiday Inspection:

Epoxy coated portion of two pipes shall be subjected to holiday inspection as per Clause 10.3.2 of ISO 21809-2 and the test voltage shall set to 5V per μm of minimum specified epoxy coating thickness. There shall be no holiday on epoxy coated portion (Refer Clause 5.4.4 and Table 5).

8.5.1.5 Dry Adhesion:

Dry adhesion test on epoxy coated pipe section of two pipes shall be carried out as Clause A.4 of ISO 21809-2. The adhesion rating obtained shall be either 1 or 2 (Refer Clause 5.4.4 and Table 5).

8.5.1.6 Hot Water Adhesion:

24 h Hot Water Adhesion Test @ $75\pm 3^{\circ}\text{C}$ on epoxy coated pipe section of two pipes shall be carried out as per clause A.16 of ISO 21809-2. The rating obtained shall be from 1 to 2 (Refer Clause 5.4.4 and Table 5).

8.5.1.7 Porosity:

Cross-Section Porosity and Interface Porosity tests shall be carried out on the epoxy coated pipe section of two pipes. Test method shall be as per clause A.12 of ISO 21809-2. Acceptance shall be less than or equal to Figures A.11 & A.12 of ISO 21809-2 (Refer Clause 5.4.4 and Table 5).

8.5.1.8 Flexibility:

2° Flexibility test at 00C shall be conducted on ring specimen obtained from epoxy coated pipe section of two pipes as per clause A.13 of ISO 21809-2. No cracking, tear disbondment or delamination shall be observed (Refer Clause 5.4.4 and Table 5).

8.5.1.9 Impact Test:

1.5 J Impact test at 00C shall be conducted on ring specimen obtained from epoxy coated pipe section of two pipes as per clause A.14 of ISO 21809-2. There shall be no holiday on impact area (Refer Clause 5.4.4 and Table 5).

8.5.2 Tests on Pipes Coated with all Three Layers:

8.5.2.1 Visual Inspection:

Immediately following the coating, each coated pipe shall be visually checked for imperfections and irregularities of the coating. The coating shall be of natural colour and gloss, smooth and uniform and shall be blemish free with no dust or other particulate inclusions. The coating shall not show any defects such as blisters, pinholes, scratches, wrinkles, engravings, cuts, swellings, disbonded zones, air inclusions, tears, voids or any other irregularities. Special attention shall be paid to the areas adjacent to the longitudinal weld (if applicable), adjacent to the cut-back at each end of pipe and within the body of the pipe.

In addition, inside surface of the pipe shall also be visually inspected for presence of any foreign material or shots and grit (free or embedded/sticking to pipe inside surface). The pipe inside surface shall be examined using sharp floodlight focused at the middle of the pipe at one end while inspection is carried out visually from another end.

8.5.2.2 Coating Thickness Measurement:

All 3LPE coated pipes shall be subject to coating thickness measurement using digital thickness gauge in accordance with ISO 2808. Digital thickness gauge shall be verified at the start of each shift using standard foil or shim within 5% tolerance.

The coating thickness shall be determined by taking at least 12 measurements at locations uniformly distributed over the length and periphery of each pipe. If any of these 12 readings is below the minimum coating thickness, carry out additional four readings around this area. The average of the additional four readings and the initial reading shall be higher than the minimum thickness.

Take the measurements at points distributed along four equally spaced longitudinal lines at pipe length with three equally circumferential lines on the middle of the pipe and at a distance of 300 mm from the end of the coating cutback.

In case of welded pipes, 6 of these readings shall be made at the apex of the weld seam, uniformly distributed over the length of the coated pipe. All readings must meet the minimum requirements. Acceptance criteria shall be as per Clause 5.3 and Table 1.

8.5.2.3 Holiday Detection:

High voltage pulse DC full circle electronic holiday detector (with audible alarm and precise voltage control) shall be used to check continuity of applied finished coating.

Applicator shall calibrate the holiday detector at least once every 4 hours of production.
Applicator shall have necessary instruments or devices for calibrating the holiday detector.

Holiday detector shall be set to test voltage min. 25 kV and testing speed shall not exceed 300 mm / s. Holiday detection shall be carried out in accordance with Annex B of ISO 21809-1.
The finished coating shall be free of holiday (Refer Clause 5.4.4 and Table 7).

Any pipe coating shall be rejected if no. of holiday and size of defect/ damage/ holiday exceed as detailed in Clause 13 of this specification.

8.5.2.4 Peel (Adhesion) Strength:

Five test pipes shall be selected for Peel strength tests as per Annex C (C2) of ISO21809 -1. On each of the selected pipes, three peel tests shall be performed for each specified temperature ($23\pm 3^{\circ}\text{C}$ & $80\pm 3^{\circ}\text{C}$), one at each end and one in the middle of the pipe. Specified peel strength requirement at each temperature shall be complied with and there shall be no disbonding between steel & epoxy (Refer Clause 5.4.4 and Table 7). Length of peel shall be minimum 140 mm. None of test pipes shall fail.

8.5.2.5 Impact Strength:

Three test pipes shall be selected for impact strength test as per Annex E of ISO 21809-1 at $23\pm 3^{\circ}\text{C}$. Minimum thirty (30) impacts (with impact energy min. 7J/mm) located equidistant (>50 mm) along the length of the pipe shall be performed. Immediately after testing, the test area shall be subjected to holiday detection @25 kV. There shall be no holiday on impact area (Refer Clause 5.4.4 and Table 7).

8.5.2.6 Indentation Resistance:

Five test pipes shall be selected for indentation resistance test and two samples from each pipe at each temperature shall be taken and tested as per Annex F of ISO 21809-1 for temperatures $23\pm 2^{\circ}\text{C}$ and $80\pm 2^{\circ}\text{C}$. The test shall comply with the specified requirement (Refer Clause 5.4.4 and Table 7) and none of the test samples shall fail.

8.5.2.7 Air Entrapment:

One sample each from pipe body and on weld (if applicable) shall be taken from all 3LPE coated pipes. Strips from adhesive strength tests or coated pipes shall be used to determine the porosity of the finished coating. Strip shall be cut from longitudinal

/ spiral weld (if applicable) and examined for presence of voids.

Peel strength test strip shall be viewed from the side and at the failure interface. At the peel strength test location, utility knife shall be used to cut the edge of the coating to a 45° angle and viewed under microscope. Similar examination shall be done in the coating cut back area.

One sample each either on the peel strength strip or coated pipe and strip cut from the longitudinal weld (if applicable) shall be examined for air entrapment per shift. Strips shall be viewed from the side.

All examination shall do using a 30X magnification hand-held microscope. The polyethylene and adhesive layers shall have no more than 10% of the observed area taken up with air entrapment (porosity or bubbles). Air entrapment shall not occupy more than 10% of the thickness in each case. Bubbles shall not link together to provide a moisture path to the epoxy layer.

8.5.2.8 Degree of Cure:

Epoxy film samples (minimum 4 no., equally spaced) shall be scrapped from one 3LPE (PQT) coated pipe and the samples shall be taken for cure test using Differential Scanning Calorimetry (DSC) procedure. Silicon coated sulphite paper or other equivalent shall be placed between the epoxy layer and adhesive layer immediately after epoxy application, to ensure physical separation of epoxy & adhesive as well as to prevent contamination of epoxy with adhesive layer, at a location from where the epoxy samples are to be removed for the test. Care shall be taken to remove the samples of full film thickness avoiding inclusion of steel debris. Glass transition temperature differential (ΔT_g) and % Cure shall comply with the specified requirements (Refer Clause 5.4.4 and Table 7).

8.5.2.9 Cathodic Disbondment:

The following CD tests shall be carried out on samples selected from 1 PQT test pipe in accordance with Annex H of ISO 21809-1:

- $65 \pm 3^\circ\text{C}/24\text{h}/-3.38\text{V};$
- $23 \pm 3^\circ\text{C}/28\text{d}/-1.38\text{V};$
- $80 \pm 3^\circ\text{C}/28\text{d}/-1.38\text{V}.$

The maximum disbondment acceptance criteria shall be as per Clause 5.4.4 and Table 7 of this specification.

8.5.2.10 Strain at Failure:

Six samples each from three selected coated pipes i.e., total 18 samples in all shall be tested in accordance with ISO 527-2 and the test shall comply with the specified requirement (refer Clause 5.4.4 and Table 7). None of the test samples shall fail.

8.5.2.11 Stress at Yield:

Six samples from one selected coated pipe shall be tested in accordance with ISO 527-2 and the test shall comply with the specified requirement (refer Clause 5.4.4 and Table 7). None of the test samples shall fail.

8.5.2.12 Resistance to Hot Water Immersion:

One test pipe shall be selected for hot water immersion test previously subjected to holiday test. Three samples shall be prepared from the selected test pipe and shall be placed in vessel filled with tap water already pre-heated to $80\pm 3^{\circ}\text{C}$ for 48 hours. The test method shall be as per Annexure L of ISO 21809-1.

Loss of adhesion shall be average ≤ 2.0 and maximum 3.0 mm beyond 5mm on each side of the corner. All samples shall pass the test (refer Clause 5.4.4 and Table 7).

8.5.2.13 Flexibility:

One test pipe shall be selected for Flexibility test. The test method shall be as per Annexure I of ISO 21809 Part 1. Three samples shall be prepared from the test pipe. The samples shall be placed in freezer and cooled between -2°C and 0°C and hold at that temperature for 1 hour and then bent at 2° ppd over fixed radius mandrel.

No cracking, tear, disbondment or delamination shall observe in any of the samples (refer Clause 5.4.4 and Table 7).

8.5.2.14 Product Stability during Application of HDPE Top Layer:

Three test pipes shall be selected for product stability test of PE top layer. The test method shall be as per ISO 1133-1. One sample shall be prepared from each test pipe. The measured MFR value of the applied PE layer shall be within $\pm 20\%$ of the measured MFR value of the virgin compound granulate PE of the same batch (refer Clause 5.4.4 and Table 7).

8.5.2.15 Specific Electrical Coating Resistance:

The long term Specific Electrical Coating Resistance test of 3LPE coated pipes section shall be conducted for 100 days @ 23°C in accordance with Annex J of DIN 30670. Tested value shall be $\geq 108 \Omega\text{m}^2$ (refer Clause 5.4.4 and Table 7).

The test certificate (not older than 3 years) submitted by the PE manufacturer shall be of recognized independent test laboratory with a track record of 3LPE coating testing. The test laboratory should be NABL / ISO 17025 accredited and shall have approval for conducting the above specific test as per DIN 30670.

Owner may decide to get the test conducted for 3LPE coating applied during PQT and get tested for the above long-term test at the cost of the coating applicator at an accredited independent laboratory as per above requirement.

8.5.2.16 UV Resistance and Thermal Ageing:

The followings long term tests for extruded PE top material shall be conducted in accordance with Annex G of ISO 21809-1:

8.5.2.16.1 UV Ageing Test:

Continuous irradiation of UV xenon lamp; Black standard Temperature: $65\pm 3^{\circ}\text{C}$; Relative Humidity: $65\pm 5\%$;

Test Duration: 2210 h.

8.5.2.16.2 Thermal Ageing Test:

Test Temperature: $100\pm 3^{\circ}\text{C}$; Test Duration: 4800 h (200 d).

Tested values shall meet the requirements as specified in Clause 5.4.4 and Table 7.

The test certificate (not older than 3 years) submitted by the PE manufacturer shall be of recognized independent test laboratory with a track record of 3LPE coating testing. The test laboratory should be NABL / ISO 17025 accredited and shall have approval for conducting the above specific tests as per ISO 21809-1.

Owner may decide to get the test conducted for PE top coat material 3LPE coating applied during PQT and get tested for the above long-term tests at the cost of the coating applicator at an accredited independent laboratory as per above requirements.

8.5.2.17 Hardness:

One PQT pipe shall be subjected to shore D hardness checking for PE top coat surface using calibrated Durometer in accordance with ISO 868. Minimum 5 measurements shall be taken on entire coated pipe surface. All measured hardness values shall be ≥ 55 Shore D (refer Clause 5.4.4 and Table 7).

8.5.2.18 Residual Magnetism:

One PQT pipe shall be subjected to residual magnetism checking at both pipe ends at 4 locations (circumferentially at 0° , 90° , 180° & 270° positions) using calibrated Gauss meter. All measured values shall meet the requirement of

Table 12.

After completion of the qualification procedures and PQT as per above, the Applicator shall prepare and issue to Owner for approval a detailed report of the coating procedures, methods, equipment and tools used and document above tests and inspection including test reports/certificates of all materials and coatings tested. This document will be termed as Application Procedure Specification (APS) and shall be referred during subsequent application of coating of production pipes.

On successful completion of PQT, coating of all seven test pipes shall be removed and completely recoated as per approved coating procedure at Applicator's expense. Remaining

eight pipes will be accepted by Owner, provided they meet the requirements of this specification and need not be stripped and re-cycled.

Only upon written approval from Owner, Applicator/ Contractor shall commence production coating.

9 RE-QUALIFICATION OF PROCEDURE QUALIFICATION:

9.1 The Applicator shall re-establish the requirements of qualification and in a manner as stated before or to the extent considered necessary by Owner, in the event of, but not limited to, the following:

9.1.1 Every time there is a change in the previously qualified procedure;

9.1.2 Every time there is a change in the manufacturer and change in formulation of any of the raw materials and change in location of raw material manufacture;

9.1.3 Every time the coating yard is shifted from one location to the other or every time the critical coating equipment (induction heater, epoxy spray system, extruder, etc.) are shifted;

9.1.4 Any change in line speed during coating application;

9.1.5 Any time when in Owner's opinion the properties are deemed to be suspect during regular production tests.

Owner reserves the right to conduct any or all the test required for qualification through an independent laboratory or agency at the cost of Applicator, when in Owner's opinion, the results are deemed suspect. Owner's decision shall be the final.

10 COATING PROCEDURE TESTS DURING PRODUCTION:

Production tests shall be carried out on partly coated epoxy, adhesive and 3LPE coated pipes as detailed here under and Table 10, 11 & 12 of this specification

10.1 Raw Material Testing:

Raw material testing shall be conducted on all the batches of all coating materials to be used for production viz. FBE epoxy powder, co-polymeric melt adhesive granules, PE top coat granules to confirm compliance as per clause 5.4 sub clauses 5.4.1,

10.2 External Pipe Surface Preparation:

Prior to coating application, the pipe steel surface shall be abrasive blasted as per Clause 7.1, followed by inspected and tested after 2nd abrasive blasting as per Table 10 to ensure compliance to required surface cleanliness, surface roughness, residual dust level, salt contamination, etc.

10.3 Chemical Pre-treatment with Phosphoric Acid Solution and / or Chromate Treatment (If specified by the Owner):

Depending on requirements, each pipe shall be subjected to Chemical Pre-treatment with Phosphoric Acid Solution followed by high pressure water rinse and / or Chromate Treatment in accordance with Clauses 7.2 & 7.3 of this specification. Treated pipe surface shall be inspected and tested in accordance with Table 11 in order to ensure characteristics of pipe surface prior to induction heating.

10.4 Pre-heating of Pipe Surface:

Pre-heating of the pipe surface shall be carried using suitable rated induction coils. The temperature and other application parameters, set during procedure qualification testing will be maintained during production and the pre-heat temperature of the pipe before entering the FBE booth shall be recorded and monitored continuously as per Table 12 of this specification.

10.5 3LPE Coating Application:

10.5.1 3LPE coating application shall be carried out as per Application Procedure Specification (APS) approved by the Owner. After successful completion of coating procedure qualification as per Clause 8, various stages of coating application shall be measured, monitored and inspected in accordance with Table 12 of this specification.

Table 10 — Requirements for inspection of surface preparation of pipe

Sl. No.	Properties	Test Method	Requirements	Frequency	
				During PQT	During Production
1	Surface condition of pipe before blasting	Visual Inspection	Free of contaminations and surface defects	Each pipe	Each pipe
2	Relative humidity	Measurement/ as required	Record (relative humidity shall be < 85%)	Every ½ h	Every ½ h
3	Pipe temperature before blasting	Thermocouple	min. 3°C above dew point	Each pipe	Every 1 h
4	Size, shape and properties of virgin abrasive	Visual + Certification as per ISO 11124-3	Conformity to certificate and compliance with manufacturing/ working procedure	Every batch	Every batch

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Volume II
of II

Bid Document No. BGL/719/2025-26

Sl. No.	Properties	Test Method	Requirements	Frequency	
				During PQT	During Production
5	Water soluble contamination abrasives	ASTM D4940	Conductivity \leq 60 μ S/cm	Once	1/shift
6	Abrasive blasting line speed	Stop watch	As per approved Qualification procedure	Each pipe	1/shift
7	Soluble salt after blasting (at one end)	ISO 8502-6 or ISO 8502-9 or SSPC Guide 15	Salt (Chloride) content as (NaCl) max. 20 mg/m ² (2 μ g/cm ²)	Each pipe	Each pipe
8	Surface roughness of blasted surface	ISO 8503-4 or ISO 8503-5	Rz / Ry5: 75 μ m to 100 μ m	Each pipe	Each Pipe
9	Visual inspection of blasted surface	ISO 8501-1	Grade Sa 2½	Each pipe	Each pipe
10	Presence of dust after dust removal	ISO 8502-3	max. class 2 (for both size and quantity)	Each pipe	Every 1 h

Table 11 — Requirements for Inspection of Chemical Pre-treatment (If specified):

Sl. No.	Properties	Test Method	Requirements	Frequency	
				During PQT	During Production
A: Chemical-pretreatment with Phosphoric Acid Solution (Oakite 31/ Oakite 33 or Equivalent)					
1	Concentration of phosphoric acid solution	Titration	10(+2) %	Prior to start of PQT	Start of shift, every 4 h thereafter and every make-up of each fresh solution batch
2	Pipe Temperature before acid wash	Thermocouple	45°C to 750C	Each pipe	Every 1 h

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Volume II
of II

Bid Document No. BGL/719/2025-26

3	Dwell time	Stop watch	Minimum 20 s or as per manufacturers recommendation No drying out of acid solution on surface	Each pipe	Every 1 h
4	pH of pipe surface after acid wash	Litmus paper	1 to 2	Each pipe	Every 1 h
Sl. No.	Properties	Test Method	Requirements	Frequency	
				During PQT	During Production
5	Pressure of water rinse after acid wash	Pressure Gauge	Min. 1500 psi (*)	Each pipe	Every 1 h
(*A minimum of 1 liter of DI water per m2 shall be used to be established during PQT)					
6	pH of pipe surface after high pressure water rinse	Litmus paper	6 to 7	Each pipe	Every 1 h
7	Temperature of hot air used for pipe drying after water rinse	Monitor and record	75°C to 850C	Once	Every 1 h
8	Quality of de-ionized water	As per Clause 7.2.6	As per Table 9	One Sample (Prior to start of PQT)	At start of shift and then Every 4 h
B: Chemical-pretreatment with Chromate Solution (Gardobond 4504 PC or Equivalent (If specified):					
9	Concentration of chromate solution	Titration	10(+2) %	Prior to start of PQT	At start of shift, every 4 h thereafter and every make-up of each fresh solution batch
10	Chromate solution temperature	Thermocouple or Glass Thermometer	<60°C or as recommended by the manufacturer	Once	Every 1 h

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

11	Pipe Temperature before application of chromate solution	Thermocouple	40°C to 800C or as recommended by the manufacturer	Each pipe	Every 1 h
12	Coverage	Visual	100% coverage of pipe surface	Each pipe	Each pipe

Table 12 — Requirements for Inspection of Plant Applied Coating (PQT & Production)

Sl. No.	Properties	Test Method	Requirements	Frequency	
				During PQT	During Production
1	Dew Point of compressed air	ASTM D4285	No indication of oil, water, Dew Point: at least -40°C	Prior to start of PQT	Start of shift & then 1/shift and at breakdown
2.0	Epoxy (FBE) Layer				
2.1	Visual inspection of pipes prior to introduction to coating line	Visual	No rust	Each pipe (100% surface area)	Each pipe (100% surface area)
2.2	Induction Coil Setting	As per APS and Clause 7.4.1.3 of this specification	As per approved APS	Each pipe	Continuous monitoring
2.3	Pipe temperature	As per APS & Clause 7.3.1.3 of this specification	225 to 2400C	Continuous monitoring & recording	Continuous monitoring & recording
2.4	Recording of application parameters (Coating line speed, No. of epoxy guns, epoxy gun pressure, inter-coat time, % of)	As per Clause 7.4	As per Approved APS	Each pipe	Start of shift & then 1/shift and each breakdown / restart (partly coated)



PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Volume II
of II

Bid Document No. BGL/719/2025-26

2.5	Air pressure in epoxy spray guns	As per Clause 7.3.2.7 of this specification	As per APS	Each pipe	Continuous monitoring & recording
2.6	Testing of reclaim FBE powder (If used) (Gel time, density, thermal analysis, particle size, moisture content)	As per APS & Clause 4.3 a, 5.4.1 & 8.4.1 of this specification	As per Clause 5.4.1 & 7.4.2.5, Table 2	Once in PQT	Once / shift
2.7	Minimum Epoxy Layer Thickness (DFT)	ISO 2808, Clause 8.6.1 b.	≥ 0.200 mm	2 Pipes	Start of shift & at breakdown / restart (partly coated)

Sl. No.	Properties	Test Method	Requirements	Frequency	
				During PQT	During Production
2.8	Degree of Cure % Cure ΔTg	ISO 21809-1 Annex D, Clause 8.6.1.1.	Min. 95% -3°C ≤ ΔTg ≤ + 3°C	4 Samples x 2 Pipes	1/shift (1sample)
2.9	Holiday Detection (Test Voltage set to 5V per μm of minimum specified epoxy coating thickness)	ISO 21809-2 Clause 10.3.2, Clause 8.6.1.4.	No holidays	2 Pipes	Not required

2.10	Dry Adhesion	ISO 21809-2 Clause A.4, Clause 8.6.1.5.	Rating 1 or 2	2 Pipes	Not required
2.11	Hot Water Adhesion 24 h at 75°C+3°C	ISO 21809-2 Clause A.16, Clause 8.6.1.6.	Rating 1 to 2	2 Pipes	1/shift (1 sample)
2.12	Cross-Section Porosity	ISO 21809-2 Clause A.12, Clause 8.6.1.7.	≤ compared with Fig. A.11 of ISO 21809-2	2 Pipes	1/shift (2 samples)



PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Volume II
of II

Bid Document No. BGL/719/2025-26

2.13	Interface Porosity	ISO 21809-2 Clause A.12, Clause 8.6.1.7.	≤compared with Fig. A.12 of ISO 21809-2	2 Pipes	1/shift (2 samples)
2.14	Flexibility at 0°C	ISO 21809-2 Clause A.13, Clause 8.6.1.8.	No cracking, tear, disbondment or delamination at 2° ppd length	2 Pipes	Not required
2.15	Impact Resistance at 0 °C	ISO 21809-2, Clause A.14, Clause 8.6.1.9.	> 1.5 J	2 Pipes	Not required
3.0	Adhesive Layer:				
3.1	Minimum Adhesive Layer Thickness	ISO 2808, Clause 8.6.1.3.	≥ 0.200 mm	2 Pipes	Start of shift & at breakdown / restart (partly coated)
3.2	Extrusion temperature of adhesive	As per APS & Clause 7.4.2.8 of this specification	As per APS or recommended by manufacturer	Continuous monitoring & recording	Continuous monitoring & recording

Sl. No.	Properties	Test Method	Requirements	Frequency	
				During PQT	During Production
4.0	HDPE Layer and 3LPE Coating:				
4.1	PE Extrusion temperature	As per APS & Clause 7.4.2.9 of this specification	As per APS or recommended by manufacturer	Continuous monitoring & recording	Continuous monitoring & recording
4.2	Coating temperature after water quenching	As per APS and Clause 7.4.2.1 & 7.4.2.9 of this specification	< 80°C	Each pipe	Every 1 h
4.3	Visual Inspection	Visual, Clause 8.6.2.1.	As per Clause 8.6.2.a. of this specification	Each pipe 100% surface area	Each pipe 100% surface area
4.4	Coating Thickness	ISO 2808, Clause 8.6.2.2.	Table 1 of this specification	Each pipe	Each pipe
4.5	Holiday Detection (test voltage shall be min. 25 kV & travel speed)	ISO 21809-1, Annex B, Clause 8.6.2.3.	No holiday in finished coating	Each pipe 100% surface area	Each pipe 100% surface area



PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Volume II
of II

Bid Document No. BGL/719/2025-26

	shall not exceed 300 mm/s)				
4.6	Peel Strength of 3LPE Coating at 23°C +/- 3°C at 80°C +/- 3°C	ISO 21809-1 Annex C2, Clause 8.6.2.4.	≥18 N/mm 23±3°C, ≥5 N/mm 80±3°C, (No disbonding between steel & epoxy)	5 pipes x 3 tests (@ both ends & middle)	2 h for pipe ends (cutback portion) & 4 h for middle of pipe
4.7	Impact Strength @ 23±3°C, 30 impacts	ISO 21809-1 Annex E, Clause 8.6.2.5.	>7J/mm. No holiday on impact area	3 Pipes	2 Pipes/shift
4.8	Indentation resistance @ 23 ± 2°C @ 80 ± 2°C	ISO 21809-1 Annex F, Clause 8.6.2.6.	≤ 0.2 mm @ 23±2 °C, ≤ 0.4 mm @ 80±2 °C.	5 Pipes X 2 Samples at each temp.	2 pipes/ shift
4.9	Air Entrapment	Clause 8.6.2.7. of this specification	≤ 10% & as per clause 8.6.2.g. of this specification	5 pipes x 1 sample from body & 1 sample from weld (if applicable)	1Pipe/shift 1 sample from body & 1 sample from weld (if applicable)
4.10	Degree of Cure	ISO 21809-1 Annex D, Clause 8.6.2.8.	-3°C ≤ ΔTg ≤ +3°C, Cure: Min 95%.	1 Pipes x 4 Samples	1st Pipe and 2 Pipes /shift (1sample/pipe)

Sl. No.	Properties	Test Method	Requirements	Frequency	
				During PQT	During Production
4.11	Cathodic Disbondment		Average Disbondment Radius)	---	---
	@65 °C/ 24 h; - 3.38 V	ISO 21809-1 Annex H, Clause 8.6.2.9.	≤ 4 mm	1 Pipe	1 Pipe / day
	@23 °C/ 28 d; - 1.38 V		≤ 5 mm	1 Pipe	Not required
	@80 °C/ 28 d; - 1.38 V		≤ 15 mm	1 Pipe	Not required
4.12	Strain at Break @23±3°C	ISO 527-2, Clause 8.6.2.10.	≥ 400%	3 Pipes x 6 Samples	Once per PE batch



PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Volume II
of II

Bid Document No. BGL/719/2025-26

4.13	Stress at Yield at 23°C ± 3°C	ISO 527-2, Clause 8.6.2.11.	≥17 MPa	1 Pipe x 6 Samples	Not required
4.14	Resistance to Hot Water Immersion (80±3°C, 48 h)	ISO 21809-1 Annex L, Clause 8.6.2.12.	Avg. ≤ 2 mm & Max. ≤ 3 mm,	1 Pipe	Once/ day
4.15	Flexibility (@0°C, 2°ppd)	ISO 21809-1 Annex I, Clause 8.6.2.13.	No cracking, tear, disbondment or delamination	1 Pipe (3 Samples)	Not required
4.16	Product Stability during Application of PE Top Layer	ISO 1133-1, Clause 8.6.2.14.	Δ MFR: ≤20 % (Variation between virgin compound granulate before application and coating after application of the same batch tested by applicator)	Each pipe	1st Pipe/ Shift
4.17	Specific Electrical Coating Resistance (23 °C ± 2 °C)	DIN 30670 Annex J, Clause 8.6.2.15.	≥108 Ωm ²	Review of Independent test certificate not older than 3 years as per clause 8.6.2.o	Not required (However, Owner may request to conduct the test for 3LPE coating at an accredited independent laboratory)

Sl. No.	Properties	Test Method	Requirements	Frequency	
				During PQT	During Production
4.18	UV Resistance and Thermal Ageing	ISO 21809-1 Annex G, Clause 8.6.2.16	Δ MFR: ≤35 %	Review of Independent test certificate not older than 3 years as per clause 8.6.2. p	Not required (However, Owner may request to conduct the test for PE top coat material at an accredited independent laboratory)

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

4.19	Hardness	ISO 868	≥ 55 Shore D	One pipe	Not required
		Clause 8.6.2.17.			
4.20	Cutback of 3LPE coating	Clause 7.4.2.12 of this specification	Length: 150mm (+)20/(-)0mm, Bevel Angle: <30°, FBE Toe: 20+/- 5mm	Each pipe	Each pipe
4.21	Residual Magnetism at each pipe end (@ 4 points: 0°, 90°, 180° & 270°)	Hall-Effect Gauss meter, Clause 8.6.2.18.	Avg: ≤ 2.0 mT (20 gauss). No single reading ≥ 2.5 mT (25 gauss)	1 Pipe x 4 readings	1/shift
4.22	Coating Repairs	Visual ISO 21809-1 Annex B	As per Clause 13 of this specification	1 Pipe	Each damage / defect

11 QUALITY ASSURANCE:

11.1 The Applicator shall have established a documented quality system that ensures that the requirements of this specification are met in all aspects. The Quality System shall be based upon ISO 9001 or equivalent.

11.2 The Applicator shall have established a Quality Assurance Group within its organization that shall be responsible for reviewing the quality system and ensuring that it is implemented.

11.3 The Applicator shall submit the procedures that comprise the Quality System to the Owner for agreement.

11.4 The Applicator quality system shall pay particular attention to the control of suppliers and sub-contractors and shall ensure that the requirements of this specification are satisfied by the suppliers and sub-contractors operating quality system in their organization.

11.5 The Applicator shall, prior to the commencement of work, prepare and issue a Quality Plan for all of the activities required satisfying the requirements of this specification. The plan shall include any sub-contracted work, for which the sub-contractor's quality plans shall be submitted. The plan shall be sufficiently detailed to indicate sequentially for each discipline the requisite quality control, inspection, testing and certification activities with reference to the relevant procedures and the acceptance standards.

11.6 The Applicator quality system and associated procedures may, with due notice, be subject to formal audits. The application of quality control by the Applicator will be

monitored by the Owner Representatives who will witness and accept the inspection, testing and associated work required by this specification.

11.7 The coating pipe mill shall have internal tracking system for pipe traceability during regular coating to reduce manual interference. SAP base system is preferred.

12 HANDLING, STORAGE AND TRANSPORTATION OF BARE & COATED PIPES:

12.1 The Applicator shall be fully responsible for the pipe and for the pipe identification marking from the time of "taking over" of bare pipe from Owner until such time that the coated line pipes are 'handed over' and/or installed in the permanent installation as the case may be according to the provisions of the CONTRACT.

At the time of "taking over" of bare pipes Applicator/ Contractor shall inspect and record all the relevant details referred above including pipe defects in the presence of Owner. All pipes shall be checked for bevel damages, weld seam height, dents, gouges, corrosion and other damages. Owner Representative shall decide whether pipe defects

/ damages are suitable for repair. Damage to the pipes that occur after the Applicator/ Contractor has taken delivery such as dents, flats, or damage to the weld ends shall be cut off or removed and pipes rebevelled and repaired again as necessary. The cost of this work, as well as that of the pipe lost in cutting and repair shall be to the Applicator/ Contractor's account. All such works shall be carried out after written approval of the Owner. Any reduction in length shall be indicated in the Applicator/ Contractor's pipe tracking system.

12.2 The Applicator shall unload, load, stockpile and transport the bare pipes within the coating plant(s) using suitable means and in a manner to avoid damage to pipes.

The Applicator shall stockpile the bare pipes at the storage area of the coating plant. The Applicator shall prepare and furnish to Owner a procedure/calculation generally in compliance with API RP-5L1 & API RP 5LT and prevailing guidelines/rules of statutory bodies (Road/ rail) for stacking of pipes of individual sizes, which shall be approved by Owner prior to commencement of work.

12.3 The Applicator/ Contractor shall load, unload, transport and stockpile the coated pipes within the coating plant using approved suitable means and, in a manner, to avoid damage to the pipe and coating. The Owner shall approve such procedure prior to commencement of work.

12.4 Coated pipes may be handled by means of slings and belts of proper width (minimum 60 mm) made of non-abrasive/non-metallic materials. In this case, pipes to be stacked shall be separated row by row to avoid damages by rubbing the coated surface in the process of taking off the slings. Use of round sectional slings is prohibited. Forklifts may be used provided that the arms of the forklift are covered with suitable pads, preferably rubber.

12.5 Bare/coated pipes at all times shall be stacked completely clear from the ground, at least 500 mm, so that the bottom row of pipes remains free from any surface water. The pipes shall be stacked at a slope so that driving rain does not collect inside the pipe. Bare/coated pipes may be stacked by placing them on ridges of sand free from stones and covered with a plastic film or on wooden supports provided with suitable cover. This cover can be of dry, germ-free straw covered with plastic film, otherwise foam rubber may be used. The supports shall be spaced in such a manner as to avoid permanent bending of the pipes.

Stacks shall consist of limited number of layers such that the pressure exercised by the pipe's own weight does not cause damages to the coating. Applicator/ Contractor shall submit calculations for Owner approval in this regard. Each pipe section shall be separated by means of spacers suitably spaced for this purpose. Stacks shall be suitably secured against falling down and shall consist of pipe sections having the same diameter and wall thickness. The weld seam of pipes shall be positioned always in a manner so as not to touch the adjacent pipes.

The bevel protector shall be removed and stored for reuse after completion of coating application. The ends of the pipes during handling and stacking shall always be protected with bevel protectors

12.6 The lorries used for transportation shall be equipped with adequate pipe supports having as many round hollow beds as there are pipes to be placed on the bottom of the flat bed type lorry/ trailer. Total width of the supports shall be at least 5% of the pipe length and min. 4 nos. support shall be provided. These supports shall be lined with a rubber protection and shall be spaced in a manner as to support equal load from the pipes. The rubber protection must be free from all nails and staples where pipes are in contact. The second layer and all following layers shall be separated from the other with adequate number of separating layers of protective material such as straw in plastic covers or mineral wool strips or equivalent, to avoid direct touch between the coated pipes.

All stanchions of lorries used for transportation shall be covered by non-abrasive material like rubber belts or equivalent. Care shall be exercised to properly cover the top of the stanchions and other positions such as reinforcement of the truck body, rivets, etc. to prevent damage to the coated surface. Slings or non-metallic straps shall be used for securing loads during transportation. They shall be suitably padded at the contact points with the pipe

12.7 Materials other than pipes and which are susceptible of deteriorating or suffering from damages especially due to humidity, exposure to high thermal excursions or other adverse weather conditions, shall be suitably stored and protected. Deteriorated materials shall not be used and shall be replaced at Applicator/ Contractor's expenses. These materials shall always be handled during loading, unloading and storage in a manner so as to prevent any damage, alteration and dispersion. When supplied in containers and envelopes, they shall not be dropped or thrown, or removed by means of hooks, both during the handling

operations till their complete use. During unloading, transport and utilization, any contact with water, earth, crushed stone and any other foreign material shall be carefully avoided.

Applicator/ Contractor shall strictly follow Manufacturer's instructions regarding storage temperature and methods for volatile materials that are susceptible to change in properties and characteristics due to unsuitable storage. If necessary, the Applicator/ Contractor shall provide for a proper conditioning.

12.8 In case of any marine transportation of bare/coated line pipes involved, the same shall be carried out in compliance with API RP 5LW. Applicator/ Contractor shall furnish all details pertaining to marine transportation including drawings of cargo barges, storing/stacking, sea fastening of pipes on the barges/marine vessels to the Owner for approval prior to undertaking such transportation works. In addition, Applicator/ Contractor shall also carry out requisite analyses considering the proposed transportation scheme and establish the same is safe and stable. On-deck overseas shipment shall not be allowed.

13 REPAIR OF COATING:

Applicator shall submit to the Owner, its methods and materials proposed to be used for executing a coating repair and shall receive approval from Owner prior to regular production.

In open storage, the repair coating materials must be compatible with parent 3LPE coating and able to withstand a temperature of at least (+) 80°C without impairing its serviceability and properties.

Applicator shall furnish manufacturer's test certificates for the repair materials clearly establishing the compliance of the repair materials with the applicable coating requirements indicated in this specification.

All pipes leaving coating plant shall have sound external coating with no holiday or porosity on 100% of the surface.

13.1 Defects, repairs and acceptability criteria shall be as follows:

13.1.1 Pipes showing porosities or very small damage not picked up during holiday test and having a surface less than 0.5 cm² or linear damage (cut) of less than 3 cm shall be repaired by melt stick using material of same quality;

13.1.2 Damages caused to coating by handling such as scratches, cuts, dents, gouges, not picked up during holiday test, having a total reduced thickness on damaged

portion not less than 2 mm and an area not exceeding 10 cm², shall be rebuilt by Repair Patch material only and without exposing to bare metal;

13.1.3 Defects of size exceeding above mentioned area or holidays of length less than 300 mm shall be repaired with heat shrink repair patch by exposing the bare metal surface;

13.1.4 Defects exceeding the above and in number not exceeding 1 per pipe and linear length not exceeding 500 mm shall be repaired using Heat Shrinkable Sleeves (HSS), HTLP 80 or equivalent;

13.1.5 More than two (02) repairs are not allowed in single length of pipe and cumulative area for these repairs shall not exceed 100 cm² per pipe;

13.1.6 Pipes with bigger damage shall be stripped and recoated.

13.1.7 In case of coating defect close to coating cut back, applicator shall remove the coating throughout the entire circumference of the pipe down to the steel surface and increase the coating cut back length. Now if the coating cutback exceeds 150 mm linear length of pipe then the coating shall be repaired by the use of heat shrink sleeves thereby making up the coating cut back length of 150 mm;

13.1.8 Notwithstanding the above, if defects exceed 70 mm from the original coating cut back length, the entire coating shall be removed and the pipe shall be recycled through the entire coating procedure;

13.1.9 Circumferential sleeve (full encirclement) repair is permitted within 100 mm length of the coating cut back area;

13.2 Irrespective of type of repair, the maximum numbers of repair of coating shall be as follows:

13.2.1 Holiday repair of size ≤ 100 cm² attributable to process of coating application shall be maximum one number per pipe;

13.2.2 In addition to the above, defects to be repaired by heat shrink patch/sleeve shall be maximum 1 (One) per pipe;

13.2.3 Defects exceeding the above limits shall cause pipe coating rejection, stripping and recoating.

The above is exclusive of the repairs warranted due to testing as per this specification.

All repairs carried out to coating for whatever reason shall be to the account of Applicator/ Contractor.

Cosmetic damages occurring in the polyethylene layer only need not be repaired by exposing up to steel surface, as deemed fit by the Owner or its Representative. In any case the Applicator / Contractor shall establish his material, methods and procedure of repair that result in an acceptable quality of product by testing and shall receive approval from Owner prior to use.

All repairs shall result in a coating thickness no less than the parent coating thickness. Applicator / Contractor shall test repairs to coating as and when required by Owner.

Repair procedures/ process shall be qualified during PQT.

Only qualified Repair personnel or Insulator shall be allowed to conduct the repair work and all repaired pipes shall be identified by indicating alphabet 'R' after the coating number.

14 MARKING:

14.1 Applicator/ Contractor shall place marking on the outside surface of the coating at one end of the coated pipe, and marking shall indicate, but not limited to the following information:

- 14.1.1 Applicator's Name and Logo;
- 14.1.2 Pipe number, Heat number;
- 14.1.3 Pipe diameter, wall thickness, material grade & length;
- 14.1.4 Coated pipe number;
- 14.1.5 Colour band (if required);
- 14.1.6 Any other information considered relevant by Owner;
- 14.1.7 Inspection Mark/Punch;
- 14.1.8 Coating Class and Max, design Temp. (If required).

Applicator/ Contractor shall obtain prior approval on marking procedure to be adopted from the Owner.

15 INSPECTION, MEASURING AND TEST EQUIPMENT:

All inspection, measuring and test equipment shall be good working condition and have valid calibration certificates traceable to ISO 17025 accredited calibration laboratory or equivalent. In addition to the above, the following measuring devices

shall be verified at a regular interval during execution of coating activities.

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

Volume II
of II

Device Name	Reference Clause No.	Frequency of in-house Verification	Tolerance
Digital Roughness Gauge	7.1.10	Start of shift	Standard value \pm 5 %
Digital Contact Thermometer	7.4.1.5	Twice / shift	Standard value \pm 2 %
Optical Pyrometer	7.4.1.5	Twice / shift	Standard value \pm 2 %
Digital Thickness Gauge	8.6.1.1, 8.6.1.2, 8.6.2.2	Start of shift	Standard value \pm 5 %
Holiday Detector	8.6.2.3.	Every 4 hours	Standard value \pm 2 %

16 RELEASE OF FINISHED COATED PIPES:

Upon successful completion of various in-process inspection and testing, Applicator QC department shall prepare all the records (including release documents) of qualification and production stages. Owner and / or its representative shall review all records and documents for endorsement and then finally release the finished product for dispatch or shipment.

ANNEXURE-1

LIST OF ACCEPTABLE COMBINATIONS OF COATING MATERIALS

The following combinations of coating materials are considered acceptable. In case any of the combinations listed below are offered, details regarding properties of the offered materials need not be furnished with bid. However, In the event of award of contract, Applicator/ Contractor shall furnish the combination(s) proposed and re-confirmation of compatibility of the proposed combination (s) from the raw materials Manufacturers.

Epoxy Powder (Manufacturer)	Adhesive (Manufacturer)	PE Compound (Manufacturer)
<p>JOTAPIPE AC 2002 (Formerly, CORRO-COAT EP-F 2002HW) (JOTUN) or SCOTCHKOTE 226N (3M) or PIPECLAD 2000/PIPECLAD 1000 (SHERWIN-WILLIAMS)</p>	<p>LUCALEN G3710E (LYONDELLBASELL)</p>	<p>LUPOLEN 4552 D (LYONDELLBASELL)</p>
<p>JOTAPIPE AC 2001 (Formerly, CORRO-COAT EP-F 2001) / JOTAPIPE AC 2002 (Formerly, CORRO-COAT EP-F 2002HW) / JOTAPIPE AC 1003 (Formerly, CORRO-COAT EP-F -1003HW) (JOTUN) or SCOTCHKOTE 226N (3M) or PIPECLAD 2000/PIPECLAD 1000 (SHERWIN-WILLIAMS)</p>	<p>ME 0420 (BOREALIS)</p>	<p>HE 3450H (BOREALIS/ BOROUGE)</p>
<p>JOTAPIPE AC 2001 (Formerly, CORRO-COAT EP-F 2001) (JOTUN) or PIPECLAD 2000/PIPECLAD 1000 (SHERWIN-WILLIAMS) or SCOTCHKOTE 226N(3M)</p>	<p>LE149V (HYUNDAI ENGINEERING PLASTICS)</p>	<p>ET509B (HYUNDAI ENGINEERING PLASTICS)</p>



Bhagyanagar
Gas Limited

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

Volume II
of II

Although the above combinations would be acceptable to the owner, the responsibility of suitability for application, performance and compliance to the coating system requirements shall unconditionally lie with the applicator/ contractor.



Bhagyanagar
Gas Limited

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

Volume II
of II

STANDARD SPECIFICATION FOR REPAIR OF POLYTHYLENE COATING



Bhagyanagar
Gas Limited

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

Volume II
of II

ABBREVIATIONS:

DC : Direct Current
EN : European Standard
KV : Kilo Volt



PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Volume II
of II

Bid Document No. BGL/719/2025-26

CONTENTS

1.0 SCOPE	5
2.0 MATERIAL AND EQUIPMENT.....	5
3.0 APPLICATION PROCEDURE.....	5
4.0 INSPECTION AND TEST.....	6
5.0 DOCUMENTATION	6

1.0 SCOPE

This specification covers the minimum requirements for materials and equipment, application procedure and inspection of repair of damaged Polyethylene coatings on steel pipes. This specification is applicable for repairing damages less than 100mm x 100 mm for pipe sizes less than 10", 150mm x 150mm for pipe sizes between 12" to 28" and 300mm x 300mm for pipe sizes more than 28".

If damaged area of coating of the pipeline is larger than above, heat shrinkable sleeve is recommended.

The repair shall be carried out using repair patch made of radiation cross-linked polyolefin backing, coated on the inside with semi-crystalline thermoplastic adhesive and filler mastic.

The repair patch shall have thermal indicators to ensure correct heat is being applied during application.

2.0 MATERIAL AND EQUIPMENT

2.1 The repair material shall be as under:

- a) Repair Patch: radiation cross-linked HDPE (Unexpanded High density polyethylene) with semi-crystalline thermoplastic adhesive.
- b) Mastic Filler
- c) Melt stick shall be Co-Polymer based and same shall be heat sensitive.
- d) Liquid Epoxy Primer (two pack)

2.2 The repair material shall be certified by DIN to meet the requirements of EN12068 Stress Class CHT 80

2.3 The material shall not be older than their period of validity at the time of application by the Contractor. Deteriorated/decomposed materials shall not be used.

2.4 Materials shall be stored in sheltered storages in the manufacturer's original packing away from direct sunlight and in accordance with manufacturer's instructions.

2.5 Contractor shall supply all equipment and manpower required for a skilful application in the field in accordance with the specification.

3.0 APPLICATION PROCEDURE

3.1 The application procedure to be followed for holiday type of damage shall be in accordance with manufacturer's instruction and minimum requirement specified below whichever are the more stringent.

3.1.1 Preparation

Remove coating from damaged area with knife, scraper or power brush. Scrap off the damaged area and adjacent coating to remove oil, grease, rust, dirt and moisture. Pipe surface shall be prepared to SA 2½.

3.1.2 Preheating

Preheat the exposed bare metal surface to approx. 80° C and adjacent pipe coating to approx. 60° C with a torch moved back and forth over the surface. Upon preheating, the pipe surface shall be applied with the two pack epoxy primer to ensure a minimum wet film thickness of not less than 200 microns to cover the exposed base metal.

3.1.3 Application of the Filler

Plastic filler shall be cut to size and applied to all exposed metal surface. The mastic shall be heated and smoothed down with a paint scraper to cover all bare metal in a manner such that all entrapped air is removed and mill applied coating thickness of the pipe is restored.

3.1.4 Application of repair tape

A patch shall be cut from the tape in a manner such that it extends 50 mm (2 inch) beyond the damaged area on all sides. The patch shall be positioned over the damaged area and heated until the temperature sensitive paint on the outside of the patch changes colour or dimples on the backing vanish. It shall be smoothed down to conform with the contour of lap, and shall be freed of any air bubbles or wrinkles.

3.2 For cosmetic type of defects such as minor gouging, tearing, and/or scratches, which do not indicate holiday during holiday inspection, following procedure shall be adopted.

3.2.1 The defective area shall be roughened to remove loose polyethylene coating, oil, grease, dirt, etc.

3.2.2 This shall be followed by application of patch as detailed in clause 3.1.4.

4.0 INSPECTION AND TEST

4.1 A visual inspection shall be carried out for the following:

- Mastic extrusion on ends of the patch shall be examined.
- There shall be no sign of punctures or pinholes or bend failure. The external appearance of the patch shall be smooth, free from dimples, air entrapment or void formation.
- The entire closure patch shall have changed colour uniformly.

4.2 Holiday Inspection

The holiday detector used shall be checked and calibrated daily with an accurate D.C. Voltmeter. The detector electrode shall be in direct contact with the surface of coating to be inspected.

The entire surface of the repaired section shall be inspected by means of a full circle holiday detector approved by Owner set to a D.C. Voltage of at least 25 KV. Inspection of repaired patch shall be conducted only after it has cooled below 50° C.

4.3 Procedure qualification shall be carried out for repair patch. The value for peel strength to pipe surface and to factory coating carried out as per EN 12068 shall be 0.5 N/mm minimum at 60°C.

4.4 All repaired joint shall be approved by the Owner.

5.0 DOCUMENTATION

Prior to procurement of coating repair materials, Contractor shall furnish four copies of, but not limited to, the following for qualification of the Manufacturer and material:

- i) Complete descriptive technical catalogs describing the materials offered along with samples of repair coating materials, its properties and installation instruction as applicable specifically to the project.
- ii) Test certificate and results of previously conducted tests from independent inspection agency, for properties listed in Para 4.3 of this specification.
- iii) Reference list of previous supplies of the similar material indicating the project details such as diameter, quantity, service conditions, year of supply, project name, contact person and feedback on performance.

Once the Company's approval has been given, any change in material or Manufacturer shall be notified to Company, whose approval in writing of all changes shall be obtained before the materials are manufactured.

5.1 Prior to shipment of materials from the Manufacturer's works, Contractor shall furnish six hard copies and an electronic copy of the following:

- i) Test certificates for each batch of materials.
- ii) Specific installation instruction with pictorial illustrations.
- iii) Specific storage and handling instructions.

5.2 All documents shall be in English Language only.



Bhagyanagar
Gas Limited

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

Volume II
of II

INSPECTION AND TEST PLAN FOR ERW LINE PIPES

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

ABBREVIATIONS:			
CE	Carbon Equivalent	PO	Purchase Order
HT	Heat Treatment	PQR	Procedure Qualification Record
IC	Inspection Certificate	RT	Radiography Testing
ITP	Inspection and Test Plan	TC	Test Certificate
MPS	Manufacturing Process Specification	TPI or TPIA	Third Party Inspection Agency
MPT/MT	Magnetic Particle Testing	UT	Ultrasonic Testing
MR	Material Requisition	VDR	Vendor Data Requirement
MTC	Material Test Certificate	WPQ	Welders Performance Qualification
NDT	Non-Destructive Testing	WPS	Welding Procedure Specification
PMI	Positive Material Identification		
LEGENDS:			
H - Hold (Do not proceed without approval)			
W - Witness (Give due notice, work may proceed after scheduled date)			
P - Perform			
R - Review			
RW - Random Witness (As specified or 10% [min.1 no. of each size and type of Bulk item])			

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

1.0 SCOPE:

This Inspection and Test Plan covers the minimum testing requirements of Electric Welded Pipes.

2.0 REFERENCE DOCUMENTS:

PO/PR/ Standards referred there in/ Job specifications /Approved documents.

3.0 INSPECTION AND TEST REQUIREMENTS:

S L. N O.	STAGE/ ACTIVITY	CHARACTERIS TICS	QUANTUM OF CHECK	RECORD	SCOPE OF INSPECTION		
					SUB VENDOR	VENDOR	TPIA
1.0	Procedure						
1.1	MPS	Documented Procedures	100%	Procedure Documents	-	H	R
1.2	WPS, PQR & WPQ	Welding parameters & Qualification Record	100%	WPS, PQR & WPQ	-	H	W- New R- Existing (Qualified under Reputed TPIA)
2.0	Raw Material Procurement						



Bhagyanagar Gas Ltd.
Bhagyanagar Gas Limited

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Volume II
of II

Bid Document No. BGL/719/2025-26

S L N O.	STAGE/ ACTIVI TY	CHARACTERIS TICS	QUANT UM OF CHE CK	RECOR D	SCOPE OF INSPECTION		
					SUB VEND OR	VEND OR	TPIA
2.1	Inspecti on of Coils at Mills (Sub vendor works)	Chemical & Mechanical Properties, Method of manufacturing, Heat Treatment Condition etc.	100%	Mill Test Certific ates (EN 10204- 3.2)	H	H (Note- 3)	R (Note-3)
3.0	In Process Inspectio n						
3.1	First Day Productio n test	All testing requirement as per PR/ MPS	As per PR/ MPS	Test Report	-	H	H
3.2	Raw material Inspection	Heat No, Coil /Plate, Visual & Dimension	100%	Inspecti on Reports	-	H	R W (Min. 1%)
		1) Mechanical 2) Chemical 3) Impact	One/Heat	Inspecti on Report	-	W	W
3.3	Coil /Skelp UT as applicable	1) 25mm (Min) from edges 2) 20 % Min Coverage in Bal. part of Coil/ Plate	100%	Inspecti on Reports	-	H	R W (Min. 1%)

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Volume II
of II

Bid Document No. BGL/719/2025-26

S L N O.	STAGE/ ACTIVI TY	CHARACTERI STICS	QUANTUM OF CHECK	RECO RD	SCOPE OF INSPECTION		
					SUB VEND OR	VEND OR	TPIA
3.4	Pipe Forming & Welding	Offset & Welding Parameters	100%	Inspection Reports	-	H	-
3.5	Heat Treatment	Weld Seam Normalising, Stress Relieving, Normalising, Tempering, Solution Annealing, Stabilization Heat Treatment, Heat Treatment temperature etc. as applicable	100%	HT Graph / Record	-	H	R
4.0	Final Inspection						
4.1	Hydrostatic Testing	Leak & pressure Drop, Calibration of Gauges/ Recorder	100%	Inspection Report	-	H	R W (Min .5%)
4.2	Calibration of UT system	Run with calibration pipe	1) Beginning of each shift 2) After Breakdown /Maintenance	Inspection Report	-	W	W



Bhagyanagar Gas Ltd.
Bhagyanagar Gas Limited

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

Volume II
of II

S L N O.	STAGE/ ACTIVI TY	CHARACTERIS TICS	QUANT UM OF CHE CK	RECOR D	SCOPE OF INSPECTION		
					SUB VEND OR	VEND OR	TPIA
4.3	Final weld UT & Pipe body UT (If applicable)	Calibration, Seam Tracking. & Examination of Defects	100%	Inspect ion Report	-	H	R W (Min.5 %)
4.4	Manual UT of Pipe end	Welding defects, crack/ lamination of base metal	100%	Inspect ion Report	-	W	R W (Min. 1%)
4.5	Inspecti on of Pipe ends MPT	1. Examination of Surface Defects after Bevelling 2. Demagnetization	100%	Inspect ion Report	-	H	R W (Min. 1%)
4.6	Final visual and dimension	1. Visual Examination 2. Dimensio nal Check Surface Condition, Straightness, End Finish, Bevel Angle, Root Face, Outer Dia., Thickness, Length, End Finish, Marking etc.	100%	Inspect ion Report	-	H	R W (Min.5 %)
4.7	Lot Testing	1. Chemical Analysis 2. Tensile Tests 3. Flattening 4. Reverse Bend Test	As per MPS/ API 5L/Sp ec.	Inspect ion Report	-	H	W



Bhagyanagar Gas Ltd.
Bhagyanagar Gas Limited

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

Volume II
of II

S L. N O.	STAGE/ ACTIVITY	CHARACTERI STICS	QUANT UM OF CH EC K	RECO RD	SCOPE OF INSPECTION		
					SUB VEND OR	VEND OR	TPIA
		5. Macro & Hardness Tests 6. Impact Tests 7. Drop Weight Tear Test, etc. as applicable					
4.8	Non-conforming product/stage	Repair / Retest /Reject	100%	Inspection Report	-	H	RW
4.9	Marking/Stenciling	Pipe No, Acceptance No., Heat. No., Size, Weight, Grade, Thickness, Colour Code etc	100%	Inspection Report	-	H	R W (Min .5%)
5.0	PAINTING						
5.1	Rust Preventive Coating & Colour Coding	Visual & Colour Coding as applicable	100%	Inspection Report	-	H	-
6.0	Documentation & IC						

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Volume II
of II

Bid Document No. BGL/719/2025-26

S L. N O.	STAGE/ ACTIVITY	CHARACTERIS TICS	QUANTU M OF CHE CK	RECO RD	SCOPE OF INSPECTION		
					SUB VENDO R	VEND OR	TP IA
6.1	Documentat ion & Inspection Certificate (IC)	Review of Stage Inspection Reports / Test Reports & Issue of IC	100%	Manufacture r TC & IC (Note-4)	-	H	H
6.2	Final documents as per PR/MR	Verification & compilation of inspection & test records for submission to customer	100%	Final dossier	-	H	H

NOTES (As applicable):

1. ITP shall be submitted including but not limited to the item/activity covered above. Any item/activity identified and required for the completeness shall also be covered in the ITP submitted by the manufacturers.
2. Acceptance Norms for all the activities shall be as per PO/PR/STANDARDS referred there in /Job Specification /Approved Documents.
3. Raw Material (Coils) shall be inspected at Mills (Sub vendors works) by TPIA appointed by Vendor.
4. Items shall be EN 10204 Type 3.2 certified based on this ITP/MR/PR for the Pipe (Final Product).



Bhagyanagar
Gas Limited

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

Volume II
of II

INSPECTION AND TEST PLAN FOR RAW MATERIAL (HR COIL/ PLATES)

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

ABBREVIATIONS:			
CE	Carbon Equivalent	PO	Purchase Order
HT	Heat Treatment	PQR	Procedure Qualification Record
IC	Inspection Certificate	RT	Radiography Testing
ITP	Inspection and Test Plan	TC	Test Certificate
MPS	Manufacturing Process Specification	TPI or TPIA	Third Party Inspection Agency
MPT/MT	Magnetic Particle Testing	UT	Ultrasonic Testing
MR	Material Requisition	VDR	Vendor Data Requirement
MTC	Material Test Certificate	WPQ	Welders Performance Qualification
NDT	Non Destructive Testing	WPS	Welding Procedure Specification
PMI	Positive Material Identification		
LEGENDS:			
H - Hold (Do not proceed without approval)			
W - Witness (Give due notice, work may proceed after scheduled date)			
P - Perform			
R - Review			
C - Certify			
RW - Random Witness (As specified or 10% [min.1 no. of each size and type of Bulk item])			

1.0 SCOPE:

This Inspection and Test Plan covers the minimum inspection & testing requirements for Rolling process for manufacturing of Hot Rolled Coil & Plates as part of raw material quality requirements for line pipes

2.0 REFERENCE DOCUMENTS:

PO/PR/ Standards referred there in/ Job specifications /Approved documents.

3.0 INSPECTION AND TEST REQUIREMENTS:



PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Volume II
of II

Bid Document No. BGL/719/2025-26

N O	Sl. No.	Comp onents & Operat ions	Character istics / Type of check	Quan tu m of ch ec k	Reference document and Acceptance norm	Respons ibility	For m at of re co rd s	Ste el Ma nuf.	Scope of Inspection	
									Pi pe Ma nuf & TPI	CONSUL TANT / CLIENT
1	2	3	4	5	6	7	8	9	10	11
2	Rolling department	Slab reheating	Heating parameters per zone	1 slab/Heat	As per Steel Manuf. control level and acceptance as per Tender Requirement	Quality In-charge	Report as per Steel Mill format	P	RW (20%)	M
3	Hot rolling department	Rolling and accelerated cooling of coils	Rolling Parameters and temperature tolerances.	1 coil/Plate per Heat	As per Steel Manuf. control level and acceptance as per Tender Requirement	Quality In-charge	Report as per Steel Mill format	P	RW (20%)	M



Bhagyanagar Gas Limited

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Volume II of II

Bid Document No. BGL/719/2025-26

4	Ultrasonic of plates	Automatic Ultrasonic machine	Internal imperfections & lamination	1 Plate/Heat	As per Steel Manuf. control level and acceptance as per Tender Requirement	Quality In-charge	Report as per Steel Mill format	P	W	RW
5	Sampling department	Sample removal	Check sample position (end or within body)	1 coil/Plate per Heat	As per Steel Manuf. control level and acceptance as per Tender Requirement	Quality In-charge	Report as per Steel Mill format	P	W	RW
6	Sampling department	Inspection of coil end surface quality and dimensions	Surface of coil	1 coil/Plate per Heat	As per Steel Manuf. control level and acceptance as per Tender Requirement	Quality In-charge	Report as per Steel Mill format	P	RW	M
7	Sampling department	Mechanical, chemical and hardness tests	Chemical analysis, Tensile Test, Bend Test, Impact Test, Hardness Test,	1 coil/Plate per Heat	As per Steel Manuf. control level and acceptance as per Tender Requirement	Quality In-charge	Report as per Steel Mill format & inspections reports	P	W	RW (Minimum 20% of Total Heats)

8	Packing and shipping department	Marking	No hard stamping	Each coil/Plate	As per Steel Manuf. control level and acceptance as per Tender Requirement	Quality In-charge	Report as per Steel Mill format	P	RW	M
9	Packing and shipping department	Production of test certificates	Manuf. Inspection Certificate as per EN 10204-3.2	Each heat of Coil & plate	As per Steel Manuf. control level and acceptance as per Tender Requirement	Quality In-charge	Report as per Steel Mill format	P	C	R



PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Volume II
of II

Bid Document No. BGL/719/2025-26

10	Packing and shipping department	Shipping	Correct loading	Each coil/Plate	As per Steel Manuf. control level and acceptance as per Tender Requirement	Quality In-charge	Report as per Steel Mill format	P	RW	H
----	--	----------	-----------------	-----------------	--	-------------------	---------------------------------	---	----	---

NOTES (As applicable):

1. ITP shall be submitted including but not limited to the item/activity covered above. Any item/activity identified and required for the completeness shall also be covered in the ITP submitted by the manufacturers.
2. Acceptance Norms for all the activities shall be as per PO/PR/STANDARDS referred there in /Job Specification /Approved Documents.
3. Successful pipe Manufacturer has to submit latest audit report of offered Coil /Plate mill along with Inspection Test plan
4. Raw Material (Coils) shall be inspected at Mills (Sub vendors works) by TPIA appointed by Vendor.
5. Items shall be EN 10204 Type 3.2 certified.
6. In case of conflict between purchase specification, contract documents and ITP, more stringent conditions shall be applicable.
7. Wherever W/R is indicated, Inspection Engineer shall decide the option to be exercised for the particular stage and supplier.
8. Wherever RW is indicated, Inspection engineer shall witness at least 10% quantity (Minimum 1No.) randomly in a specific time interval.
9. The Line Pipe Manufacturer shall be completely responsible for the design, materials, testing, inspection, preparation for shipment, loading of the supplied item strictly in accordance with the Material Requisition and all attachments thereto.
10. Line pipe manufacturer has to give at least 3 weeks advance notice for inspection to CONSULTANT/CLIENT.
11. Scope of inspection for Quantity less than 10,000MT shall be finalized after award of contract.



**PROCUREMENT OF STEEL PIPELINES IN
HYDERABAD GA**

Bid Document No. BGL/719/2025-26

Volume II
of II

**INSPECTION AND TEST PLAN FOR
3 LAYER PE COATING OF LINEPIPES**

ABBREVIATIONS

CE	Carbon Equivalent	NDT	Non Destructive Testing
DFT	Dry Film Thickness	NPSH	Net Positive Suction Head
DPT	Dye Penetrant Testing	PO	Purchase Order
DHT	De-hydrogen Heat Treatment	PESO	Petroleum Explosive Safety Organization
ERTL	Electronics Regional Test Laboratory	PQR	Procedure Qualification Record
FCRI	Fluid Control Research Institute	MR	Material Requisition
HT	Heat Treatment	PMI	Positive Material Identification
HIC	Hydrogen Induced Cracking	RT	Radiography Testing
ITP	Inspection and Test Plan	SSCC	Sulphide Stress Corrosion Cracking
IP	Ingress Protection	TC	Test Certificate
IHT	Intermediate Heat Treatment	TPI or TPIA	Third Party Inspection Agency
IC	Inspection Certificate	UT	Ultrasonic Testing
IGC	Inter Granular Corrosion	VDR	Vendor Data Requirement
MPT/MT	Magnetic Particle Testing	WPS	Welding Procedure Specification
MTC	Material Test Certificate	WPQ	Welders Performance Qualification
MRT	Mechanical Run Test		

1.0 SCOPE:

This Inspection and Test Plan covers the minimum testing requirements of 3-Layer PE Coating of Line pipes

2.0 REFERENCE DOCUMENTS:

PO/PR/ Standards referred there in/ Job specifications /Approved documents.



PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Volume II
of II

Bid Document No. BGL/719/2025-26

3.0 INSPECTION AND TEST REQUIREMENTS:

SL. NO.	STAGE/ACTIVITY	CHARACTERISTICS	QUANTUM OF CHECK	RECORD	SCOPE OF INSPECTION		
					SUB SUPPLIER	SUPPLIER	TPIA
1.0	Procedure						
1.1	Coating application, testing and Other Procedures	Documented Procedures	100%	Procedure Documents	-	H	R
2.0	Material Inspection						
2.1	Epoxy powder, Adhesive & Polyethylene compound	All the properties as per Material specification	100%	Manufacturer Test Certificates	H	R	R
3.0	In Process Inspection						

3.1	Epoxy powder, Adhesive & Polyethylene compound check testing	Properties as per Material specification	100%	Test Reports	-	H	H
3.2	Coating Procedure qualification	All the testing as per Material specification	As per Material Specification	Inspection/Test Report	-	H	H
3.3	Incoming Pipes	Visual inspection, marking verification & correlation with mill TC/Tally sheet	100%	Supplier Data Sheet	-	H	-
3.4	Blast Cleaning	Pre Heating, Elapsed time, Degree of cleaning,, Surface Profile, Contamination of shots/grits, salt level, Degree of dust & roughness	100%	Inspection Reports	-	H	RW (Min.1%)

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

3.5	Lab test for Chromate, Phosphoric acid & de-ionized water (as applicable)	Properties as per purchase specification / Manufacturer TC	As per Material Specification	Inspection Reports	-	H	RW (Once in a Day)
3.6	Phosphoric acid wash followed by de-ionized water wash (as applicable)	Visual, PH Value, salt level etc.	100%	Inspection Reports	-	H	RW (Once in a Day)
3.7	Chromate Treatment (as applicable)	Uniform application as per Manufacturer's recommendation	100%	Inspection Reports	-	H	RW (Once in a Day)
3.8	Coating application	Preheating temperature, Inter coat time, line speed, Adhesive / PE film temperature, Overlap of layers etc.	100%	Inspection Reports	-	H	RW (Min.1%)
3.9	Epoxy and adhesive Thickness on semi coated pipe	Visual, Thickness, overlap, Adhesion test (St Andrew's Cross Cut method) etc.	As per Material Specification	Inspection Reports	-	H	W
4.0	Final Inspection						
4.1	Holiday detection at 25KV	Pin hole, coating damage & Other through thickness defects.	100%	Inspection Report	-	H	RW (Min.1%)
4.2	Visual and Dimensional	Visual, coating thickness, Cut back dimension, Marking , colour coding etc.	100%	Inspection Report	-	H	RW (Min.1%)
4.3	Impact test	No coating damage @ specified Energy	As per Material Specification	Inspection Report	-	H	W

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Volume II
of II

Bid Document No. BGL/719/2025-26

4.4	Peel Test	Bond strength, mode of failure, rate of peeling etc.	As per Material Specification	Inspection Report	-	H	RW (Min.1%)
4.5	Resistance to indentation test	Hardness against indentation	As per Material Specification.	Inspection Report	-	H	W
4.6	Cathodic Disbondment Test	Disbonded area / Equivalent circle radius (ECR)	As per Material Specification	Inspection Report	-	H	W
4.7	Dry Adhesion Test	Epoxy Coating resists Disbondment from the steel (rating 1 or 2)	As per Material Specification	Inspection Report	-	H	W
4.8	Hot water immersion test	Average less than or equal to 2 and maximum less than or equal to 3 as per ISO 21809-1	As per Material Specification	Inspection Report	-	H	W
4.9	Elongation at Break	Minimum 400%	As per Material Specification	Inspection Report	-	H	W
4.10	Visual (Air Entrapment)	Air entrapment between the layers	As per Material Specification	Inspection Report	-	H	W

4.11	Degree of Cure Test	Cure %, Glass Transition Temp(ΔH and ΔT_g)	As per Material Specification	Inspection Report	-	H	W
4.12	Calibration of measuring Instruments / Holiday tester	Verify Accuracy	As per Material Specification	Calibration Report	-	H	R
4.13	Handling, Load out & Transportation (Bare & coated pipes)	Pipes stacking & weather protection	As per Material Specification	Inspection Report	-	H	-

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Volume II
of II

Bid Document No. BGL/719/2025-26

5.0	Documentation & IC						
5.1	Documentation & Inspection Certificate(IC)	Review of Stage Inspection Reports / Test Reports & Issue of IC	100%	Manufacturer TC & IC	-	H	H
5.1	Final Document submission	Compilation of Inspection / Test reports as per VDR / PR	100%	Final data folder /Completeness certificate	-	H	H

Legend: H - Hold (Do not proceed without approval), P - Perform, RW - Random Witness (As specified or 10% [min.1 no. of each size and type of Bulk item]), R - Review, W - Witness (Give due notice, work may proceed after scheduled date).

NOTES (As applicable):

1. This document describes the generic test requirements. Any additional test or Inspection scope if specified in contract documents shall also be applicable.
(Unless otherwise agreed upon)
2. Acceptance Norms for all the activities shall be as per
PO/MR/STANDARDS referred there in /Job Specification /Approved Documents.

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

Volume II
of II

FORM - A

CHECK LIST - TECHNICAL

REQUISITION FOR :	CARBON STEEL COATED/ BARE PIPES
PROJECT :	

Bidder confirms following, as a minimum, have been enclosed in the offer:

SI. No.	Requirements	Complied by Bidder
1.0	Total compliance to technical requirements of the Material Requisition, as per Compliance Statement (Form-C), enclosed.	Yes/No
2.0	Bidder has clearly identified the quoted items covered in Material Requisition including location of pipe mill(s) where the quoted items are proposed to be manufactured.	Yes/No
3.0	Type of Line pipe (ERW) quoted has been clearly indicated for each quoted item, as applicable.	Yes/No
4.0	Bidder meets Bidder's Evaluation criteria (BEC) and documentary evidence in support of BEC is enclosed in the offer as per following, as a minimum:	Yes/No
	a) Name & Location of Proposed Pipe Mill	Yes/No
	b) Valid API 5L certificate and copy of license to use API monogram on line pipes of PSL 2 quality as per API spec 5L	Yes/No
	c) Proposed Pipe Mills' past track record for supply of line pipes of same or higher in terms of diameter, wall thickness and grade in the last seven years as per Form-B	Yes/No
	d) Documentary evidence in support of BEC [i.e. copies of W.O/ P.O (without price) & Inspection release notes/ completion certificate etc.]	Yes/No
5.0	a) Regarding raw material supplier(s) i.e. steel plate/ coil material, Bidder confirms compliance to relevant notes of General Notes to "Material Requisition for Line Pipe" and Documentary evidence required as per above note are enclosed with the offer along with duly filled-up Form-D.	Yes/No
	b) Compliance to Applicable VCS specification attached with MR / from proposed steel plate/ coil manufacturer(s) is enclosed with the offer.	Yes/No

To be filled, signed and stamped by Bidder.

Bidder's seal
of Bidder

Signature



Bhagyanagar Gas Ltd.
Bhagyanagar Gas Limited

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

Volume II
of II

FORM – B

REFERENCE LIST OF SUPPLY OF LINE PIPES FOR THE LAST SEVEN YEARS

Pipe Manufacturer: _____ **Mill Name & Location:** _____

Sl. No.	Project	Client (Company name, Address, email ID, contact phone no.)	Diameter NB (inch)	Grade API 5L X-	Wall thickness (mm)	Length (metres)	Process of Manufacture (ERW)	Product Specification Level (PSL-2)	Service	Year of supply	Purchase/ Work Order No. (Note-2)	Inspection Release Note/ Completion Certificate No. (Note-2)

To be filled, signed and stamped by

Bidder. Note:

1. This form shall be filled separately by linepipe manufacturer for each proposed mill.
2. Copy of Purchase/ work order(s) and Inspection Release Note(s)/ Completion Certificate(s) shall be enclosed.

Bidder's seal

Signature of Bidder

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

FORM - C

COMPLIANCE STATEMENT

REQUISITION FOR :	CARBON STEEL COATED LINEPIPES
PROJECT :	

Sl. No.	Requirement	Bidder's Confirmation
1	Bidder confirms that the offer is in total compliance with technical requirements of the complete Material Requisition including General notes to MR, Data sheet SOW etc. as well as specification and there are no technical deviations. Bidder to note that as this is a “Zero-Deviation Bid” , deviation expressed or implied anywhere in the offer shall not be considered valid.	<div style="border: 1px solid black; height: 100px; width: 100%;"></div>
2	Bidder confirms meeting the Bidder's Evaluation Criteria (BEC) with necessary documentary evidence as per BEC.	<div style="border: 1px solid black; height: 30px; width: 100%;"></div>
3	(a) Bidder confirms meeting the qualification requirements of steel plates/ coil manufacturer as stipulated in relevant notes of Material Requisition for the proposed steel supplier(s).	<div style="border: 1px solid black; height: 30px; width: 100%;"></div>
	(b) Bidder confirms compliance to applicable VCS specification nos. by steel plate/ coil manufacturer.	<div style="border: 1px solid black; height: 30px; width: 100%;"></div>
4	Bidder confirms that for the items quoted by the bidder, the entire process of line pipe manufacturing shall be carried out in the proposed pipe mill(s).	<div style="border: 1px solid black; height: 30px; width: 100%;"></div>
5.	Bidder confirms that all materials proposed by the bidder are same/ superior to those specified in specification/ data sheets enclosed.	<div style="border: 1px solid black; height: 30px; width: 100%;"></div>

Bidder's Signature with stamp



PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

Volume II
of II

FORM - D

REFERENCE LIST OF SUPPLY OF STEEL COIL/ PLATE FOR THE LAST SEVEN YEARS

Steel Manufacturer: _____ **Mill Name & Location:** _____

Sl. No.	Project	Owner (Company name, Address, email ID, contact phone no., contact phone no.)	Pipe Manufacturer (Name, address, contact phone no., email ID etc.)	Coil Width (mm)	Plate Width (mm)	Billet	Grade API 5L X-	Product Specification Level (PSL-2)	Wall thickness (mm)	Quantity (MT) > 5000 MT	Pipe Diameter for which supplied NB (inch)	Year of supply	Purchase/ Work Order No. (Note-3)	Inspection Release Note/ Completion Certificate No. (Note-3)

To be filled, signed and stamped by

Bidder. Note:

1. This form shall be submitted along with the bid.
2. This form shall be filled separately by line pipe manufacturer for each steel coil/ plate manufacturer proposed by the bidder.
3. Copy of Purchase/ work order(s) and Inspection Release Note(s)/ Completion Certificate(s) shall be enclosed.

Bidder's seal

Signature of Bidder

INSTRUCTION TO BIDDERS

1. Bidder to note that no correspondence shall be entered into or entertained after the bid submission.
2. Bidder shall furnish quotation only in case he can supply material strictly as per this Material Requisition and specification/data sheet forming part of Material Requisition.
3. If the offer contains any technical deviations or clarifications or stipulates any technical specifications (even if in line with MR requirements) and does not include complete scope & technical / performance data required to be submitted with the offer, the offer shall be liable for rejection.
4. Bidder must submit all documents as listed in checklist with his offer.
5. Supplier must note that stage wise inspection for complete fabrication, testing including the raw material inspected to be carried out.
6. Vendors for bought out items to be restricted to the approved vendor list attached with bid document. Approval of additional vendor if required, for all critical bought out items shall be obtained by the supplier from the purchaser before placement of order. Credentials/PTR of the additional vendor proposed to be submitted by supplier for review and approval of Purchaser/ Purchaser's representative



Bhagyanagar Gas Limited

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

Volume II
of II

VENDOR DRAWINGS DOCUMENT SCHEDULE

VENDOR DRAWINGS

DOCUMENT SCHEDULE

		Vendor Drawing/ Document Submission Schedule				Status:		
						Date:		
Client	Project			Vendor Name				
Item Description	PO No.			Address				
	Date				Contact Person:	Fax:		
VCS Department		Contact Person(VCS)		Phone:	Email:			
S. No.	Equipment/ Item Number	Drg./Doc. Nomenclature	Vendor Drg./ Doc. Number	Vendor Drg./Doc. Title	Category Review (R) / Records	Scheduled date of 1 st submission (Rev.0)	Form Electronic/ Print	Remarks
0	25.05.2017	ISSUED AS STANDARDS		AS	GS	AD		
REV	DATE	DESCRIPTION		PREP	CHK	APPR		



**PROCUREMENT OF STEEL PIPELINES IN
HYDERABAD GA**

Volume II
of II

Bid Document No. BGL/719/2025-26

**STANDARD SPECIFICATION
FOR
DOCUMENTATION
REQUIREMENTS FROM
SUPPLIERS**

Abbreviations:

DCI	:	Document Control Index
edms	:	Electronic Document Management System
FOA	:	Fax of Acceptance
HOD	:	Head of Division / Department
IC	:	Inspection Certificate
IRN	:	Inspection Release Note
ITP	:	Inspection and Test Plan
LOA	:	Letter of Acceptance
MOU	:	Memorandum of Understanding
MR	:	Material Requisition
PO	:	Purchase Order
PR	:	Purchase
Requisition PVC	:	Polyvinyl Chloride
QMS	:	Quality Management System
TPIA	:	Third Party Inspection Agency
URL	:	Universal Resource Locator



PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Volume II
of II

Bid Document No. BGL/719/2025-26

CONTENTS

1.0	SCOPE	4
2.0	DEFINITIONS	4
3.0	REFERENCE DOCUMENTS	4
4.0	DOCUMENTATION REQUIREMENTS	4

Attachments

Format for completeness of Final

Documentation Annexure-1

1.0 SCOPE

This specification establishes the Documentation Requirements from Suppliers. All documents/data against the PO / PR / MR shall be developed and submitted to OWNER by the suppliers for review / records, in line with this specification.

2.0 DEFINITIONS

2.1 Supplier

For the purpose of this specification, the word "SUPPLIER" means the person(s), firm, company or organization who is under the process of being contracted by OWNER for delivery of some products (including service). The word is considered synonymous to bidder, contractor or vendor.

2.2 Owner

Owner means the owner of the project for which services / products are being purchased and includes their representatives, successors and assignees.

3.0 REFERENCE DOCUMENTS

VCS-SS-PP-2044 Standard Specification for Quality Management System Requirements from Vendors

4.0 DOCUMENTATION REQUIREMENTS

4.1 Documents/Data to be Submitted by the Supplier

4.1.1 The Supplier shall submit the documents and data against the PO/PR/MR as per the list given in respective PO/PR/MR.

4.1.2 Review of the supplier drawings by PMC/ OWNER would be only to review the compatibility with basic designs and concepts and in no way absolve the supplier of his responsibility/contractual obligation to comply with PR requirements, applicable codes, specifications and statutory rules/regulations. Any error/deficiency noticed during any stage of manufacturing/execution/installation shall be promptly corrected by the supplier without any time and cost implications, irrespective of comments on the same were received from OWNER during the drawing review stage or not.

4.1.3 Unless otherwise specified, submission of documents for Review/Records shall commence as follows from the date of Fax of Intent / Letter of Intent/ Fax of Acceptance (FOA)/ Letter of Acceptance (LOA):

QMS - 1 week

Drawing/Document Control Index - 2 weeks

Other Documents/Drawings - As per approved Drawing/Document Control

Index/Schedule

4.1.4 Documents as specified in PO/PR/MR are minimum requirements. Supplier shall submit any other document/data required for completion of the job as per OWNERs instructions.

4.2 Style and Formatting

4.2.1 All Documents shall be in ENGLISH language and in M.K.S System of units.

1.1.1 Before forwarding the drawings and documents, contractor shall ensure that the following information are properly mentioned in each drawing:

Purchase Requisition Number

Name of Equipment / Package

Equipment / Package Tag No.

Name of Project

Client

Drawing / Document Title

Drawing / Document No.

Drawing / Document Revision No. and Date

1.2 Review and Approval of Documents by Supplier

1.2.1 The Drawing/Documents shall be reviewed, checked, approved and duly signed/stamped by supplier before submission. Revision number shall be changed during submission of the revised supplier documents and all revisions shall be highlighted by clouds. Whenever the supplier requires any sub-supplier drawings to be reviewed by OWNER, the same shall be submitted by the supplier after duly reviewed, approved and stamped by the supplier. Direct submission of sub-supplier's drawings without contractor's approval shall not be entertained.

1.3 Document Category

1.3.1 Review Category

Following review codes shall be used for review of supplier Drawings/Documents:

Review Code A	-	No comments. Proceed with manufacture/fabrication as per the document.
Review Code B	-	Proceed with manufacture/fabrication as per commented document. Revised document required.
Review Code C	-	Document does not conform to basic requirements as marked. Resubmit for review
Review Code D	-	Document Rejected
Review Code F	-	For information
R	-	Document is retained for Records. Proceed with manufacture/fabrication.
V	-	Void

1.1 Methodology for Submission of Documents to PMC/Owner

1.1.1 Document Control Index (DCI)

Supplier shall create and submit Document Control Index (DCI) for review based on PO/PR/MR along with schedule date of submission of each drawing/document on OWNERs eDMS. The DCI shall be specific with regard to drawing/document no. and the exact title. Proper sequencing of the drawings/documents should be ensured in scheduled date of submission on of the job as per OWNER.

1.1.2 Submission of Drawings/Documents

Drawings/documents and data shall be uploaded on the eDMS Portal as per DCI

1.1.3 Statutory Approvals

Wherever approval by any statutory body is required to be taken by Supplier, the Supplier shall submit copy of approval by the authority to PMC/OWNER.

1.1.4 Details of Contact Persons of Supplier

After placement of order supplier shall assign a Project Manager for that order. The details are to be filled online through the portal. The details include e-mail address, mailing address, telephone nos., fax nos. and name of Project Manager. All the system generated emails pertaining to that order shall be sent to the assigned Project Manager.

1.1.5 Schedule and Progress Reporting

Supplier shall submit monthly progress report and updated procurement, engineering and manufacturing status (schedule vs. actual) every month, beginning within 2 weeks from FOA/LOA . In case of exigencies, PMC/Owner can ask for report submission as required on weekly/fortnightly/adhoc basis depending upon supply status and supplier shall furnish such reports promptly without any price implication. Format for progress report shall be submitted by the Supplier during kick off meeting or within one week of receiving FOA/LOA, whichever is earlier.

1.1.6 Quality Assurance Plan/Inspection and Test Plan

Inspection and test plans (ITP) attached if any, to the MR/PR are to be followed.

However for cases wherein ITPs have not been attached with MR/PR, Supplier shall submit within one week of receiving FOA/LOA, the Quality Assurance Plan for manufacturing, covering quality control of critical bought out items/materials, inspection& testing at various stages of production, quality control records and site assembly &testing as may be applicable to the specific order and obtain approval from OWNER /PMC/ third party inspection agency, as applicable.

For Package equipment contracts, the supplier shall prepare a list of items/ equipment's and their inspection categorization plan for all items included in the scope of supply immediately after receipt of order and obtains approval for the same from OWNER. The

items shall be categorized into different categories depending upon their criticality for the scope of inspection of TPIA and/or OWNER/ OWNER appointed PMC.

1.1.1 Inspection Release Note (IRN)/ Inspection Certificate (IC)

IRN/ IC shall be issued by PMC Inspector/ third party inspection agency on the basis of successful inspection, review of certificates as per specifications & agreed quality plan (as applicable) and only after all the drawings/documents as per DCI are submitted and are accepted under review code-A or code R. Supplier shall ensure that necessary documents/manufacturing and test certificates are made available to PMC/TPIA as and when desired.

Note: Non fulfilling above requirement shall result into appropriate penalty or withholding of payment as per conditions of PO/PR/MR.

Transportation Plan for Over Dimensional Consignments (ODC), if any, shall be submitted within 2 weeks of receiving FOA/LOA, for approval. Consignment with parameters greater than following shall be considered as over dimensional.

Dimensions: 4 meters width x 4 meters height x 20 meters length

Weight: 32 MT

1.2 Final Documentation

1.2.1 As Built Drawings

Shop changes made by Supplier after approval of drawings under 'Code A' by OWNER/OWNER appointed PMC and deviations granted through online system, if any, shall be marked in hard copies of drawings which shall then be stamped 'As-built' by the supplier. These 'As-built' drawings shall be reviewed and stamped by PMC Inspector/TPIA also. Supplier shall prepare scanned images files of all marked — up 'As — built drawings. Simultaneously Supplier shall incorporate the shop changes in the native soft files of the drawings also.

1.2.2 As Built Final Documents

As built final documents shall be submitted as listed in PO/PR/MR.

1.2.3 Packing/Presentation of Final Documents

Final Documents shall be legible photocopies in A4, A3 size only. Drawings will be inserted in plastic pockets (both sides transparent, sheet thickness minimum 0.1 mm) with an extra strip of 12 mm wide for punching so that drawings are well placed.

Final Documentation shall be bound in Hard board Plastic folder(s) of size 265 mm x 315 mm (10 1/2 inch x 12 1/2 inch) and shall not be more than 75 mm thick. It may be of several volumes and each volume shall have a volume number, index of volumes and index of contents of that particular volume. Where number of volumes are more, 90mm thickness can be used. Each volume shall have top PVC sheet of minimum 0.15mm thick duly fixed and pressed on folder cover and will have 2 lever clips. In case of imported items documents, 4 lever clips shall also be accepted. All four corners of folders shall be properly metal clamped. Indexing of contents with page numbering must be incorporated by supplier. Spiral/Spico bound documents shall not be acceptable. As mentioned above,

books should be in hard board plastic folders with sheets punched and having 2/4 lever clips arrangement.

Each volume shall contain on cover a Title Block indicating package Equipment Tag No. & Name, PO/Purchase Requisition No., Name of Project and Name of Customer. Each volume will have hard front cover and a reinforced spine to fit thickness of book. These spines will also have the title printed on them. Title shall include also volume number (say 11 of 15) etc.

1.1.1 Submission of Soft Copies

Supplier shall submit to OWNER, the scanned images files as well as the native files of Drawings / documents, along with proper index.

In addition to hard copies, Supplier shall submit electronic file (CD-ROM) covering soft copies of all the final drawings and documents, all text documents prepared on computer, scanned images of all important documents (not available as soft files), all relevant catalogues, manuals available as soft files (editable copies of drawings/text documents, while for catalogues/manuals/proprietary information and data, PDF files can be furnished).

All the above documents shall also be uploaded on the OWNERS eDMS portal.

1.1.2 Completeness of Final Documentation

Supplier shall get the completeness of final documentation verified by PMC appointed TPIA and attach the Format for Completeness of Final Documentation Format duly signed by OWNER/ OWNER appointed PMC/ Inspector or TPIA as applicable to the document folder.



PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Volume II
of II

Bid Document No. BGL/719/2025-26

ANNEUXRE-1

COMPLETENESS OF FINAL DOCUMENTATION

Name of Supplier/Contractor :

Customer :

Project :

OWNER's Job No. :

Purchase Order No./

Contract No. :

Purchase Requisition No./

Tender No. :

Rev. No. :

Name of the Work/

Equipment :

Tag. No. :

Supplier's/ Contractor's

Works Order No. :

Certified that the Engineering Documents/ Manufacturing & Test Certificates submitted by the supplier is complete in accordance with the Vendor Data Requirements of Purchase Requisition.

Signature :.....

Signature:.....

Date :.....

Date:.....

Name :.....

Name:.....

Designation :.....

Designation:.....

Department :.....

Department:.....

Supplier/Contractor

OWNER/PMC/TPIA



**PROCUREMENT OF STEEL PIPELINES IN
HYDERABAD GA**

Bid Document No. BGL/719/2025-26

Volume II
of II

**STANDARD SPECIFICATION
FOR
QUALITY MANAGEMENT
SYSTEM REQUIREMENT
FROM VENDORS**



Bhagyanagar
Gas Limited

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

Volume II
of II

Abbreviations:

CV : Curriculum Vitae
ISO : International Organization for Standardization
MR : Material Requisition
PO : Purchase Order
PR : Purchase
Requisition QA : Quality Assurance
QMS : Quality Management System



PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Volume II
of II

Bid Document No. BGL/719/2025-26

CONTENTS

1.0	SCOPE	4
2.0	DEFINITIONS	4
3.0	REFERENCE DOCUMENTS	4
4.0	QUALITY MANAGEMENT SYSTEM - GENERAL	4
5.0	QUALITY SYSTEM REQUIREMENTS	4
6.0	AUDITS	6
7.0	DOCUMENTATION REQUIREMENTS	7

1.0 SCOPE

This specification establishes the Quality Management System requirements to be met by BIDDER for following purpose:

- QMS requirements to be met by suppliers/contractors after award of work/ during contract execution.

2.0 DEFINITIONS

2.1 Bidder

For the purpose of this specification, the word "BIDDER" means the person(s), firm, company or organization who is under the process of being contracted by Owner for delivery of some products (including service). The word is considered synonymous to supplier, contractor or vendor.

2.2 Project Quality Plan

Document tailored from Standard Quality Management System Manual of BIDDER, specifying how the quality requirements of the project will be met.

2.3 Owner

Owner means the owner of the project for which services / products are being purchased and includes their representatives, successors and assignees.

3.0 REFERENCE DOCUMENTS

VCS-SS-PP-2043 Standard Specification for Documentation Requirements from Suppliers

4.0 QUALITY MANAGEMENT SYSTEM – GENERAL

Unless otherwise agreed with PMC / Owner, the BIDDER proposed quality system shall fully satisfy all relevant requirements of ISO 9001 "Quality Management Systems - Requirements." Evidence of compliance shall be current certificate of quality system registration to ISO 9001 or a recent compliance audit recommending registration from a certification agency. The quality system shall provide the planned and systematic control of all quality related activities for execution of contract. Implementation of the system shall be in accordance with BIDDER'S Quality Manual and PROJECT specific Quality Plan.

1.0 QUALITY SYSTEM REQUIREMENTS

1.1 BIDDER shall prepare and submit for review / record, Project Quality Plan / Quality Assurance Plan for contracted scope / job. The BIDDER'S Quality Plan shall address all of the applicable elements of ISO 9001, identify responsible parties within BIDDER'S organization, for the implementation / control of each area, reference the applicable procedures used to control / assure each area, and verify the documents produced for each area. The Project Quality Plan shall necessarily define control or make reference to the relevant procedures, for design and engineering, purchase, documentation, record control, bid evaluation, inspection, production/manufacturing, preservation, packaging and storage, quality control at

construction site, pre-commissioning, commissioning and handing over (as applicable) in line with contract requirement and scope of work.

5.2 BIDDER shall identify all specified or implied statutory and regulatory requirements and communicate the same to all concerned in his organization and his sub contractor's organization for compliance.

5.3 BIDDER shall deploy competent and trained personnel for various activities for fulfilment of PO / contract. BIDDER shall arrange adequate infrastructure and work environment to ensure that the specification and quality of the deliverable are maintained.

5.4 BIDDER shall do the quality planning for all activities involved in delivery of order. The quality planning shall cover as minimum the following:

- Resources
- Product / deliverable characteristics to be controlled.
- Process characteristics to ensure the identified product characteristics are realized
- Identification of any measurement requirements, acceptance criteria
- Records to be generated
- Need for any documented procedure

The quality planning shall result into the quality assurance plan, inspection and test plans (ITPs) and job procedures for the project activities in the scope of bidder.

These documents shall be submitted to PMC/Owner for review/approval, before commencement of work.

5.5 Requirements for sub-contracting / purchasing of services specified in contract / tender shall be adhered to. In general, all outsourced items will be from approved vendors of OWNER. Wherever requirements are not specified, or approved sub vendors do not exist, the sub-contractor shall establish and maintain a system for purchasing / sub-contracting to ensure that purchased product / service conforms to specified requirements. Criteria for selection of sub-contractor, evaluation, re-evaluation, maintenance of purchasing data and verification of purchased product (subcontractor services), constitute important components of this requirement.

5.6 BIDDER shall plan and carry production and service provision under controlled conditions. Controlled conditions shall include, as applicable the availability of information that describes the characteristics of the product the availability of work instructions the use of suitable equipment the availability and use of monitoring and measuring devices the implementation of monitoring and measurement the implementation of release, delivery and post-delivery activities.

5.7 BIDDER shall validate any processes for production and service provision where resulting output cannot be verified by subsequent monitoring and measurement. This includes any process where deficiencies become apparent only after the product is in use or service has been delivered.

5.8 BIDDER shall establish a system for identification and traceability of product /deliverable throughout product realization. Product status with respect to inspection and testing requirements shall be identified.

5.9 BIDDER shall identify, verify, protect and safeguard PMC / Owner property (material / document) provided for use or incorporation into the product. If any OWNER/ PMC property is lost, damaged or otherwise found to be unsuitable for use, this shall be reported to the OWNER/ PMC.

5.10 BIDDER shall ensure the conformity of product / deliverable during internal processing and delivery to the intended destination. Requirements mentioned in the tender shall be adhered to.

5.11 BIDDER shall establish system to ensure that inspection and testing activities are carried out in line with requirements. Where necessary, measuring equipment's shall be calibrated at specified frequency, against national or international measurement standards; where no such standard exists, the basis used for calibration shall be recorded. The measuring equipment's shall be protected from damage during handling, maintenance and storage.

5.12 BIDDER shall ensure effective monitoring, using suitable methods, of the processes involved in production and other related processes for delivery of the scope of contract.

5.13 BIDDER shall monitor and measure the characteristics of the product/deliverable to verify that product requirement has been met. The inspection (stage as well as final) by BIDDER and OWNER / Owner personnel shall be carried out strictly as per the ITPs forming part of the contract. Product release or service delivery shall not proceed until the planned arrangements have been satisfactorily completed, unless otherwise approved by relevant authority and where applicable by Owner / PMC.

5.14 BIDDER shall establish and maintain a documented procedure to ensure that the product which does not conform to requirements is identified and controlled to prevent its unintended use or delivery.

5.15 All non-conformities (NCs) / deficiencies found by the BIDDER'S inspection /surveillance staff shall be duly recorded, including their disposal action shall be recorded and resolved suitably. Effective corrective and preventive action shall be implemented by the BIDDER so that similar NCs including deficiencies do not recur.

5.16 All deficiencies noticed and reported by PMC / OWNER shall be analysed by the BIDDER and appropriate corrective and preventive actions shall be implemented. BIDDER shall intimate PMC / OWNER of all such corrective and preventive action implemented by him.

5.17 BIDDER should follow the standards, specifications and approved drawings. Concessions/Deviations shall be allowed only in case of unavoidable circumstances. In such situations Concession/deviation request must be made by the BIDDER through online system of OWNER/ PMCs eDMS.

5.18 BIDDER shall have documented procedure for control of documents.

5.19 All project records shall be carefully kept, maintained and protected for any damage or loss until the project completion, then handed over to PMC / Owner as per contract requirement (VCS-SS-PL-0047 Specification for Documentation Requirements from Suppliers), or disposed as per relevant project procedure.

6.0 AUDITS

BIDDER shall plan and carry out the QMS audit for the job. Quality audit programme shall cover design, procurement, construction management and commissioning as applicable including activities carried out by sub-vendors and sub-contractors. This shall be additional to the certification body surveillance audits carried out under BIDDER'S own ISO 9001 certification scheme.

The audit programmes and audit reports shall be available with bidder for scrutiny by PMC

/ OWNER. PMC or OWNER representative reserves the right to attend, as a witness, any audit conducted during the execution of the WORKS.

In addition to above OWNER, PMC and third party appointed by PMC/Owner may also perform Quality and Technical compliance audits. BIDDER shall provide assistance and access to their systems and sub-contractor / vendor systems as required for this purpose. Any deficiencies noted shall be immediately rectified by BIDDER.

7.0 DOCUMENTATION REQUIREMENTS

BIDDER shall submit following QMS documents immediately after award of work (Within one week) for record / review by PMC/ Owner.

- Organization chart (for complete organization structure and for the project)
- Project Quality Plan/Quality Assurance Plan
- Job specific Inspection Test Plans, if not attached with PR
- Job Procedures
- Inspection/Test Formats

In addition to above QMS documents, following documentation shall be maintained by the BIDDER for submission to PMC / Owner on demand at any point of time during execution of the project.

- Quality Manual
- Certificate of approval for compliance to ISO: 9001 standards
- Procedure for Control of Non-conforming Product
- Procedure for Control of Documents
- Sample audit report of the QMS internal and external audits conducted during last one year
- Customer satisfaction reports from at least 2 customers, during the last one year
- Project QMS audit report
- Technical audit reports for the project
- Corrective action report on the audits



PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

Volume II
of II

Documents as specified above are minimum requirements. BIDDER shall submit any other document/data required for completion of the job as per PMC/Owner instructions.



Bhagyanagar
Gas Limited

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

Volume II
of II

LIST OF ACCEPTABLE STEEL PLATE / COIL / BILLETS MANUFACTURERS

LIST OF ACCEPTABLE STEEL PLATE/ COIL MANUFACTURERS

The following Steel manufacturers are acceptable for the supply of Plate/ Coil to be used in the manufacture of quoted line pipes.

1. FOR PLATES: (Up to X-70)

S.NO.	VENDOR NAME
1.	Mannesmann Salzgitter Roehrenwerke, Germany
2.	Dillinger, Germany
3.	JSW Steel, USA
4.	Ilva ,Italy
5.	Azovstahl, Ukraine
6.	Arcelor Mittal, France/ Germany
7.	Nippon Steel, Japan
8.	Usiminas, Brazil
9.	POSCO, South Korea
10.	Arcelor Mittal Nippon Steel India (earlier Essar Steel, India)
11.	Voest alpine, Austria
12.	Welspun PCMD, India
13.	Baoshan Iron & Steel Co. Ltd., Shangai,China
14.	Jindal Steel & Power Ltd. (upto WT 20.6 mm)
15.	Sumitomo Metal, Japan
16.	Rourkela Steel Plant (SAIL) (up to WT 23.8 mm)

Legend:

WT: Wall Thickness

2. FOR COILS: (Up to X-70)

S.NO.	VENDOR NAME
1.	ThyssenKrupp, Germany
2.	AHMSA (Altos Hornos De Mexico), Mexico
3.	Baoshan Iron & Steel Co. Ltd., Shangai,China
4.	Wuhan Iron & Steel, China
5.	US Steel Kosice, Slovak Republic

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

Volume II
of II

6.	Arcelor Mittal Nippon Steel India (earlier Essar Steel, India)
7.	Erdemir, Turkey
8.	POSCO, South Korea
9.	TISCO (Group) Co. Ltd, China
10.	Maanshan Iron & Steel Co. Ltd., China
11.	Jinan Iron & Steel Co. Ltd., China
12.	Benxi Iron & Steel, China
13.	Jiangsu Shagang (Group), China
14.	Shou-gang Qian Iron & Steel Co. Ltd., China
15.	Hyundai Steel, South Korea
16.	Hadeed Saudi Iron & Steel Co., Saudi Arabia
17.	Hunan Valin Lianyuan Steel Co. Ltd. China (Arcelor Mittal Group)
18.	Arcelor Mittal, France/ Germany
19.	Anyang Iron & Steel Group Co.Ltd. China
20.	Angang Steel Co.Ltd., China
21.	HBIS Hebei Iron & Steel Group Co.Ltd, China
22.	Megasteel, Malaysia (WT up to 10.3mm)
23.	JSW steel limited, Dolvi (earlier Ispat (WT up to 11.7mm)
24.	SAIL, Bokaro (WT up to 11.1mm)
25.	JSW Steel Limited, Vijayanagar, Bellary, India
26.	Tata Steel Limited, Jamshedpur (Up to API 5L X-60, WT up to 9.53mm)
27.	Tata Steel Limited, Kalinganagar (WT up to 16.0mm)
28.	Tata Steel BSL Limited, Meramandali (WT up to 12.7mm)
29.	Inner Mongolia Baotou Steel Union Co. Ltd. China (WT up to 12.8 mm)
30.	Baosteel Zhanjiang Iron & Steel Co. Ltd., China (WT up to 12.8 mm)
31.	Jindal Steel Power Ltd, Raigarh (up to WT 16 mm)

Legend:

WT: Wall Thickness

1. FOR BILLETS:



Bhagyanagar
Gas Limited

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

Volume II
of II

S.NO.	VENDOR NAME
1.	Jindal Steel Limited, Vijay Nagar
2.	Jindal Steel & power Limited, Raigarg, Chhatisgarh
3.	JSW Steel Limited, Salem
4.	Kalyani Steel Limited, Hospet

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

(HFW/ERW)

LINE PIPE MANUFACTURING MILL CAPABILITY CERTIFICATION

This is to certify that M/s _____ reference plant's production line _____ has following manufacturing facilities to manufacture _____ (type of pipes) line pipes as per API SL PSL2 or equivalent.

Sl. No.	Description	Inspection Agency	
		Observation	Remarks on Conformity
A	GENERAL INFORMATION		
1.0	Detailed description of Organization (Structure, number of Employees, facilities, equipments, etc.) concerning the following:		
1.1	Overall structure of Mill Organization		
1.2	Line Pipe production facilities and Capacity		
1.3	Testing Laboratories		
1.4	Quality Control/Quality Assurance (QA/QC): Type and location of the testing facility and step-by-step operations followed to achieve High quality product as per technical specifications.		
1.5	Non-Destructive testing facilities.		
1.6	Latest Audit certified documents performed during production by one of the International Inspection Agencies (as listed in SCC).		
2.0	Company has valid ISO 9001-2000 Certificate and established Quality manual.		
B	FABRICATION & INSPECTION PROCEDURES		
1.0	Give detailed description of the Fabrication Process to produce Line pipes as per technical documents		
1.1	Inspection of raw material (Plates/Coils)		
1.2	Forming of the plates/Coils		

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

Sl. No.	Description	Inspection Agency	
		Observation	Remarks on Conformity
1.3	De-coiling and Inspection		
1.4	Edge preparation		
1.5	Forming		
1.6	Welding		
1.7	Testing		
2.0	Following shall be certified for Mill capability:		
2.1	Inspection of raw material (Plates/Coils) The machine shall have an inbuilt edge machining and Ultrasonic testing to test about 25mm width on both sides of the plate edges.		
2.2	Forming of the Plates/ Coils During Forming and welding the machine should have tracking system to control welding groove and edge offsets.		
2.3	Welding Pipe mill shall have a continuous tack welding arrangement for better dimensional control, minimum repairs and higher production. Weld procedure qualified shall ensure testing of Impact at -20° C for Weld and HAZ.		
2.4	Inspection & Testing		
	Type and location of the testing facility and step-by-step operations followed to achieve High quality product as per technical specifications.		
	List of all relevant NDT procedures (including Acceptance criteria)		
	List of NDT qualified personnel with valid ASNT-1A certificates for level III and Level II operators.		
	Ultrasonic machines being used should		



PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Volume II
of II

Bid Document No. BGL/719/2025-26

Sl. No.	Description	Inspection Agency	
		Observation	Remarks on Conformity
	ensure tracking of weld seam during testing and representing defects on a printout.		
	All instruments used shall have a valid Calibration certificates.		
	Capability of mill and procedure followed to produce pipes within the technical specifications with special attention to clause number 7.2 of TS {Out of roundness limited to 5 mm).		
	HSAW mill shall ensure, prove and establish adequate methodology that the residual stresses are within acceptable limits (at least equal to cold expanded pipes).		
	Capability of Mill and procedure followed to perform Impact test at -20/0 Deg.C. as per technical document requirements.		
	Work Instructions and approved procedures to be displayed at each and every work centres for ready reference		
	Various procedures established shall have approval from International Inspection agencies as listed in SEC.		

Overall acceptability

Acceptable / Not Acceptable

For & On behalf of

Signature
Name

Designation

Agency's name & Seal

Note: All pages of this report (Form-10A) shall be signed and stamped by the agency

FORMAT-13A

3 LPE EXTERNAL I INTERNAL COATING PLANT CAPABILITY ASSESSMENT

This is to certify that M/s _____ reference plant's production line has following coating facilities to undertake 3 LPE External Coating and Internal Liquid Epoxy coating of Bare Line Pipes as per relevant standards attached in bid document.

S. No.	DESCRIPTION	INSPECTION AGENCY	
		OBSERVATION	REMARKS ON CONFORMITY
A.	GENERAL INFORMATION		
1.0	Detailed description of Organisation (Structure, number of employees, facilities, equipments, etc.) concerning the following		
1.1	Overall structure of Plant Organisation		
B	EXTERNAL AND INTERNAL COATING FACILITIES & CAPACITY		
1.0	Testing Laboratories		
1.1	Quality Control/ Quality Assurance (QA / QC): Type and location of the testing facility and step-by-step operations followed to achieve high quality product as per technical specifications.		
1.2	Company shall have valid ISO 9001- 2000 certificate and established quality manual.		
C	3 LPE COATING & INSPECTION PROCEDURES		
1.0	Give detailed description of the coating process to produce coated pipes as per technical documents.		
1.1	Identification		
1.2	Review of the manufacturer's certificates of Base material (PE/Epoxy/Adhesive)		
1.3	Inspection of raw material (Epoxy/ Adhesive/ PE) batch wise at vendor laboratory		
	Surface preparation (Blasting & surface treatment)		
1.4	Pre-heating before abrasive blasting		



Bhagyanagar Gas Ltd.
Bhagyanagar Gas Limited

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

Volume II
of II

S. No.	DESCRIPTION	INSPECTION AGENCY	
		OBSERVATION	REMARKS ON CONFORMITY
1.6	Phosphoric acid treatment		
1.7	PH of pipe surface after phosphoric acid wash		
1.8	Salt contamination check after abrasive blasting		
1.9	Anchor pattern and degree of cleaned surface & degree of dust		
D	COATING		
2.1	Temperature of pipe before chromate application and visual application		
2.2	Temperature of pipe before epoxy application		
2.3	Temperature of PE, adhesive, epoxy		

12.4 Coating chamber and cooling chamber (inter coat time I cure time)

2.5	Epoxy chamber/ gun location/ number of guns / gun pressure		
2.6	PE & adhesive extruders RPM		
2.7	Line speed. Monitoring system for line speed shall be in place		
2.8	Epoxy/Adhesive/ PE film thickness/ Total coating thickness		
2.9	Following shall be certified for Plant Capability:		
2.10	<u>Inspection of Raw Material (Epoxy /Adhesive/ PE)</u> The plant shall have all in house test facilities for batch testing of incoming raw materials		
2.11	<u>Pre Heating of Pipes before blasting</u> Mill shall be equipped with required number of blasting stations and pre heating arrangement before 1 st blasting and also with facility for surface treatment before blasting (DM water wash station)		
2.12	<u>Surface Treatment</u> Mill shall be equipped with surface treatment facilities (chromating) before pre heating before epoxy chamber		

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Volume II
of II

Bid Document No. BGL/719/2025-26

S. No.	DESCRIPTION	INSPECTION AGENCY	
		OBSERVATION	REMARKS ON CONFORMITY
2.13	<u>Pre heating before Epoxy application</u> Induction heater with high temperature tripping system along with visual and audio alarm indicators shall be installed		
2.14	<u>Number of Epoxy guns and Positioning before adhesive application:</u> Number of guns and gun pressure shall be sufficient to achieve desired thickness of epoxy on the pipe surface. Positioning / location (distance before adhesive application) of guns should be maintained to satisfy cure time requirement of epoxy.		
2.15	PE / Adhesive Extruders: PE / adhesive extruders RPM shall be maintained to achieve adhesive and final coating thickness.		
2.16	Cooling Chamber (Chiller): Length of cooling chamber should be sufficient to attain the coating pipe temperature out of cooling chamber as per requirement.		
2.17	Total coating thickness		

IE

11.1

Inspection and Testing

In house testing facility for all the lab testing and plant testing shall be in place

1.2	All the testing procedures for Raw material testing, 1 st day production testing and routine testing shall be available.		
1.3	Lab testing: Raw Material testing Procedure qualification testing Routine testing etc.		
1.4	Plant testing: Impact test, Holiday test, Peel off testing, Procedures qualification tests, St Andrew Cross Test, cathodic disbandment test, Test on partly coated pipes etc.		
S. No.	DESCRIPTION	INSPECTION AGENCY	
		OBSERVATION	REMARKS ON CONFORMITY

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

1.5	All instruments used shall have valid calibration certificates. Availability of calibration reference standards and instruments.		
1.6	Final Dimensional & Visual check (cut back on both ends of the pipe)		

Internal Coating

	For internal coating facility for the in house testing of raw material and long duration procedure qualification test shall be ensured.		
1.2	Dust level after internal blasting to be ensured.		
1.3	Mixing ratio of Hardener and Liquid epoxy to be ensured.		

11.4 | Facilities at yard for handling and storage of internal coated pipes to be ensured.

1.5	Work instructions and procedures to be displayed at each and every work station for ready reference for both internal / external coating.		
1.6	Various procedures established shall have approval from international inspection Agencies.		
G	Documentation & final certification		

Overall acceptability:

ACCEPTABLE / NOT ACCEPTABLE

For & On behalf of

Signature
Name

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

Design
ation

Agency's Name & Seal

Note: all pages of this report (Form-13) shall be signed and stamped by agency

SL. NO.	NAME OF TPIA
1	Det Norske Veritas (DNV)
2	Germanischer Lloyd Industrial Services GmbH
3	Bureau Veritas (India) Pvt. Ltd.
4	Moody International (India) Pvt. Ltd. (Industry Services Division)
5	SGS India Pvt. Ltd.
6	Certification Engineer International Limited (CEIL)
7	TÜV SÜD South Asia Pvt. Ltd.
8	ABS Industrial Verification (India) Pvt. Ltd.
9	Lloyd Register of Industrial Services
10	IRCLASS Systems and Solutions Private Limited
11	Tata Projects Limited
12	International Certification Services Pvt. Ltd.
13	TUV India Pvt. Ltd., Industrial Services Division



Bhagyanagar
Gas Limited

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

Volume II
of II

14	Intertek India Pvt. Ltd. (Industry Services Division)
15	Quality Austria Central Asia Pvt. Ltd.
16	Edlipse Engineering Global Pvt. Ltd.



Bhagyanagar
Gas Limited

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA

Bid Document No. BGL/719/2025-26

Volume II
of II

SECTION : 9 SCHEDULE OF RATESS



**PROCUREMENT OF STEEL PIPELINES IN
HYDERABAD GA**

Bid Document No. BGL/719/2025-26

Volume II
of II



SCHEDULE OF RATES: ITEM NO-01

ITEM NO. 1: 3LPE EXTERNALLY COATED CARBON STEEL PIPE (12" x 6.4mm)

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA'S

Bid Document No. BGL/719/2025-26

Item No.	Pipe Size (Inch.)	W.T. (mm)	Grade/d. / Code of Pipe	Type of Line Pipes Quoted	Total Qty. (Mtrs.)	EX-works price quoted by the bidder (including packing & forwarding, but excluding Inland Transportation & GST to Delivery Location) including cost of Inspection by Third Party Agency, etc. (wherever applicable)	Inland transportation up to Delivery location including transit insurance, unloading & stacking and other costs incidental to delivery of goods	GST (CGST & SGST / UTGST or IGST) on the finished goods i.e. on Column (4) excluding inland transportation		GST on Inland transportation i.e. on Column (5)	Unit FOT site price inclusive all taxes & duties, inland transportation, transit insurance, unloading and stacking at site	Total FOT site price inclusive all taxes & duties, inland transportation, transit insurance, unloading and stacking at site	Harmonized System Nomenclature (HSN)
						(INR per meter)	Amount (INR per meter)	%	Amount (INR per meter)	%	Amount (INR per meter)	(INR per meter)	
(1)	(2)			(3)	(4)	(5)	(6A)	(6B)	(7A)	(7B)	(8) = (4) + (5) + (6B) + (7B)	(9) = (8) x (3)	(10)
The scope covers engineering, manufacture, inspection, factory testing and supply, transportation, unloading and stacking of External Coated Carbon Steel Pipes in accordance with the requirements of this tender.													
ITEM NO. 3LPE EXTERNALLY COATED CARBON STEEL PIPE (12" x 6.4mm) (approx.11.5m to12.5m)													
NAME OF THE BIDDER :													
1	12"	6.4	X5 2	API5L	Coated	ERW	2000.00				-	-	-
Grand Total												0.00	
Amount in Words													



SCHEDULE OF RATES: ITEM NO-02

ITEM NO. 2: 3LPE EXTERNALLY COATED CARBON STEEL PIPE (10" x 6.4mm)

PROCUREMENT OF STEEL PIPELINES IN HYDERABAD GA'S

Bid Document No. BGL/719/2025-26

Item No.	Pipe Size (Inch.)	W.T. (mm)	Grade	Std./ Code	Type of Pipe	Type of Line Pipes Quoted	Total Qty. (Mtrs.)	Ex-works price quoted by the bidder (including packing & forwarding, but excluding Inland Transportation & GST to Delivery Location) including cost of Inspection by Third Party Agency, etc. (wherever applicable)	Inland transportation up to Delivery location including transit insurance, unloading & stacking and other costs incidental to delivery of goods Description of Item and excluding GST	GST (CGST & SGST / UTGST or IGST) on the finished goods i.e. on Column (4) excluding inland transportation		GST on Inland transportation i.e. on Column (5)	Unit FOT site price inclusive all taxes & duties, inland transportation, transit insurance, unloading and stacking at site	Total FOT site price inclusive all taxes & duties, inland transportation, transit insurance, unloading and stacking at site	Harmonized System Nomenclature (HSN)	
								(INR per meter)	Amount (INR per meter)	%	Amount (INR per meter)	%	Amount (INR per meter)	(INR per meter)	(INR)	
(1)	(2)					(3)	(4)	(5)	(6A)	(6B)	(7A)	(7B)	(8) = (4) + (5) + (6B) + (7B)	(9) = (8) x (3)	(10)	
The scope covers engineering, manufacture, inspection, factory testing and supply, transportation, unloading and stacking of External Coated Carbon Steel Pipes in accordance with the requirements of this tender.																
ITEM NO. 3LPE EXTERNALLY COATED CARBON STEEL PIPE (10" x 6.4mm) (approx.11.5m to12.5m)																
NAME OF THE BIDDER :																
2	10	6.4	X52	API5L	Coated	ERW	9,000.00				-		-	-	-	
														Grand Total	0.00	
Amount in Words																